Mechanical Seal Face Material Datasheet

Document No: DS-SEAL-05 Revision: B Date: 2023-01-30

Face material limits

Face pairing	Max continuous temp (deg C)	Max pressure (bar)	Notes
Carbon vs Silicon Carbide	95	16	Prone to thermal cracking above limit
Silicon Carbide vs Silicon Carbide	150	25	Sensitive to dry running
Carbon vs Ceramic	80	10	Not for abrasive fluids

Select face materials with at least 10 percent margin below the maximum continuous temperature.