CoolPAK™ S5819

Mixed Metal Semisynthetic

CoolPAK™ S5819 provides good cooling and medium to high mechanical lubricity for machining and grinding cast iron as well as a wide range of mixed metals, including aluminium alloys, stainless steels and titanium.

Application Guidelines

- Not recommended for use on very reactive metals such as magnesium.
- Running at or above 7% offers the best sump life and corrosion inhibition on cast iron chips.
- In mixed-metal situations, concentration control, over 7%, is critical to fight galvanic corrosion.
- For additional product application information, including performance optimisation, please contact your Master Fluid Solutions' Authorised Distributor at https://www.masterfluids.com/eu/en/distributors/index.php, your District Sales Manager, or call our Tech Line at +49 211 41 72 8 -900.

Physical Properties Typical Data

Colour (Concentrate)	Light brown
Colour (Working Solution)	Light amber
Odour (Concentrate)	Mild Amine
Form (Concentrate)	Liquid
Flash Point (Concentrate)	> 160°C (ASTM D93-08)
pH (Concentrate as Range)	9.2 - 10.2
pH (Typical Operating as Range)	9.0 - 10.0
Coolant Refractometer Factor	2.0

Choose CoolPAK S5819:

- Long life
- Runs clean
- Formaldehyde releaser and boron free
- Machines high silica aluminium alloys
- Good for titanium machining applications
- Does not require special disposal or recycling
- Low foaming in high-pressure, high-volume applications
- Performs well where traditional soluble oils may not cool sufficiently
- Provides good corrosion inhibition on all ferrous and nonferrous metals

Health and Safety

For further information, see the most recent SDS which is available directly from Master Fluid Solutions or from your Master Fluid Solutions' Authorised Distributor.

Packaging

CoolPAK™ S5819

Mixed Metal Semisynthetic

Recommended Concentrations

Light Duty	5.0% - 7.0%
Moderate Duty	7.0% - 9.0%
Heavy Duty	9.0% - 10.0%
Design Concentration Range	5.0% - 10.0%

Mixing Instructions


- Recommended usage concentration in water: 5.0% - 10.0%
- To help ensure the best possible working solution, add the required amount of concentrate to the required amount of water (never the reverse) and stir until uniformly mixed.
- Use mineral-free water to improve sump life and corrosion inhibition while reducing carryoff and concentrate usage.

Additional Information

- Use Master STAGES™ Whamex XT™ for a quick and thorough precleaning of your machine tool and coolant system.
- Consult Master Fluid Solutions before using on any metals or applications not specifically recommended.
- This product should not be mixed with other metalworking fluids or metalworking fluid additives, except as recommended by Master Fluid Solutions, as this may reduce overall performance, result in adverse health effects, or damage the machine tool and parts. If contamination occurs, please contact Master Fluid Solutions for recommended action.

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation, or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. Contact your Master Fluid Solutions' District Sales Manager for the latest version of this document. Master STAGES™, CoolPAK™, and Whamex XT™ are trademarks of Master Chemical Corporation d/b/a Master Fluid Solutions.

Concentration by % Brix



% Concentration = Refractive Reading x Refractive Factor
Coolant Refractometer Factor % Brix = 2.0

Master Fluid Solutions WDG GmbH
Hasselsstraße 6-14
Düsseldorf, 40597
Germany

+49 211 41 72 82 00
info-eu@masterfluids.com
masterfluids.com/eu/en/