GREASES

BENTONE 2.

A clay-thickened, non-melting grease.

PRODUCT RANGE

Clay-Thickened & Non-Melting Greases

110 cSt	> 285 °C	2	Brown
Viscosity @ 40°C	Dropping point	NLGI grade	Colour

APPLICATION

- Bearings at elevated temperature
- Oven and dryer applications
- Where a soap grease would melt out

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Smooth, adhesive grease**
Colour	ASTM D1500	**Brown**
Thickener		**Organically modified clay**
NLGI Classification		**2**
Base Oil Viscosity @ 40°C (IP71), cSt		**110**
Oil Separation (IP121), %		**2.5**
Dropping Point (IP132), °C		**> 285**
Four Ball Weld Load (IP 239) kg		**200**
100 Hours @ 99°C Pressure Drop psi		**4.5**
Worked Penetration (IP50)		**265 to 295**
Copper Corrosion (IP112)		**1b**
Operating Temperature Range, °C	short periods to +160°C	**-20°C to +140**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0400

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063