GREASES

LITHIUM Z2.

A lithium grease loaded with 10% zinc oxide for extreme water resistance.

PRODUCT RANGE
Lithium Greases

110 cSt	185 min °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Marine and dockside bearings
- Washdown areas and wet process plant
- Pumping equipment running in water
- Anywhere a standard grease washes out

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Off White, Smooth**
NLGI Classification		**2**
Thickener		**Lithium Soap**
Base Oil		**Solvent Refined Min. Oil**
Base Oil Viscosity @ 40°C		**110**
Dropping Point (IP132), °C		**185 min**
Copper Corrosion (IP112)		**Pass**
Zinc Oxide Content, %		**10**
Worked Penetration (IP50)		**265 to 295**
Water Washout (ASTM D1264) @ 39°C, %		**2**
Water Washout (ASTM D1264) @ 79°C, %		**4**
EMCOR (IP220)		**0 : 0**
Operating Temperature Range, °C		**-30°C to +140**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0927

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063