GREASES

SARGREASE CGR2.

A calcium-thickened grease.

PRODUCT RANGE

Calcium & Calcium Sulphonate Greases

140 min °C	2	Black
Dropping point	NLGI grade	Colour

APPLICATION

- Worn plain bearings and slides
- Marine and humid industrial applications
- Extending the life of worn components
- Heavy slow-moving surfaces

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Smooth grease**
Colour	ASTM D1500	**Black**
NLGI Classification		**2**
Base Oil		**Highly refined mineral oil**
Base Oil viscosity @ 38°C, cSt		**110**
Thickener		**Calcium hydroxystearate**
Copper Corrosion (IP112)		**Pass**
Dropping Point (IP132)		**140°C min**
Resistance to Corrosion (Emcor IP220)		**0:0**
Water Washout (ASTM D1264) @ 38°C, %		**3**
Four Ball Weld Load (IP239) kg		**315**
Worked penetration (IP50)		**265 to 295**
Operating Temperature Range, °C		**-20°C to +110**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0928

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063