GREASES

SARGREASE LC2 MOLY.

A mixed lithium-calcium soap grease, which is a deliberate compromise and a good one: lithium brings mechanical stability and temperature capability, calcium brings water resistance, and the mixed soap gets a useful shar

PRODUCT RANGE
Lithium-Calcium Greases

APPLICATION

- Very high loads in wet conditions
- Plain bearings and pins exposed to washout
- Heavy plant working in water and mud

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Smooth grease**
Colour	ASTM D1500	**Grey/black**
NLGI Classification		**2**
Thickener		**Lithium-Calcium**
Copper Corrosion (IP112)		**Negative**
Aluminium Corrosion (mod IP112)		**Negative**
Mild Steel Corrosion (mod IP112)		**Negative**
Dropping Point (ASTM D566)		**170°C min**
Water Washout (IP215) @ 38°C, %		**2**
Water Washout (IP215) @ 79°C, %		**3**
Four Ball Weld Load (IP239)		**315kg**
Timken OK Load (IP326)	45lbs	**20kg**
Operating Temperature Range, °C		**-25°C to +140**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0408

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063