GREASES

SUPER MOLY 5.

A conventional lithium soap grease on solvent-refined mineral oil with an EP and anti-corrosion package, the most widely used grease chemistry there is, and for most general plant and vehicle greasing points the correct

PRODUCT RANGE
Lithium Greases

180 cSt	185 min. °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Extreme shock and boundary load conditions
- Heavy plant pins and bushes
- Slow oscillating joints carrying full load
- Very dusty and abrasive sites

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Smooth Grease**
Colour	ASTM D1500	**Grey / Black**
NLGI Classification		**2**
Thickener		**Lithium Soap**
Base Oil		**Mineral Oil**
Base Oil Viscosity @ 40°C (IP 71), cSt		**180**
Worked Penetration (IP 50)		**265 to 295**
Dropping Point (IP 132), °C		**185 min.**
Oil Separation (IP 121), %		**5 max.**
Copper Corrosion (IP 112)		**Pass**
Resistance To Corrosion Emcor (IP 220)		**0 : 0**
Water Washout (ASTM D1264) @ 39°C, %		**3**
Four Ball Weld Load (IP 239) kgs		**450**
Timken OK Load (IP 326) lbs		**50**
Oxidation Stability @ 100°C (IP 142) Pressure Drop After 100 hrs psi		**4**
Molybdenum Disulphide Content, %		**5**
Operating Temperature Range, °C		**-20°C to +140**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0781

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063