GREASES

SYNTHETIC HIGH TEMP 2-460.

A synthetic high temperature grease on a lithium complex thickener with PTFE.

PRODUCT RANGE

High Temperature Greases

APPLICATION

- Oven, dryer and stenter bearings
- Kiln car and furnace trolley bearings
- Hot process plant running continuously
- Bearings cycling between cold start and high heat

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Synthetic base stocks give a wider operating temperature window than a mineral equivalent
- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Smooth Brown Grease**
Thickener		**Lithium Complex**
NLGI Classification		**2**
Base Oil		**460 cSt Synthetic Blend**
Solid Lubricant		**PTFE**
Dropping Point (ASTM D2265), °C		**> 260**
Dynamic Corrosion Resistance (EMCOR) (IP 220)		**0 : 0**
Weld Load (Shell 4 Ball)		**355 Kgs**
Load Wear Index		**68 Kgs**
Corrosion (ASTM D130)		**1b**
dN Factor		**500,000**
Operating Temperature Range, °C		**-40°C to +170°C, short periods to +200**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0582

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063