GREASES

WTL 2 GREASE.

A lithium complex grease.

PRODUCT RANGE
Lithium Complex Greases

450 cSt	250 max °C	2
Viscosity @ 40°C	Dropping point	NLGI grade

APPLICATION

- Slow, heavily loaded bearings
- Wide operating temperature range applications
- Industrial and automotive general use

NOT RECOMMENDED

- × Applications requiring an NSF H1 food-grade grease
- × Mixing with greases of a different thickener type without purging the bearing first
- × Continuous service above the stated upper temperature limit

BENEFITS

- Stays in place under load, shock and vibration instead of being thrown off
- Resists water wash-out, protecting bearings in wet and wash-down areas
- Extended relubrication intervals reduce greasing labour and consumption
- Mechanically stable, will not soften and leak in service

TYPICAL PROPERTIES

PROPERTY	METHOD	TYPICAL
Appearance	Visual	**Brown smooth grease**
NLGI classification		**2**
Thickener		**Lithium complex**
Base Oil viscosity @40°C (IP71), cSt		**450**
Copper corrosion (IP112)		**Pass**
Water washout @38°C (IP215), %		**3**
Resistance to corrosion EMCOR (IP220)		**0 : 0**
Four Ball Weld Load (IP239)		**315kgs**
Wear Load Index		**62**
Timken OK Load (IP326)		**20kgs**
Dropping point (IP1322)		**250°C max**
Operating temperature range, °C		**-20°C to + 150**

Typical values. They do not form a specification.

PACK SIZES

400 g cartridge, 3 kg, 12.5 kg, 50 kg, 180 kg. Other pack sizes and bulk deliveries up to 25,000 litres are available on request.

HEALTH AND SAFETY

Read the safety data sheet before use. It covers handling, health and disposal and should be passed on to anyone who works with this product. Read all precautions on container labels.

SDS GR0907

SAR Lubricants (Squire A. Radcliffe & Sons Ltd) · Gill Bridge Works, Lowlands Road, Mirfield, WF14 8LU
+44 (0)1924 494371 · enquiries@sarlubricants.co.uk · sarlubricants.co.uk · Registered in England 05866783 · VAT 889171063