INSTITUTO TECNONÓLOGICO Y DE ESTUDIOS
SUPERIORES DE MONTERREY

A Review on Nano/Micro Fiber Fabrication Methods by Near-Field Electrospinning

Author(s):
Antonio Osamu KATAGIRI Tanaka; Héctor Alán AGUIRRE Soto;

ITESM Campus Monterrey
School of Engineering and Sciences

Monterrey, Nuevo León, June 12, 2019

INSTITUTO TECNONÓLOGICO Y DE ESTUDIOS SUPERIORES DE MONTERREY

Abstract

Faculty: Nanotechnology

School of Engineering and Sciences

A Review on Nano/Micro Fiber Fabrication Methods by Near-Field Electrospinning

by Antonio Osamu KATAGIRI Tanaka; Héctor Alán AGUIRRE Soto;

Lorem ipsum dolor sit amet, consectetur adipiscing elit, sed do eiusmod tempor incididunt ut labore et dolore magna aliqua. Ut enim ad minim veniam, quis nostrud exercitation ullamco laboris nisi ut aliquip ex ea commodo consequat. Duis aute irure dolor in reprehenderit in voluptate velit esse cillum dolore eu fugiat nulla pariatur. Excepteur sint occaecat cupidatat non proident, sunt in culpa qui officia deserunt mollit anim id est laborum.

keywords: nanotechnology, nano-fiber, near-field electrospinning, NFES

1 Summary

TABLE 1.1: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(ethylene oxide) (PEO)
Solvent(s):	Deionized water
NFES Variant:	Low-Voltage NFES
Polymer Solution and Process Properties:	• PEO Concentration: 1, 2, and 3 $wt\%$ • Rise in solution conductivity with the increase in PEO concentration • Solution Stirring: 24 h of free diffusion followed by 96 h of stirring at 30 rpm • 3 mL syringe • 27 gauge type 304 stainless steel needle • Solution deposition rate: lower than 1 $\mu L/h$ • needle-to-collector distance: 1 mm • Collector substrate: Pyrolyzed SU-8 carbon and Si • NFES process initiated by an air interference with a glass microprobe tip (1 to 3 μm tip diameter) to overcome the surface tension • Time to produce a stable continuous jet: 45 min • Polymer jet initiated at 400-600 V and dispensed at 200-400 V • Collector linear speed: 10-40 mm/s • The voltage turned on when the solution formed a full-sized droplet of 500 μm diameter at the needle tip.
Fiber Characterization:	• Diameter: 50-425 nm
Ref:	[1]

[9]
[10]
[11]
[12]
[14]
[13]

TABLE 1.2: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly[2-methoxy-5-(2-ethylhexyloxy)-1,4-phenylenevinylene] (MEH-PPV) with Poly(ethylene oxide) (PEO)
Solvent(s):	acetonitrile / toluene mixture (65 / 35); acetic acid / toluene (17 / 83); pure toluene
NFES Variant:	*Not determined.*
Polymer Solution and Process Properties:	• Concentrations: – MEH-PPV solution: 10 mg of MEH-PPV in 2 mL of toluene – 500 μL of MEH-PPV solution with 250 mg of PEO in 3.5 mL of acetonitrile / toluene (65 / 35) – 500 μL of MEH-PPV solution with 250 mg of PEO in 3 mL of acetic acid / toluene (17 / 83) – The resulting MEH-PPV/PEO concentration is 1:100 • Solution Stirring: MEH-PPV solution stirred for 4 h; PEO solution stirred for 8 h; MEH-PPV/PEO solution stirred and ultrasonically agitated • Collector substrate: SiO2/Si (oxide thickness = 800 nm) • needle-to-collector distance: 500 μm • μm-diameter tip Tungsten spinneret in a 26 gauge needle • Solution deposition rate: 50 $\mu L/h$ • Electrostatic voltage: around 1.3 kV • x-y stage velocity: 50 cm/s
Fiber Characterization:	• Distance between adjacent fibers: around 100 μm • Fiber diameter: around 100 nm
Ref:	[2]

[15]
[16]
[17]
[18]
[19]
[20]
[21]
[22]
[23]
[24]

TABLE 1.3: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(ethylene oxide) (PEO)
Solvent(s):	Water
NFES Variant:	Scanning Tip Electrospinning and NFES
Polymer Solution and Process Properties:	• 7 wt % PEO aqueous solution • Under room temperature at 1 atm • needle-to-collector distance: 500 μm • needle diameter: outer: 200 μm; inner: 100 μm • applied voltage for jet initiation: 1.5 kV • applied voltage for fiber deposition: 600 V • Mechanical drawing is applied by using a tungsten probe with 1 μm tip diameter to poke inside the meniscus. • The probe is then rapidly pulled away from the polymer droplet to activate the continuous electrospinning process • polymer jet diameter: 3 μm • polymer feed rate: 0.1 $\mu L/h$ • x-y stage velocity: 120 mm/s
Fiber Characterization:	• 108 m yield in 15 min with a fiber diameter of 709 $\pm$ 131 nm • Fiber diameter: around 49-74 nm when applied voltage is 800 V
Ref:	[3]

TABLE 1.4: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(ε-Caprolactone) (PCL)
Solvent(s):	*Not applicable.*
NFES Variant:	Melt Electrospinning Writing (MEW)
Polymer Solution and Process Properties:	• Collector substrate: NCO-sP(EO-stat-PO)-coated glass slide surfaces • Accelerating voltage 2.0–10.0 kV • Collector distance: 1–10 mm • Heating temperature: 80–120 $^{\circ}C$ • Feeding air pressure 0.5–4.0 bar • Spinneret diameters: 21, 23, 25, 27, 30, and 33 G • Axis velocity: 1000–9000 mm/min • Fibre spacing: 100 μm
Fiber Characterization:	• Filament surface is smooth and homogeneous • The crystalline regions formed perpendicular to the filament • Fiber diameter: 817 ± 165 nm
Ref:	[4]

TABLE 1.5: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(vinylidine fluorid) (PVDF)
Solvent(s):	N,N-dimethylformamide (DMF)
NFES Variant:	Helix Electrohydrodynamic Printing (HE-printing)
Polymer Solution and Process Properties:	• 1.8 g PVDF in 4.1 g of DMF and 4.1 g of acetone to obtain a concentration of 18% • Solution kept at 35 $^{\circ}C$ for about 6 h until the solution was homogeneous. • Collector substrate: Poly(dimethylsiloxane) (PDMS) on Ecoflex • Solution feed rate: 400 nL/min • Needle diameter: inner 260 μm; external 510 μm • Applied voltage: 1.5–3 kV • Nozzle-to-collector distance: 10-50 mm • x-y stage velocity: 0-400 mm/min • At room temperature and 35–45% humidity
Fiber Characterization:	• Stretchable serpentine structures with specific wavelength and amplitude. • Wavelength: about 100-2000 μm • Fiber diameter: about 1.5-3 μm
Ref:	[5]

TABLE 1.6: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Polyhedral Oligomeric Silsesquioxane-Poly(Carbonate-Urea)Urethane (POSS-PCU) and Polyhedral Oligomeric Silsesquioxane-Poly(Caprolactone-Poly(Carbonate-Urea)Urethane) (POSS-PCL-PCU)
Solvent(s):	Dimethylacetamide (DMAC) and 1-Butanol
NFES Variant:	Electrohydrodynamic 3D Print-patterning or Electrohydrodynamic Jetting
Polymer Solution and Process Properties:	• Solution concentration: POSS-PCU and POSS-PCL-PCU used in 20% w/w concentration in DMAC • Needle diameter: 750 μm • Applied voltage: 8.0-10.0 kV • Solution flow rate: less than 1 $\mu L/min$ • Needle-to-collector distance: about between 500 μm to 2 mm • x-y stage velocity: 10 mm/s • Ethanol-coated substrate
Fiber Characterization:	• Distance between adjacent fibers: 250 μm • Fiber diameter: 5-50 μm
Ref:	[6]

TABLE 1.7: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(ethylene oxide) (PEO)
Solvent(s):	Distilled water
NFES Variant:	Electrohydrodynamic Writing or Mechanoelectrospinning (MES)
Polymer Solution and Process Properties:	• Polymer solution weight concentration: 6 $wt\%$ PEO • Needle-to-collector distance: 7.5 mm • Applied voltage to initiate the jet: 2 kV • Applied voltage during deposition: 0.8-1 kV • Under the room temperature and relative humidity of about 25%. • x-y stage velocity: around 400 mm/s • Solution flow rate: 1200 nL/min
Fiber Characterization:	• Distance between adjacent fibers: 5 μm • Fiber diameter: 200-350 nm
Ref:	[7]

TABLE 1.8: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	Poly(ethylene oxide) (PEO)
Solvent(s):	Deionized water and the ethanol with a volume ratio of 3:1
NFES Variant:	Airflow-assisted Electrohydrodynamic Direct-writing (EDW)
Polymer Solution and Process Properties:	• Concentration: 8 $wt\%$ PEO • Outer airflow passage diameter: 1 mm • Airflow gas pump pressure: 25 kPa • Inner liquid passage diameter: 0.21 mm • Silicon substrate • Needle-to-collector distance: 2 mm • Solution flow rate: 30 $\mu L/h$ • Applied voltage: about 2 kV • x-y stage velocity: between 1-20 mm/s
Fiber Characterization:	• Fiber deposition position accuracy: 5.13 ± 6.67 μm • Fiber diameter: 3.73 ± 1.37 μm
Ref:	[8]

TABLE 1.9: Electrospun Polymer Solutions - Solution and Process Parameters

Polymer(s):	
Solvent(s):	
NFES Variant:	
Polymer Solution and Process Properties:	• 1
Fiber Characterization:	• a
Ref:	[1]

References

[1] Gobind S. Bisht et al. "Controlled Continuous Patterning of Polymeric Nanofibers on Three-Dimensional Substrates Using Low-Voltage Near-Field Electrospinning". In: *Nano Letters* 11.4 (Apr. 2011), pp. 1831–1837. ISSN: 1530-6984. DOI: 10.1021/nl2006164. URL: https://pubs.acs.org/doi/10.1021/nl2006164.

[2] Daniela Di Camillo et al. "Near-field electrospinning of conjugated polymer light-emitting nanofibers". In: *Nanoscale* 5 (2013), pp. 11637–11642. DOI: 10.1039/C3NR03094F. URL: https://arxiv.org/ftp/arxiv/papers/1310/1310.5101.pdf.

[3] Chieh Chang, Kevin Limkrailassiri, and Liwei Lin. "Continuous near-field electrospinning for large area deposition of orderly nanofiber patterns". In: *Appl Phys Lett* (2008), p. 3. DOI: 10.1063/1.2975834. URL: http://www-bsac.eecs.berkeley.edu/publications/search/send%7B%5C_%7Dpublication%7B%5C_%7Dpdf2client.php?pubID=1217995664.

[4] Paul D Dalton, T Joergensen, and Juergen Groll. "Additive manufacturing of scaffolds with sub-micron filaments via melt electrospinning writing Related content Patterned melt electrospun substrates for tissue engineering". In: (2015). DOI: 10.1088/1758-5090/7/3/035002. URL: https://iopscience.iop.org/article/10.1088/1758-5090/7/3/035002/pdf.

[5] Yongqing Duan et al. "Helix Electrohydrodynamic Printing of Highly Aligned Serpentine Micro/Nanofibers." In: *Polymers* 9.9 (Sept. 2017). ISSN: 2073-4360. DOI: 10.3390/polym9090434. URL: http://www.ncbi.nlm.nih.gov/pubmed/30965737%20http://www.pubmedcentral.nih.gov/articlerender.fcgi?artid=PMC6418525.

[6] Ashish Gupta et al. "Novel Electrohydrodynamic Printing of Nanocomposite Biopolymer Scaffolds". In: *Journal of BIOACTIVE AND COMPATIBLE POLYMERS* 22 (2007). DOI: 10.1177/0883911507078268. URL: https://journals.sagepub.com/doi/pdf/10.1177/0883911507078268.

[7] YongAn Huang et al. "Versatile, kinetically controlled, high precision electrohydrodynamic writing of micro/nanofibers". In: *Scientific Reports* 4.1 (May 2015), p. 5949. ISSN: 2045-2322. DOI: 10.1038/srep05949. URL: http://www.nature.com/articles/srep05949.

[8] Jiaxin Jiang et al. "Electrohydrodynamic Direct-Writing Micropatterns with Assisted Airflow". In: *Micromachines* 9.9 (Sept. 2018), p. 456. ISSN: 2072-666X. DOI: 10.3390/mi9090456. URL: http://www.mdpi.com/2072-666X/9/9/456.

[9] Jinseong Kim, Bohee Maeng, and Jungyul Park. "Characterization of 3D electrospinning on inkjet printed conductive pattern on paper". In: *Micro and Nano Systems Letters* 6.1 (Dec. 2018), p. 12. ISSN: 2213-9621. DOI: 10.1186/s40486-018-0074-1. URL: https://mnsl-journal.springeropen.com/articles/10.1186/s40486-018-0074-1.

[10] Jongwan Lee et al. "Fabrication of Patterned Nanofibrous Mats Using Direct-Write Electrospinning". In: *Langmuir* 28.18 (May 2012), pp. 7267–7275. ISSN: 0743-7463. DOI: 10.1021/la3009249. URL: http://pubs.acs.org/doi/10.1021/la3009249.

[11] Z H Liu et al. "Direct-write PVDF nonwoven fiber fabric energy harvesters via the hollow cylindrical near-field electrospinning process". In: (2014), pp. 25003–25014. DOI: 10.1088/0964-1726/23/2/025003. URL: http://iopscience.iop.org/0964-1726/23/2/025003.

[12] Sung-Yong Min et al. "Large-scale organic nanowire lithography and electronics". In: *Nature Communications* 4.1 (June 2013), p. 1773. ISSN: 2041-1723. DOI: 10.1038/ncomms2785. URL: http://www.nature.com/articles/ncomms2785.

[13] Cheng-Tang Pan et al. "Near-field electrospinning enhances the energy harvesting of hollow PVDF piezoelectric fibers". In: *RSC Advances* 5.103 (2015), pp. 85073–85081. ISSN: 2046-2069. DOI: 10.1039/C5RA16604G. URL: http://xlink.rsc.org/?DOI=C5RA16604G.

[14] Cheng-Tang Pan et al. *Poly(γ-benzyl α, l-glutamate) in Cylindrical Near-Field Electrospinning Fabrication and Analysis of Piezoelectric Fibers*. Tech. rep. 2. 2014, pp. 63–73. URL: https://myukk.org/SM2017/sm%7B%5C_%7Dpdf/SM971.pdf.

[15] Chiho Song et al. "Patterned polydiacetylene-embedded polystyrene nanofibers based on electrohydrodynamic jet printing". In: *Macromolecular Research* 23.1 (Jan. 2015), pp. 118–123. ISSN: 1598-5032. DOI: 10.1007/s13233-015-3024-2. URL: http://link.springer.com/10.1007/s13233-015-3024-2.

[16] Daoheng Sun et al. "Near-Field Electrospinning". In: (2006). DOI: 10.1021/nl0602701. URL: https://pubs.acs.org/doi/10.1021/nl0602701..

[17] Han Wang et al. "Research on Multinozzle Near-Field Electrospinning Patterned Deposition". In: *Journal of Nanomaterials* 2015 (July 2015), pp. 1–8. ISSN: 1687-4110. DOI: 10.1155/2015/529138. URL: http://www.hindawi.com/journals/jnm/2015/529138/.

[18] Zhifeng Wang et al. "Controllable deposition distance of aligned pattern via dual-nozzle near-field electrospinning". In: *AIP Advances* 7.3 (Mar. 2017), p. 035310. ISSN: 2158-3226. DOI: 10.1063/1.4974936. URL: http://aip.scitation.org/doi/10.1063/1.4974936.

[19] Zhifeng Wang et al. "Fabrication and evaluation of controllable deposition distance for aligned pattern by multi-nozzle near-field electrospinning". In: *AIP*

Advances 8.7 (July 2018), p. 075111. ISSN: 2158-3226. DOI: 10.1063/1.5032082. URL: http://aip.scitation.org/doi/10.1063/1.5032082.

[20] Jiachen Xu et al. "Accuracy Improvement of Nano-fiber Deposition by Near-Field Electrospinning". In: *International Workshop on Microfactories* IWMF2014.9th (2014). URL: http://conf.papercept.net/images/temp/IWMF/media/files/0041.pdf.

[21] Niannan Xue et al. "Rapid Patterning of 1-D Collagenous Topography as an ECM Protein Fibril Platform for Image Cytometry". In: *PLoS ONE* 9.4 (Apr. 2014). Ed. by Wei-Chun Chin, e93590. ISSN: 1932-6203. DOI: 10.1371/journal.pone.0093590. URL: https://dx.plos.org/10.1371/journal.pone.0093590.

[22] Gaofeng Zheng et al. "Precision deposition of a nanofibre by near-field electrospinning". In: *Journal of Physics D: Applied Physics* 43.41 (Oct. 2010), p. 415501. ISSN: 0022-3727. DOI: 10.1088/0022-3727/43/41/415501. URL: http://stacks.iop.org/0022-3727/43/i=41/a=415501?key=crossref.304f8be16661d1ca2c851060187b28

[23] Jiang-Yi Zheng et al. "Electrohydrodynamic Direct-Write Orderly Micro/Nanofibrous Structure on Flexible Insulating Substrate". In: *Journal of Nanomaterials* 2014 (May 2014), pp. 1–7. ISSN: 1687-4110. DOI: 10.1155/2014/708186. URL: http://www.hindawi.com/journals/jnm/2014/708186/.

[24] Jie Zheng et al. "Polymer nanofibers prepared by low-voltage near-field electrospinning". In: *Chinese Physics B* 21.4 (2012), pp. 1–6. ISSN: 16741056. DOI: 10.1088/1674-1056/21/4/048102.