Fabrication of graphitic-carbon suspended nanowires through mechano-electrospinning of photo-crosslinkable polymers

Osamu Katagiri-Tanaka
A01212611@itesm.mx

Principal Advisor: **Dr. Héctor Alán Aguirre Soto**
Co-advisor and Director of Program: **Dra. Dora Iliana Medina Medina**

25 Nov 2020

Agenda

• Motivation & Problem Statement	: 10 min
• Objectives	: 3 min
• NFES literature review	: 10 min
• Rheology Analyses	: 10 min
• Fabrication & Characterization	: 5 min
• Conclusions & Future Work	: 3 min

Motivation & Problem Statement

Carbon Based Nanomaterials (CBNs)



The crystallite size, molecular arrangement, and anisotropy determine the material's properties.

The interminable collection of CBNs range from soft, conductive lubricants to very hard, low conductivity solids; and from black colour, bulks to transparent, disordered thin films

R.L. McCreery, Advanced Carbon Electrode Materials for Molecular Electrochemistry, Chem. Rev. 108 (2008) 2646–2687. https://doi.org/10.1021/cr068076m.
S. Beigi-boroujeni, O. Katagiri-tanaka, B. Cardenas-benitez, O. Sergio, A. Aguirre-soto, Pyrolytic Carbon from Novolac Epoxy Resin Compressed before Photocrosslinking and Pyrolysis, Mater. Today Proc. (2020).

Carbon allotropes



R.B. Heimann, S.E. Evsvukov, Y. Koga, Carbon allotropes: a suggested classification scheme based on valence orbital hybridization, Carbon N. Y. 35 (1997) 1654–1658. https://doi.org/10.1016/S0008-6223(97)82794-7.
E.A. Belenkov, Classification of carbon structures, in: Carbon Nanotub. Graphene, Chelyabinsk State University, Chelyabinsk, Russia, 2003: p. 5.
M. Fedel, Blood compatibility of diamond-like carbon (DLC) coatings, in: Diamond-Based Mater. Biomed. Appl., Elsevier, 2013: pp. 71–102. https://doi.org/10.1533/9780857093516.1.71.
M. Razeghi, Fundamentals of Solid State Engineering, Springer International Publishing, Cham, 2019. https://doi.org/10.1007/978-3-319-75708-7.
K. Alstrup Jensen, J. Bøgelund, P. Jackson, N. Raun Jacobsen, R. Birkedal, P. Axel Clausen, A. Thoustrup Saber, H. Wallin, U. Birgitte Vogel, Carbon nanotubes - Types, products, market, and provisional assessment of the associated risks to man and the environment, The Danish Environmental Protection Agency, 2015.

Carbon allotropes



R.L. McCreery, Advanced Carbon Electrode Materials for Molecular Electrochemistry, Chem. Rev. 108 (2008) 2646–2687. https://doi.org/10.1021/cr068076m.
S. Beigi-boroujeni, O. Katagiri-tanaka, B. Cardenas-benitez, O. Sergio, A. Aguirre-soto, Pyrolytic Carbon from Novolac Epoxy Resin Compressed before Photocrosslinking and Pyrolysis, Mater. Today Proc. (2020).
Harry Marsh. Introduction to Carbon Science. Vol. 46. 1. Elsevier, Apr. 1989, p. 43. ISBN: 9780408038379. DOI: 10.1016/C2013- 0- 04111- 4. URL: https: //linkinghub.elsevier.com/retrieve/pii/C20130041114.
Pierson Hugh. Handbook of Carbon, Graphite, Diamonds and Fullerenes. Elsevier, 1994, p. 419. ISBN: 9780815513391.

Glass-like Carbon



Attractive for its electrochemical stability, thermal resistance, electrical conductivity, biocompatibility and is gas impermeable.

- It is used in the manufacture of semiconductors.

R.L. McCreery, Advanced Carbon Electrode Materials for Molecular Electrochemistry, Chem. Rev. 108 (2008) 2646–2687. https://doi.org/10.1021/cr068076m.
G. Speranza, The Role of Functionalization in the Applications of Carbon Materials: An Overview, C — J. Carbon Res. 5 (2019) 84. https://doi.org/10.3390/c5040084.

MicroChem's SU-8 & Tokai's recipe

Electrical resistivity, comparison:

highly oriented pyrolytic graphite (HOPG) $<_{\times 10^3}$ TOKAI Glassy carbon $<_{\times 4}$ SU-8 glass-like carbon

Tokai's recipe is a secret …

R.L. McCreery, Advanced Carbon Electrode Materials for Molecular Electrochemistry, Chem. Rev. 108 (2008) 2646–2687. https://doi.org/10.1021/cr068076m.
G. Speranza, The Role of Functionalization in the Applications of Carbon Materials: An Overview, C — J. Carbon Res. 5 (2019) 84. https://doi.org/10.3390/c5040084.

Current approaches

Photolithography
Physical & Optical Limitations



Two-Photon Polymerization (TPP)
Slow (mm per sec) & Expensive



*Near-Field Electrospinning (NFES)
Suspended Nanowires w/Spatial Control



V. Galstyan, M. Bhandari, V. Sberveglieri, G. Sberveglieri, E. Comini, Metal Oxide Nanostructures in Food Applications: Quality Control and Packaging, Chemosensors. 6 (2018) 16. https://doi.org/10.3390/chemosensors6020016.
D. Kluge, J.C. Singer, B.R. Neugirg, J.W. Neubauer, H.-W. Schmidt, A. Fery, Top–down meets bottom–up: A comparison of the mechanical properties of melt electrospun and self-assembled 1,3,5-benzenetrisamide fibers, Polymer (Guildf). 53 (2012) 5754–5759. https://doi.org/10.1016/j.polymer.2012.10.016.

Glass-like Carbon NWs: Applications



V. Baudrit J, Recycling and Elimination of Wastes obtained from Agriculture by using Nanotechnology: Nanosensors, Int. J. Biosens. Bioelectron. 3 (2017) 368–375.https://doi.org/10.15406/ijbsbe.2017.03.00084.
R.L. McCreery, Advanced Carbon Electrode Materials for Molecular Electrochemistry, Chem. Rev. 108 (2008) 2646–2687. https://doi.org/10.1021/cr068076m.
G. Speranza, The Role of Functionalization in the Applications of Carbon Materials: An Overview, C — J. Carbon Res. 5 (2019) 84. https://doi.org/10.3390/c5040084.

MicroChem's SU-8

However, SU-8 as is not electrospinnable
SU-8 does not have the right viscosity & solution conductivity.
SU-8 is design for photolithography.



SU-8 + TBF + PEO



Tetrabutylammonium tetrafluoroborate (TBF)

→ To increase the solution conductivity

Poly(ethylene oxide) (PEO)

→ To provided the required viscosity

... both needed for smooth PEO flow during electrospinning

D.R. Flores, Role of rheological properties in near field electrospun fibers morphology, (2017) 130.
B. Cárdenas Benítez, Advanced Manufacturing Techniques for the Fabrication and Surface Modification of Carbon Nanowires, Tecnológico de Monterrey, 2017.

NFES Process Parameters

- Properties of an electrospun fiber depend on many parameters,
- and each parameter also depends on the polymer-solvent system.

Solution Parameters:
- **Concentration**
- **Molecular weight**
- **Viscosity**
- **Electrical conductivity**

Ambient Parameters:
- **Humidity**
- **Temperature**

Process Parameters:
- **Applied Voltage**
- **Flow rate**
- **Working distance**

The interdependence between the process and solution parameters presents a challenge to predict the fiber morphology.

S.B. Gadkari, Scaling analysis for electrospinning, Springerplus. 3 (2014) 705. https://doi.org/10.1186/2193-1801-3-705.

Best Results so far by NFES (previous work)

Fiber yield rate of 81 %
Fiber diameter before pyrolysis of 4.966 μm
Fiber diameter after pyrolysis of 204 nm
Fiber length of 60.5 ± 4.3 μm
Fiber resistance from 407 KΩ to 1.727 MΩ

wt% PEO	SU-8 2002 [mg]	PEO [mg]	TBF [mg]
0.25	2246	5.65	11.32



D.R. Flores, Role of rheological properties in near field electrospun fibers morphology, (2017) 130.
B. Cárdenas Benítez, Advanced Manufacturing Techniques for the Fabrication and Surface Modification of Carbon Nanowires, Tecnológico de Monterrey, 2017.

Methods: Implications of PEO

The fiber yield rate and fiber conductivity are impacted negatively as PEO introduces more oxygen to the solution

Some samples are destroyed during pyrolysis

High variance in the obtained conductivity across samples.

The addition of oxygen decreases the char yield.



Poly(ethylene oxide) (PEO)

D.R. Flores, Role of rheological properties in near field electrospun fibers morphology, (2017) 130.
B. Cárdenas Benítez, Advanced Manufacturing Techniques for the Fabrication and Surface Modification of Carbon Nanowires, Tecnológico de Monterrey, 2017.

Objectives

Objectives

General. Formulate polymer/solvent combinations that have the greatest potential to replace or modify the SU-8/PEO formulation for the fabrication of microscopic polymer fibers that may be converted to conductive suspended carbon nano-wires.

Specific1. Learn how the diameter of the electrospun polymer fiber can be controlled by appropriate tuning of the NFES parameters and solution properties.

Specific2. Through rheological analyses, determine if polymer solutions have comparative viscoelastic properties to those of the SU-8/PEO benchmark, and if they can be easily electrospun by NFES.

Specific3. Propose alternatives to the SU-8/PEO benchmark formulation for the production of microscopic polymer fibers with potential for the fabrication of carbon nano-wires.

Specific Objective 1. Learn how the diameter of the electrospun polymer fiber can be controlled by appropriate tuning of the NFES parameters and solution properties.

NFES literature review

Methods: NFES literature
(first NFES apparatus built in 2003 by J. Kameoka et al.)



Thinnest fiber achieved by C. Chang et al. with ~50 nm in diameter. (PEO in water)

However, fiber yield rate was not reported

J. Kameoka, R. Orth, Y. Yang, D. Czaplewski, R. Mathers, G.W. Coates, H.G. Craighead, A scanning tip electrospinning source for deposition of oriented nanofibres, Nanotechnology. 14 (2003) 1124–1129. https://doi.org/10.1088/0957-4484/14/10/310.
C. Chang, K. Limkrailassiri, L. Lin, Continuous near-field electrospinning for large area deposition of orderly nanofiber patterns, Appl Phys Lett. (2008) 3. https://doi.org/10.1063/1.2975834.

Methods: Data collection
(analysis of NFES articles from 2003 to 2020)

The author does not mention the fiber diameter in writing but provides a EM characterization.

Python Image Analysis (with a 3.2% error in



Figures from Min2013



Figures from Camillo2013

S.-Y. Min, T.-S. Kim, B.J. Kim, H. Cho, Y.-Y. Noh, H. Yang, J.H. Cho, T.-W. Lee, Large-scale organic nanowire lithography and electronics, Nat. Commun. 4 (2013) 1773. https://doi.org/10.1038/ncomms2785..
https://github.com/katagirimx/OpenCV-image-measuring
D. Di Camillo, V. Fasano, F. Ruggieri, S. Santucci, L. Lozzi, A. Camposeo, D. Pisignano, Near-field electrospinning of conjugated polymer light-emitting nanofibers, Nanoscale. 5 (2013) 11637–11642. https://doi.org/10.1039/C3NR03094F.

Conclusion 1.1:

- Polymer Concentration,
- Nozzle Diameter,
- Solution Flow Rate,
- Working Distance,
  &
- Applied Voltage

are the main drivers of the **final Fiber Diameter**



Conclusion 1.1: Process Parameters



Conclusion 1.2: Let’s focus on polymer concentration

Polymer concentration is the most reliable process parameter to control the morphology of electrospun fibers. (regardless the type of NFES process)





Diameter Prediction of Electrospun Fibers

The fiber morphology not only depends on the process parameters, but also on the type of electrospinning process and on polymer-solvent system.

"[…] the fiber diameter decreases as the applied voltage increases."
Helgeson et al.

"[…] neither the collecting distance nor the applied voltage has large influences on fiber diameter […]"
Zhang et al.

"[…] while decreasing the voltage could also be used to reduce the average fiber diameter."
Brown et al.

The existing interdependence between the process and solution parameters adds complexity and ambiguity to the effect of each parameter

Siddharth B. Gadkari. "Scaling analysis for electrospinning". In: SpringerPlus 3.1 (Dec. 2014), p. 705. ISSN: 2193-1801. DOI: 10.1186/2193-1801-3-705. URL https://springerplus.springeropen.com/articles/10.1186/2193-1801-3-705.
B. Zhang, F. Kang, J.-M. Tarascon, J.-K. Kim, Recent advances in electrospun carbon nanofibers and their application in electrochemical energy storage, Prog. Mater. Sci. 76 (2016) 319–380. https://doi.org/10.1016/j.pmatsci.2015.08.002.
M.E. Helgeson, K.N. Grammatikos, J.M. Deitzel, N.J. Wagner, Theory and kinematic measurements of the mechanics of stable electrospun polymer jets, Polymer (Guildf). 49 (2008) 2924–2936. https://doi.org/10.1016/j.polymer.2008.04.025.
T.D. Brown, F. Edin, N. Detta, A.D. Skelton, D.W. Hutmacher, P.D. Dalton, Melt electrospinning of poly(ε-caprolactone) scaffolds: Phenomenological observations associated with collection and direct writing, Mater. Sci. Eng. C. 45 (2014) 698–708. https://doi.org/10.1016/j.msec.2014.07.034.

Diameter Prediction of Electrospun Fibers

Helgeson and Wagner have presented an adimensional analysis to predict the fiber diameter with conservation equations of momentum, mass, electric charge and four dimensionless numbers:

Correlation between the electrostatic and viscous forces:

$$\Pi_1 = RePe\Psi = \frac{2\bar{\varepsilon}^2{\Phi_0}^2}{K\eta_0 L^2}$$

Ohnesorge number (jet behaviour and capillary rupture):

$$Oh = \frac{Re^2}{We} = \frac{\eta_0}{\sqrt{\rho\gamma R_{jet}}}$$

Helgeson get rid of known and/or hard to measure parameters, such as the initial jet velocity.

M.E. Helgeson, N.J. Wagner, A correlation for the diameter of electrospun polymer nanofibers, AIChE J. 53 (2007) 51–55. https://doi.org/10.1002/aic.11056.

Diameter Prediction of Electrospun Fibers



$$\Pi_1 Oh = \frac{2\bar{\varepsilon}^2 {\Phi_0}^2}{KL^2\sqrt{\rho\gamma R_{jet}}} = 2.5 \pm 0.2 \times 10^{-8}$$

https://doi.org/10.1021/acsnano.5b03134.

Conclusion1.3: Selection of Polymer-Solvent combinations

Zhenan Bao et al. investigated the effect of the polymer chemical Structure of:



- higher sp2 carbon content translates into higher graphitization degree and higher electrical conductivity
- polymers with functional groups are required for the creation of smooth and continuous fibers.

N. Liu, K. Kim, H.Y. Jeong, P.C. Hsu, Y. Cui, Z. Bao, Effect of Chemical Structure on Polymer-Templated Growth of Graphitic Nanoribbons, ACS Nano. 9 (2015) 9043–9049. https://doi.org/10.1021/acsnano.5b03134.

Conclusion1.3: Selection of Polymer-Solvent combinations

Polymers with **high carbon content** relative to **oxygen content**



Poly(styrene-co-butadiene)
in Tetrahydrofuran, N,N-Dimethylformamide, and 1-Methyl-2-Pyrrolidinone (Fong1999)



Polystyrene (PS)
in Tetrahydrofuran (Yousefi2019)



Poly(9-Vinyl Carbazole) (PVK)
in Chloroform (Min2013)



Poly(styrene-co-a-methylstyrene)
in N,N-Dimethylformamide (no records)

A.A. Yousefi, A.R. Mohebbi, S. Falahdoost Moghadam, S.A. Poursamar, L. Hao, Uniaxially aligned microwire networks for flexible transparent electrodes using a novel electrospinning set-up, Sol. Energy. 188 (2019) 1111–1117. ttps://doi.org/10.1016/j.solener.2019.07.007.
H. Fong, D.H. Reneker, Elastomeric nanofibers of styrene-butadiene-styrene triblock copolymer, J. Polym. Sci. Part B Polym. Phys. 37 (1999) 3488–3493. https://doi.org/10.1002/(SICI)1099-0488(19991215)37:24<3488::AID-POLB9>3.0.CO;2-M.
S.-Y. Min, T.-S. Kim, B.J. Kim, H. Cho, Y.-Y. Noh, H. Yang, J.H. Cho, T.-W. Lee, Large-scale organic nanowire lithography and electronics, Nat. Commun. 4 (2013) 1773. https://doi.org/10.1038/ncomms2785.

Specific Objective 2. Through rheological analyses, determine if polymer solutions have comparative viscoelastic properties to those of the SU-8/PEO benchmark, and if they can be easily electrospun by NFES.

Rheology Analyses

Literature claims

- As <u>"electropinnability"</u> is determined by the **polymer chain entanglement**,
- **chain entanglement** is controlled by *molecular weight*,
- increasing *molecular weight* increases <u>viscosity</u>, and
- <u>viscosity</u> is controlled by **polymer concentration**, then

The **critical/spinnable concentration** can be found in a **viscosity vs. concentration** plot



D.R. Flores, Role of rheological properties in near field electrospun fibers morphology, (2017) 130.
G.L. Wilkes, An overview of the basic rheological behavior of polymer fluids with an emphasis on polymer melts, J. Chem. Educ. 58 (1981) 880. https://doi.org/10.1021/ed058p880.

Methods: Sample Preparation (SU8-PEO)

Sample	Weight Percent $wt\%$		
	SU-8	**PEO**	**TBF**
1	99.50	0.00	0.50
2	99.25	0.25	0.50
3	99.00	0.50	0.50
4	98.75	0.75	0.50
5	98.50	1.00	0.50
density [g/ml]	1.123		

3.0 ml samples
on a heating plate at 160 rpm and 60°C,
for 2 hours each.

A salt (TBF) was added to all the samples to increase the electrical conductivity

Methods: Rheology – Frequency Sweeps

Geometry:
Steel cone plate, Peltier plate
(60.0 mm diameter, 0.9979° cone angle, 23 μm truncation)

Procedure:
Frequency sweep
(20°C, for 20 min
from 10^{-3} to 10^{4} 1/s shear rates)

Methods: The Carreau-Yasuda Model



$$\eta = \frac{\eta_0 - \eta_\infty}{\left[1 + (\kappa\dot{\gamma})^a\right]^{\frac{1-n}{a}}} + \eta_\infty$$

η : viscosity
$\dot{\gamma}$: shear rate
η_∞ : infinite shear rate viscosity
η_0 : zero shear rate viscosity
κ : time constant
n : Power Law index
a : width of the transition region

Methods: Rheology results validation for 0wt% PEO



Measured:

$(8.05 \pm 0.28)\ \mathrm{mPa \cdot s}$

vs.

MicroChem data sheet:

$$\frac{7.5\mathrm{cSt}\ (1.123\mathrm{g/ml})}{1000\mathrm{cSt} \cdot \mathrm{s} \cdot \mathrm{m} \cdot \mathrm{g/ml} \cdot \mathrm{Kg}}$$
$$= 8.422\ \mathrm{mPa \cdot s}$$

$1.09\ \%error$

Microchem, Su-8 2000.5, 2002, 2005, 2007, 2010, 2015, Microchem. (2018) 1–5. papers3://publication/uuid/859F51B9-0382-4DE8-88A9-267F936939A3.

Methods: Rheology results validation for 0wt% PEO



Measured:

$0.499\ \mathrm{mPa \cdot s}$

vs.

Anton-Paar data sheet:

$0.563\ \mathrm{mPa \cdot s}$

$11.36\ \%error$

https://wiki.anton-paar.com/en/chloroform/

Spinnable/Critical Concentration



Spinnable/Critical Concentration



Conclusion2.1: Spinnable/Critical Concentration



A low molecular weight shall be compensated with higher concentrations to reach a spunable viscosity.

Polymer	Molecular Weight [$g \cdot mol$]	Solvent	c^* [wt%]	η_0 [$Pa \cdot s$]
PEO	4,000,000	CPO (SU-8)	0.25	60.022
PS	192,000	THF	20.00	0.166
PSB	490,000	NMP	8.00	0.028
PSB	490,000	THF and DMF	15.00	0.092
PSMS	2,658,076	DMF	5.00	0.282
PVK	1,100,000	CHL	15.00	41.861
PVK	1,100,000	CPO (SU-8)	0.75	49.657

Vu Anh Doan et al. “Interphase transfer of tackifier between poly(butadiene) and poly(styrene-co-butadiene)”. In: Journal of Materials Science 48.5 (Mar. 2013), pp. 2046–2052. ISSN: 0022-2461. DOI: 10.1007/s10853- 012- 6974- 1. URL: http://link.springer.com/10.1007/s10853-012-6974-1.
Ralph H. Colby, Lewis J. Fetters, and William W. Graessley. “The melt viscosity-molecular weight relationship for linear polymers”. In: Macromolecules 20.9 (Sept. 1987), pp. 2226–2237. ISSN: 0024-9297. DOI: 10 . 1021 / ma00175a030. URL: https : / / pubs . acs . org / doi / abs / 10 . 1021 / ma00175a030.

Specific Objective 3. Propose alternatives to the SU-8/PEO benchmark formulation for the production of microscopic polymer fibers with potential for the fabrication of carbon nano-wires.

Fabrication & Characterization

Methods: Design of experiments / NFES

Given the results of previous work, the experiments shall reflect:

- The SU8-PEO sample set is the control
- The calculated critical concentration were used for each sample set.
- Each sample was electrospun at different applied voltages from 200 to 600V
    - Other process parameters (working distance, stage velocity, flow rate) are to be tuned and remain constant during NFES.





Fabrication: Process Parameters

- Fabrication velocity: 10 mm/s
- Working distance: 0.5 mm
- Applied voltage: 200V to 600V
- Applied current: 10 uA
- Flow rate: 0.04 uL/min
- Spacing: 10um

0.25 wt% PEO in SU-8



Characterization:





PEO in SU-8

Results: Spinnable solutions



Conclusion3.1: non-spinnable solutions

Polymer / Solvent	Critical / spinnable concentration	Rationale
Poly(Styrene-co-alpha-Methylstyrene) (PSMS) in N,N-Dimethylformamide (DMF)	5 wt% (and 10, 15 wt%)	Fibres were broken into agglomerates / dust
Poly(Styrene-co-Butadiene) (PSB) in 1-Methyl-2-Pyrrolidinone (NMP)	8.00 wt%	Development of a shell around the drop.

Conclusions & Future Work

Helgeson's Dimensionless analysis

Helgeson's model was thought to work with far-field electrospinning, hence the deviation of the NFES data from the model trend.

For an accurate NFES fiber diameter prediction, the mechanical stresses introduced by the moving stage shall be considered in the model

Pyrolysis Process

This work verifies the electro-spinnability of four new formulations and one modification to the PEO/SU-8 solution, however fibers were not carbonized into carbon structures.

Further work shall study the pyrolysis process of the proposed fibers to get carbon structures with good electrical conductivity.

A photo-polymerization process could be introduced before pyrolysis to increase the order of the molecules and achieve carbon with higher conductivity.

Process Parameters

The viscosity-concentration plot is a helpful tool to estimate the critical spinnable concentration of a polymer-solvent system as NFES solutions require specific viscosities to initiate a polymer jet. However there is room for improvement as this method only considers rheological data.

Other methods could be adopted to better tune other process parameters such as stage velocity, and applied voltage.





Thank You





Tecnológico
de Monterrey

CONACYT
Consejo Nacional de Ciencia y Tecnología


Any Questions?