

INSTITUTO TECNOLÓGICO Y DE ESTUDIOS
SUPERIORES DE MONTERREY



MASTERS THESIS PROPOSAL

**Fabrication of graphitic-carbon suspended
nanowires through
mechanoelectrospinning of
photocrosslinkable polymers**

Author:

Antonio Osamu KATAGIRI
Tanaka

Principal Advisor:

Dr. Héctor Alán AGUIRRE
Soto

Co-advisor and

Director of Program:

Dra. Dora Iliana MEDINA
Medina

*A thesis proposal submitted in fulfillment of the requirements
for the degree of Master of Science in Nanotechnology (MNT)*

in

ITESM Campus Estado de México
School of Engineering and Sciences

Estado de México, Atizapan de Zaragoza, April 3, 2019

INSTITUTO TECNOLÓGICO Y DE ESTUDIOS SUPERIORES DE
MONTERREY

Campus Estado de México

Supervising Committee

The committee members, hereby, recommend that the proposal by Antonio Osamu KATAGIRI Tanaka to be accepted to develop the thesis project as a partial requirement for the degree of Master of Science in Nanotechnology (MNT).

Dr. Héctor Alán AGUIRRE Soto
Tecnológico de Monterrey
Principal Advisor

Dra. Dora Iliana MEDINA Medina
Tecnológico de Monterrey
Co-Advisor

Marc MADOU
Tecnológico de Monterrey
Committee Member

Sergio Omar MARTÍNEZ Chapa
Tecnológico de Monterrey
Committee Member

Dra. Dora Iliana MEDINA Medina
Director of Program in Nanotechnology
School of Engineering and Sciences

Estado de México, Atizapan de Zaragoza, April 3, 2019

Contents

Supervising Committee	i
Abstract	v
1 Introduction	1
2 Problem Definition and Motivation	3
3 Hypothesis and Research Questions	5
3.1 Research Hypothesis	5
3.2 Research Questions	5
4 Objectives	6
4.1 General objective	6
4.2 Particular objectives	6
5 Theoretical Framework	7
5.1 Photoresists	7
5.2 Electro-Mechanical Spinning	8
5.3 Pyrolysis	9
5.4 Carbon nano-wire	11
6 Methodology	12
6.1 Work package 1 : Preliminary Literature Review	12
6.2 Work package 2 : Evaluation of Fabrication Parameters	12
6.3 Work package 3 : Polymer Solution Design	13
6.4 Work package 4 : Fabrication of Carbon Nano-wires	13
6.5 Work package 5 : Data Collection and Analysis of Results	14
6.6 Work package 6 : Documentation	14
7 Work Plan	15

List of Figures

1.1	Fabrication Process	1
5.1	Far Field Electrospinning set-up	9
5.2	Near Field Electrospinning set-up	10

List of Abbreviations

CEM	Campus Estado de México
CNWs	Carbon Nano-wires
DC	Direct Current
EMS	Electromechanical Spinning
FFES	Far Field de Electrospinning
ITESM	Instituto Tecnológico y de Estudios Superiores de Monterrey
MA	Massachusetts
MEMS	Microelectromechanical Systems
MNT	Maestría en Nanotecnología (<i>Master of Science in Nanotechnology</i>)
MTY	Monterrey <i>or</i> Campus Monterrey
NFES	Near Field de Electrospinning
USA	United States of America
UV	Ultraviolet

INSTITUTO TECNOLÓGICO Y DE ESTUDIOS SUPERIORES DE
MONTERREY

Abstract

Faculty: Nanotechnology

School of Engineering and Sciences

Master of Science in Nanotechnology (MNT)

**Fabrication of graphitic-carbon suspended nanowires through
mechanoelectrospinning of photocrosslinkable polymers**

by Antonio Osamu KATAGIRI Tanaka

Carbon nano-wires are versatile materials composed of carbon chains with a wide range of applications due to their unrivalled **properties in electrical matters**. Regardless of the high interest in the implementation of carbon nano-wires in several applications and devices, no feasible processes have been developed to fabricate **carbon nano-wires**. **Carbon nano-wires have been fabricated with the use of a photoresist**, but little is known about polymers that can produce more conductive carbon nano-wires after pyrolysis. Various polymer solutions have been tested in near field electrospinning (NFES) and photopolymerization processes, however, few have been tested for nano-wire fabrication purposes through pyrolysis. The intention behind the thesis proposal is to implement **rheology** analyses of different polymer solutions to determine if they can be easily electrospun at low voltages and then **fabricate** nano-wires with them. This **thesis** work arises from the need to test a greater variety of polymers with the goal to design a polymer solution to fabricate carbon nano-wires with better properties than the **current SU-8 polymeric nano-fibers**. The research process will include the design of polymer solutions that can be electrospun, photopolymerized, and then pyrolyzed into conducting carbon nanowires. On the other hand, it is intended to engineer a newly designed polymer solution **to achieve** mass scale manufacturing of carbon nano-wires in a inexpensive, continuous, simple and reproducible manner.

keywords: nanotechnology, carbon, nano-wires, electrospinning, NFES

1 Introduction

Carbon nano-materials are subjected to great interest for research purposes due to their various potential applications in diverse areas that take advantage of the nano-scale properties. [26] Carbon nano-materials are suitable for the catalysis, adsorption, carbon capture, energy and hydrogen storage, drug delivery, bio-sensing and cancer detection. [26] Some matchless properties that allow carbon nano-materials to be utilized within multiple functionalities include high porosity, distinguished structures, uniform morphologies, high stability, high magnetic properties and high conductivity. [26]

This document bestow a thesis proposal to perform a research to engineer and design a polymer solution to achieve mass scale manufacturing of high conductive carbon nano-wires with a reduced diameter in an inexpensive, continuous, simple and reproducible manner. The research intends to involve several manufacturing processes such as near field electrospinning, photopolymerization, pyrolyzation and carbonization, as they have shown to be promising methods for the fabrication of carbon nano-materials. [6] See Figure 1.1. A number of processes have been developed for specific purposes of polymeric nano-fibers, some include surface deposition, composites, and chemical adjustments. Polymeric nano-fibers must be also pyrolyzed to generate carbon nano-wires with conductive capabilities [15] for electrochemical sensing and energy storage purposes.




FIGURE 1.1: Fabrication process of carbon nano-wires to achieve through the proposed dissertation.

Nanotechnology has explored different polymer patterning techniques to integrate carbon nano-wires structures. One technique is known as far-field electrospinning, a process in which electrified jets of polymer solution are dispensed to synthesize nano-fibers which then are pyrolyzed at high temperatures. One sub-technique derived from electrospinning is near field electromechanical spinning or EMS. EMS has proved to deliver high control in patterning polymeric nano-fibers. [6]

The proposal is to continue the previous work done in regards of the synthesis of carbon nano-wires. Previous work includes the fabrication of suspended carbon nano-wires by two methods: electro-mechanical spinning and multiple-photon polymerization with a photoresist. [6] This research proposal is intended to focus on electro-mechanical spinning processes only, to bring off polymer solutions that can be electrospun by near field electrospinning (NFES), photopolymerized and pyrolyzed into conducting carbon nano-wires. The polymer solutions described in [6] are to be amended to achieve the goal mentioned in the previous statement.

Traditional near-field electrospinning or NFES allows large scale manufacturability combined with **controlled guidance**. [15] However, the reported efforts required the use of electric fields in excess of 200 kV/m for continuous operation, resulting in limited control for nano-fiber patterning in traditional NFES processes. [15] the current state-of-the-art synthesis processes for polymer nano-fibers lack to yield precise, inexpensive, fast, and continuous manufacturing properties.

2 Problem Definition and Motivation

Carbon nanowires have been fabricated with a photoresist by multiple-photon polymerization techniques. However little is known about polymers that can produce conductive carbon nano-wires after pyrolysis. The lack of research **relays** on the fact that in the past years, it was assumed that most polymers are non-graphitic through pyrolysis [8]. In the past years photon polymerization processes have been applied to the fabrication of nano-structures with the use of a epoxy based photoresist. [5] Photon polymerization techniques deliver patterning resolutions with nano-scale tolerances for the production of highly detailed structures [9].

On the other hand, electrospinning has been acknowledged as a process with promising results at nano-structure fabrication [5], yet there is little research regarding the implementation of electrospinning for the fabrication of carbon nano-wires. Electrospinning has the potential to be a more straightforward process for the design and fabrication of nano-structures, as it can achieve mass scale manufacturing in a continuous, simple and reproducible manner. Cárdenas [6] shows that electrospinning can be implemented with ease for carbon nano-wire synthesis. Mechano-electrospinning, a new variant of electrospinning shows promising results in the production of ordered carbon nano-wires. As stated in [6], mechano-electrospinning is an early technology invention, and brings new challenges, such as the reproducibility of carbon nano-wire production. Furthermore, the study of a new fabrication process to produce carbon nanowires that involves mechano-electrospinning will enable spatial control of the structures' patterning.

Since electrospinning seems to be a better alternative for carbon nano-wire

fabrication processes; and for that purpose of its implementation, it is required to develop polymer solutions that can be mechano-electrospun, photopolymerized and pyrolyzed into conducting carbon nano-wires. Carbon nano-materials have been subjected to research due to their various potential applications in diverse areas that take advantage of the nano-scale properties. [26] Carbon nano-materials are suitable for the catalysis, adsorption, carbon capture, energy and hydrogen storage, drug delivery, bio-sensing and cancer detection. [26] However most applications are not currently feasible due to the lack of a continuous, simple and reproducible fabrication method with inexpensive processes. With the newly designed polymer solution, it would be possible to produce carbon nano-wires in large quantities, and therefore more applications will become feasible. On the other hand, the new technique will overcome some limitations of other methods such as lithography currently has. For instance, patterns created by lithography processes cannot be originated, only replicated, all constituent points of the pattern can only be addressed at the same time, and the process requires the pattern to be encoded into a mask. [12]

3 Hypothesis and Research Questions

3.1 Research Hypothesis

The rheological properties of polymer solutions along with synthesis parameters (stage velocity, voltage, dispense rate) can be amended through rheological analyses to obtain a low voltage electrospun-able, photopolymerizable and graphitizable fibers for the synthesis of carbon nano-wires with specified dimensions (diameter and length).

3.2 Research Questions

- Is there any evidence of carbon nano-wire fabrication through electrospun-able and pyroizable polymer solutions?
- What are the process parameters to consider/control for the fabrication processes of carbon nano-wires?
- What rheological properties are to be controlled/tested to deliver an electrospun-able and pyroizable polymer solution?
- Are there any efforts employed to the design of polymer solutions that can be electrospun, photopolymerized, and pyrolyzed into conducting carbon nanowires?
- Are the optimal fabrication parameters defined [6] for the synthesis of carbon nano-wires through near-field electromechanical spinning?

4 Objectives

4.1 General objective

Study the practice and feasibility of a new synthesis process to achieve mass scale manufacturing of carbon nano-wires in an inexpensive, continuous, simple and reproducible manner; by the integration of mechano-electrospinning technique.

4.2 Particular objectives

- Design polymer solutions that can be electrospun by NFES, photopolymerized, and then pyrolyzed.
- Through rheological analyses, determine if polymer solutions can be easily employed for conducting carbon nano-wire synthesis.
- Determine and control the polymer solution rheological properties along with the process parameters of carbon nano-wire synthesis.

5 Theoretical Framework

5.1 Photoresists

The electronic industry requires sustainable raw material supply for its development [29]. Photoresists are a type of raw material used in microelectronics, which is composed by four main elements: a polymer (resin), a photoactive compound, a solvent, and an additive [23]. The additive requires to be with a low molecular weight as it is intended to act as a photosensitive material. Photoresists are used within the manufacturing process of printed circuit boards [28]. Photoresists are classified into two categories. The resist is defined as positive if the radiation exposed material is soluble in photoresist developer; otherwise, for negative photoresist the exposed material remains to stay in the photoresist surface as it crosslinks upon exposure [12, 24]. In the manufacturing process of a semiconductor, the radiation sources which are often used in a lithography process are ultraviolet (UV) and X-ray [16].

The polymeric material is available on the broad market either in liquid or solid state; *MicroChem Corp.* (Westborough, MA, USA) is the principal provider of SU-8 photoresist. SU-8 and similar photoresists are inexpensive with good adhesion on the semiconductor surface and high sensitivity [28]. Epoxy resins are copolymer-thermosetting plastics which are normally produced by a chemical reaction process that involves epichlorohydrin and bisphenol-A compound [27]. A epoxy-based polymer is typically used to produce patterns by lithography with the application of UV radiation. Lithography is a technique to transfer patterns from a mask and then transferred onto the substrate [12, 31]. SU-8 is a epoxy-based negative photoresist with the advantages of being inexpensive with good mechanical properties, good chemical resistance, and good electrical isolation [31]. SU-8 photoresists are used in the production processes of MEMS [32]. Photoresist-wise, the contrast and quality level of UV radiation lithography is affected by the wavelengths of radiation sources. The higher the sensitivity of the material, the better is the

lithography process as it absorbs radiation energy with ease to perform photochemical reactions in forming patterns [32].

In summary, a photoresist is a "epoxy-based resin (polymeric) material which changes its dissolution rate in a liquid solvent, called a developer, under high energy radiation." [12]

5.2 Electro-Mechanical Spinning

Diverse polymer patterning techniques have being develop for the fabrication of nano-fibers, such as arc discharge [30], chemical vapor deposition, laser ablation [20], and vapor growth [17]. Nonetheless, those processes are expensive due to either the low product yield or the expensive equipment required. The electrospinning method (invented by Formhals Anton in 1934) can produce fibers with a range of diameters between 10 *nm* and 10 μm [11, 2] from a polymer solution under the influence of an electrostatic force. The applied electric field and solution conductivity and viscosity is an important parameter the affects the fiber diameter during the spinning along with other parameters such as jet length, solution viscosity surrounding gas, flow rate and the collector geometry [1, 13, 4, 25].

Even though electrospinning is an old invention [2], it is currently a trending topic among researchers [10, 21, 22]. Some of the reasons electrospinning is to be studied is its potential to fabricate polymer nano-fibers from a variety of polymers. The technique allows the production of thin continuous fibers with ease, with diameters down to 3 *nm* in some cases, which is something difficult to achieve by other techniques. Furthermore, the basic set-up can be modified with ease to fabricate different fibers with diversified functionalities with different materials. The produced fibers can be aligned or unaligned. Besides, the electrospinning equipment is inexpensive and of small size, compared to the equipment of standard spinning techniques. On the other hand, the understanding of the electrospinning process has improved in the last years [14]. As Reneker and Yarin state: "Electrospinning has rapidly changed fiber making from a capital intensive, large scale process to a low cost, broadly applicable method that manufactures fibers on a laboratory bench, to serve diverse needs ranging from materials science and technology to life sciences and clinical medicine." [21]

The main components of the electrospinning technique are the fluid control

unit (e.g. syringe pump) and a DC power supply. The process also requires a target electrode or combination of electrodes on which the fibers can be collected. Figure 5.1 describes a typical electrospinning set-up. [14]




FIGURE 5.1: Typical far field electrospinning (FFES) set-up [14].

Two sub-techniques can be derived from electrospinning depending on the distance between the dispensing electrode and the collector. The process in which the electrospun jet can be controlled near the tip is called NFES or near-field electrospinning. [7] Moreover, if the distance between the collector and the dispensing needle is farther, the configuration is known as FFES or far-field electrospinning. [18] The difference between NFES and mechano-electrospinning is the presence of a mechanical collector that allows higher precision when patterning. Figure 5.2 shows a typical near field mechano-electrospinning apparatus.

5.3 Pyrolysis

Pyrolysis is technique that involves heating of biomass in the absence of air or oxygen at a maximum pyrolysis temperature. A small amount of oxygen can burn the structures and make them unusable [19]. Once the maximum pyrolysis temperature is reached, the temperature remains constant to produce solid char, liquids, and non-condensable products. In most cases the liquid product is the main interest of the pyrolysis process, and the properties of the pyrolysis products depend on the maximum pyrolysis temperature and the heating rate [19, 3].





FIGURE 5.2: Typical near field electrospinning (NFES) set-up [33].

The heating of large biomass molecules results in decomposition. The pyrolysis decomposition process comprises char, liquids (condensable gases) and non-condensable gases; where the condensable gases may suffer further decomposition into non-condensable gases such as CO , CO_2 , H_2 , and CH_4 . Equation 5.1 is a general representation of the pyrolysis decomposition reaction [3].



Pyrolysis yields solid products that are more energy dense than the initial biomass, however the gas and liquid products are less energy dense [3]. The liquid product of pyrolysis is usually of colour black containing hydrocarbons with a large amount of oxygen and 20% water. When the liquid product is of interest, a rapid "quenching" (freeze) is required after pyrolysis to prevent further decomposition or reaction with other substances [3]. The solid yields of pyrolysis is usually around 85% carbon with some oxygen, hydrogen and other substances that are present within the initial biomass [3]. The biomass decomposition by pyrolysis produces non-condensable and condensable gases. The vapors (condensable gases) add up to the liquid yield of pyrolysis which is generated upon cooling. The gases (non-condensable gases) are comprised by ethylene, ethane, methane, carbon monoxide and carbon dioxide [3].

5.4 Carbon nano-wire

Carbon nano-wires (CMWs) are known as long, thin strings with diameters between 10 and 1 thousand nm ; composed mostly by carbon atoms aligned parallel to the long axis of the fiber [18]. Carbon nano-wires are different from carbon nano-tubes, as CMWs are not composed by graphene sheets in cylindrical form [18]. Carbon nano-wires are typically fabricated by electro-spinning and pyrolysis/carbonization as the main processes. During the fabrication process, the polymer molecules are to be crosslinked to prevent melting during the subsequent pyrolysis. The carbonization step removes non-carbonized components in form of condensable and incondensable gases [3] to then yield carbon structures of about 50% to 75% of the mass of the original polymeric structure [18].

6 Methodology

The following describes the proposed work to be done to fulfill the objectives stated in this document. The tasks are grouped in several work packages as described below:

6.1 Work package 1 : Preliminary Literature Review

The first step to the thesis development is the study of preliminary literature and related work. The purpose of this work package is the familiarization of the existing techniques such as: far and near field electrospinning, lithography, pyrolysis, carbonization and photopolymerization. On the other hand, some research is to be done in order to recognize if there are any efforts in the design of electrospun-able, photopolymerizable and pyrolysable polymer solutions.

Furthermore, the motive of this work package is to find common parameters that could link the techniques mentioned above for the fabrication of carbon nano-wires from polymer solutions that can be electrospun by NFES, photopolymerized and then pyrolyzed. This work package is to be carried out through the entire thesis development process, as the state-of-the-art may change within that period of time.

6.2 Work package 2 : Evaluation of Fabrication Parameters

As the polymer solution is the principal input to the proposed technique (See Figure 1.1), it is required to identify and understand the fabrication parameters that have an impact to the quality of the carbon nano-wires. For that reason two tasks are to be executed:

- Study and identify the process parameters that influence the fabrication of carbon nano-wires

- Study and identify the rheological properties in polymer solutions that affect the electrospinning and pyrolysis techniques

6.3 Work package 3 : Polymer Solution Design

Once the process parameters and rheological properties that affect the fabrication of carbon nano-wires are identified, the design process shall take place. This work package is to study polymer solutions that can be electrospun by NFES, photopolymerized and pyrolyzed. The polymer solution design will comprise of two steps:

- Prepare and test various polymer solutions with specific distinctions according to the identified solution properties and process parameters.
- Perform rheological analyses to determine if the prepared polymer solutions can be employed for the fabrication of carbon nano-wires.

6.4 Work package 4 : Fabrication of Carbon Nano-wires

From the rheological analyses, determine and control the polymer solution properties and fabricate carbon nano-wires.

This work package intends to involve several manufacturing processes (near field electrospinning, photopolymerization, pyrolyzation and carbonization) for the fabrication of carbon nano-wires. This task will require the integration of several techniques:

- *Electrospinning* - to convert the polymer solution into polymer nano-fibers
- *Photopolymerization* - to change the chemical properties of the polymer solution and crosslink its molecules. This is to prevent the polymer to melt during pyrolysis [3].
- *Pyrolysis* - to transform the polymer nano-fibers into conductive carbon nano-wires.

See Figure 1.1.


6.5 Work package 5 : Data Collection and Analysis of Results

The data collection work package comprehends the study of the created carbon nano-wires using the newly design polymer solution. The purpose is characterize the carbon nano-wires and compare them to the carbon nano-structures produced by existing techniques.

6.6 Work package 6 : Documentation

Finally the documentation refers to the Thesis writing tasks. This task is intended to carried out through the entire thesis development process, as every work package above is to be referenced within the thesis document.

7 Work Plan



The previous are Gantt diagrams to show the work plan to be executed for the development of the proposed dissertation. The tasks mark with @CEM are to be carry out in Tecnológico de Monterrey campus Estado de México; consequently, the tasks mark with @MTY are to be perform in Tecnológico de Monterrey campus Monterrey.

References

- [1] Formhals Anton. "Method and apparatus for spinning". In: (Aug. 1938). DOI: <https://patents.google.com/?q=D01D5%2f0092>. URL: <https://patents.google.com/patent/US2349950A/en>.
- [2] Formhals Anton. *Process and apparatus for preparing artificial threads*. Dec. 1930. DOI: <https://patents.google.com/?q=D01D5%2f0076>. URL: <https://patents.google.com/patent/US1975504A/en>.
- [3] Prabir Basu. *Biomass Gasification, Pyrolysis and Torrefaction - Practical Design and Theory*. 3rd Editio. Elsevier, 2018. URL: <https://app.knovel.com/hotlink/pdf/id:kt011PGVNJ/biomass-gasification/biomass-ga-historical>.
- [4] Peter K Baumgarten. "Electrostatic spinning of acrylic microfibers". In: *Journal of Colloid and Interface Science* 36.1 (May 1971), pp. 71–79. DOI: [10.1016/0021-9797\(71\)90241-4](https://doi.org/10.1016/0021-9797(71)90241-4). URL: <https://www.sciencedirect.com/science/article/pii/0021979771902414>.
- [5] Jan Boer and Clemens Blitterswijk. *Tissue Engineering*. Ed. by Academic Press of Elsevier AP. 2nd. Safary O Reilly, 2014. URL: <https://learning.oreilly.com/library/view/tissue-engineering-2nd/9780124201453/XHTML/B9780124201453000109/B9780124201453000109.xhtml>.
- [6] Braulio Cárdenas. "Advanced Manufacturing Techniques for the Fabrication and Surface Modification of Carbon Nanowires". In: (2017), p. 160.
- [7] Albert Cisquella-Serra et al. "Study of the electrostatic jet initiation in near-field electrospinning". In: *Journal of Colloid and Interface Science* 543 (May 2019), pp. 106–113. ISSN: 0021-9797. DOI: [10.1016/J.JCIS.2019.02.041](https://doi.org/10.1016/J.JCIS.2019.02.041). URL: <https://0-www-sciencedirect-com.millennium.itesm.mx/science/article/pii/S0021979719302152>.
- [8] Rosalind Elsie Franklin. "Crystallite growth in graphitizing and non-graphitizing carbons". In: *Proceedings of the Royal Society of London. Series A. Mathematical and Physical Sciences* 209.1097 (Oct. 1951), pp. 196–218. ISSN: 2053-9169. DOI: [10.1098/rspa.1951.0197](https://doi.org/10.1098/rspa.1951.0197). URL: <http://www.royalsocietypublishing.org/doi/10.1098/rspa.1951.0197>.
- [9] Kolin C Hribar et al. "Light-assisted direct-write of 3D functional biomaterials." In: *Lab on a chip* 14.2 (Jan. 2014), pp. 268–75. ISSN: 1473-0189. DOI: [10.1039/c3lc50634g](https://doi.org/10.1039/c3lc50634g). URL: <http://www.ncbi.nlm.nih.gov/pubmed/24257507>.

- [10] Zheng-Ming Huang et al. "A review on polymer nanofibers by electrospinning and their applications in nanocomposites". In: *Composites Science and Technology* 63.15 (Nov. 2003), pp. 2223–2253. ISSN: 0266-3538. DOI: 10.1016/S0266-3538(03)00178-7. URL: <https://www.sciencedirect.com/science/article/pii/S0266353803001787>.
- [11] Krishnan Jayaraman et al. "Recent Advances in Polymer Nanofibers". In: *Journal of Nanoscience and Nanotechnology* 4.1-2 (2003), pp. 52–65. URL: https://www.researchgate.net/publication/8591778%7B%5C_%7DRecent%7B%5C_%7DAdvances%7B%5C_%7Din%7B%5C_%7DPolymer%7B%5C_%7DNanofibers.
- [12] Stefan. Landis. *Nano-lithography*. ISTE, 2011, p. 325. ISBN: 9781848212114. URL: <https://learning.oreilly.com/library/view/nano-lithography/9781118621707/>.
- [13] L. Larrondo and R. St. John Manley. "Electrostatic fiber spinning from polymer melts. III. Electrostatic deformation of a pendant drop of polymer melt". In: *Journal of Polymer Science: Polymer Physics Edition* 19.6 (June 1981), pp. 933–940. DOI: 10.1002/pol.1981.180190603. URL: <http://doi.wiley.com/10.1002/pol.1981.180190603>.
- [14] Quan Li. *Chapter 7: Liquid Crystal-Functionalized Nano- and Microfibers Produced by Electrospinning - Liquid Crystals Beyond Displays: Chemistry, Physics, and Applications*. John Wiley & Sons, 2012. DOI: 9781118078617. URL: <https://learning.oreilly.com/library/view/liquid-crystals-beyond/9781118259535/chapter07.html>.
- [15] Marc J. Madou et al. "Controlled Continuous Patterning of Polymeric Nanofibers on Three-Dimensional Substrates Using Low-Voltage Near-Field Electrospinning". In: *Nano Letters* 11.4 (2011), pp. 1831–1837. ISSN: 1530-6984. DOI: 10.1021/nl2006164.
- [16] Harutaka Mekaru. "Performance of SU-8 Membrane Suitable for Deep X-Ray Grayscale Lithography". In: *Micromachines* 6.2 (Feb. 2015), pp. 252–265. DOI: 10.3390/mi6020252. URL: <http://www.mdpi.com/2072-666X/6/2/252>.
- [17] Arunan Nadarajah, Joseph G Lawrence, and Thomas W Hughes. "Development and Commercialization of Vapor Grown Carbon Nanofibers: A Review". In: *Trans Tech Publications* 380.1662-9795 (2008), pp. 193–206. DOI: 10.4028/www.scientific.net/KEM.380.193. URL: www.scientific.net/KEM.380.193.
- [18] S.K. Nataraj, K.S. Yang, and T.M. Aminabhavi. "Polyacrylonitrile-based nanofibers—A state-of-the-art review". In: *Progress in Polymer Science* 37.3 (Mar. 2012), pp. 487–513. ISSN: 0079-6700. DOI: 10.1016/J.PROGPOLYMSCI.2011.07.001. URL: <https://0-www-sciencedirect-com.millennium.itesm.mx/science/article/pii/S0079670011000931>.
- [19] Bidhan Pramanick et al. "Effect of pyrolysis process parameters on electrical, physical, chemical and electro-chemical properties of SU-8-derived carbon structures fabricated using the C-MEMS process". In: *Materials Today: Proceedings* 5.3 (Jan. 2018), pp. 9669–9682. ISSN: 2214-7853. DOI: 10.1016/J.MATPR.

- 2017.10.153. URL: <https://0-www-sciencedirect-com.millennium.itesm.mx/science/article/pii/S2214785317321788>.
- [20] Z F Ren et al. *Synthesis of Large Arrays of Well-Aligned Carbon Nanotubes on Glass*. Tech. rep. Science, 1998, pp. 1105–1107. DOI: [10.1126/science.282.5391.1105](https://doi.org/10.1126/science.282.5391.1105). URL: www.sciencemag.org.
- [21] Darrell H. Reneker and Alexander L. Yarin. “Electrospinning jets and polymer nanofibers”. In: *Polymer* 49.10 (May 2008), pp. 2387–2425. ISSN: 0032-3861. DOI: [10.1016/J.POLYMER.2008.02.002](https://doi.org/10.1016/J.POLYMER.2008.02.002). URL: <https://www.sciencedirect.com/science/article/pii/S0032386108001407>.
- [22] Jessica D. Schiffman and Caroline L. Schauer. “A Review: Electrospinning of Biopolymer Nanofibers and their Applications”. In: *Polymer Reviews* 48.2 (May 2008), pp. 317–352. ISSN: 1558-3724. DOI: [10.1080/15583720802022182](https://doi.org/10.1080/15583720802022182). URL: <http://www.tandfonline.com/doi/abs/10.1080/15583720802022182>.
- [23] Christine Schuster et al. “mr-NIL 6000LT – Epoxy-based curing resist for combined thermal and UV nanoimprint lithography below 50 °C”. In: *Microelectronic Engineering* 86.4-6 (Apr. 2009), pp. 722–725. DOI: [10.1016/J.MEE.2008.12.018](https://doi.org/10.1016/J.MEE.2008.12.018). URL: <https://www.sciencedirect.com/science/article/abs/pii/S0167931708006400>.
- [24] Maneesh Sharma et al. *Evaluation of microlithographic performance of ‘deep UV’ resists: Synthesis, and 2D NMR studies on alternating ‘high ortho’ novolak resins*. Tech. rep. 2. 2012, pp. 395–401. URL: www.ias.ac.in/chemsci.
- [25] Y.M. Shin et al. “Experimental characterization of electrospinning: the electrically forced jet and instabilities”. In: *Polymer* 42.25 (Dec. 2001), pp. 09955–09967. DOI: [10.1016/S0032-3861\(01\)00540-7](https://doi.org/10.1016/S0032-3861(01)00540-7). URL: <https://www.sciencedirect.com/science/article/pii/S0032386101005407>.
- [26] M.T.H Siddiqui et al. “Fabrication of advance magnetic carbon nano-materials and their potential applications: A review”. In: *Journal of Environmental Chemical Engineering* 7.1 (Feb. 2019), p. 102812. ISSN: 2213-3437. DOI: [10.1016/J.JECE.2018.102812](https://doi.org/10.1016/J.JECE.2018.102812). URL: <https://0-www-sciencedirect-com.millennium.itesm.mx/science/article/pii/S2213343718307358>.
- [27] Manoj Singla and Vikas Chawla. *Mechanical Properties of Epoxy Resin-Fly Ash Composite*. Tech. rep. 3. 2010, pp. 199–210. URL: http://file.scirp.org/pdf/JMMCE20100300003%7B%5C_%7D77044062.pdf.
- [28] Matthias Staab et al. “Applications of Novel High-Aspect-Ratio Ultrathick UV Photoresist for Microelectroplating”. In: *Journal of Microelectromechanical Systems* 20.4 (Aug. 2011), pp. 794–796. DOI: [10.1109/JMEMS.2011.2159098](https://doi.org/10.1109/JMEMS.2011.2159098). URL: <http://ieeexplore.ieee.org/document/5948317/>.
- [29] Sutikno Sutikno, Muhammad Hakim, and Sugianto Sugianto. “Synthesis of Phenolic-Based Resist Materials for Photolithography”. In: *Oriental Journal of Chemistry* 32.1 (Mar. 2016), pp. 165–170. DOI: [10.13005/ojc/320117](https://doi.org/10.13005/ojc/320117). URL: <http://www.orientjchem.org/vol32no1/synthesis-of-phenolic-based-resist-materials-for-photolithography/>.

- [30] Yu Wang et al. "Helical microtubes of graphitic carbon". In: *Acta Mechanica Sinica* 23.6 (2007), pp. 663–671. URL: https://www.researchgate.net/publication/260358247%7B%5C_%7DHelical%7B%5C_%7Dmicrotubes%7B%5C_%7Dof%7B%5C_%7Dgraphitic%7B%5C_%7Dcarbon.
- [31] Guang-Rui Xu, Miao-Jun Xu, and Bin Li. "Synthesis and characterization of a novel epoxy resin based on cyclotriphosphazene and its thermal degradation and flammability performance". In: *Polymer Degradation and Stability* 109 (Nov. 2014), pp. 240–248. ISSN: 0141-3910. DOI: 10.1016/J.POLYMDEGRADSTAB.2014.07.020. URL: <https://www.sciencedirect.com/science/article/pii/S0141391014002808>.
- [32] J Zhang et al. "Polymerization optimization of SU-8 photoresist and its applications in microfluidic systems and MEMS". In: *Journal of Micromechanics and Microengineering* 11.1 (Jan. 2001), pp. 20–26. DOI: 10.1088/0960-1317/11/1/304. URL: <http://stacks.iop.org/0960-1317/11/i=1/a=304?key=crossref.7e129e3392c38764a08aee10d49f57a6>.
- [33] Ziming Zhu et al. "Fabricated Wavy Micro/Nanofiber via Auxiliary Electrodes in Near-Field Electrospinning". In: *Materials and Manufacturing Processes* 31.6 (Apr. 2016), pp. 707–712. ISSN: 1042-6914. DOI: 10.1080/10426914.2015.1048464. URL: <http://www.tandfonline.com/doi/full/10.1080/10426914.2015.1048464>.