

Polyglykol 400

Polyglykol 400 G

Composition

Polyethylene glycol
 $\text{H}(\text{OCH}_2\text{CH}_2)_n\text{OH}$
 $n = \text{about } 9$

CAS-No.: 25322-68-3
INCI-designation: PEG-8

Product properties^{*)}

Polyglykol 400 and Polyglykol 400 G are clear viscous liquid at room temperature. Polyglykol 400 / 400 G can be supplied in tank trucks or in steel drums. Its two hydroxy end groups as well as its ether groups mainly control the physical and chemical properties of Polyglykol 400. Therefore Polyglykol 400 is soluble in water and polar organic solvents like acetone or methanol. Polyglykol 400 is insoluble in pure hydrocarbons. Polyglykol 400 displays typical chemical reactions of alcohols/diols. In comparison to the standard Polyglykol 400 the alkali ion residue of Polyglykol 400 G is minimized. Therefore Polyglykol 400 G can be used for polyurethane synthesis.

The solidification point, of Polyglykol 400 is about 6°C.

Storage

When stored in a cold, dry place in a closed container Polyglykol 400 or 400 G can be kept for at least two years.

Applications

Based on their physical and chemical characteristics -polyethylene glycols are used for a wide variety of applications.

Fields of applications:

- Reactive diol/polyether component in polyester or polyurethane resins
- Component of auxiliaries for leather and textile processing
- Cosmetic / pharmaceutical formulations (e.g. humectant or solubilizer for creams, shampoos, tooth paste and injection fluids)
- Lubricant and mould release agent for rubber and elastomer processing
- Plasticizer and binder for ceramic and concrete manufacturing
- Component of lubricant formulations
- Water soluble, lubricating component in metal working fluids
- Humectant for paper, wood and cellulose films
- Solvent and humectant for dyes and inks
- Modifier for production of regenerated viscose
- Humectant and plasticizer for adhesives
- Heat transfer medium

^{*)} These characteristics are guidance only and not be taken as product specifications. The tolerances are given in the product specification sheet. For further product properties, specifications, safety and ecological data, please refer to the MSDS.

Polyglykol 400

Polyglykol 400 G

Product data^{*)}

water content (DIN 51777)	% m/m	max. 0.5
colour index [APHA] (EN 1557) (25 % in water)		max. 15
pH (10% w/w in water) (DIN EN 1262)		5 – 7 4 – 7 (400 G)
hydroxyl number (DIN 53240)	mg KOH/g	267 – 295
molecular weight	g/mol	380 – 420
solidification point (EP III)	°C	4 – 8
viscosity at 20°C (50 % w/w in water) (DIN 51562)	mPas	112 – 124
flash point (DIN 51376)	°C	240
ignition temperature (DIN 51794)	°C	> 320
ethylene oxide	ppm	max. 1
dioxane	ppm	max. 1

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.

^{*)} These characteristics are guidance only and not be taken as product specifications. The tolerances are given in the product specification sheet. For further product properties, specifications, safety and ecological data, please refer to the MSDS.

®= Registrierte Marke

Mai 06
Seite 2/2

Clariant Produkte (Deutschland) GmbH
Division Functional Chemicals
D-65926 Frankfurt am Main
TH 20728 E