

# Investigation of multispectral imaging algorithm for temperature determination on a numerical experiment platform in Laser-based Powder Bed fusion of Metals

Untersuchung des multispektralen Bildgebungsverfahrens zur Temperaturbestimmung auf einer numerischen Experimentierplattform beim Laserbasierten Pulverbett-Schmelzverfahren von Metallen.

## Semester Thesis

at the Department of Mechanical Engineering of the Technical University of Munich

<b>Supervised by</b>	Prof. Dr.-Ing. Katrin Wudy M.Sc. Ruihang Dai Laser-based Additive Manufacturing
<b>Submitted by</b>	Zhaoyong Wang Connollystr.3 80809 München
<b>Submitted on</b>	July 31, 2023 in Garching



# Scope of Work

## **Title of the Semester Thesis:**

Investigation of multispectral imaging algorithm for temperature determination on a numerical experiment platform in Laser-based Powder Bed fusion of Metals

**Author:** B.Sc. Zhaoyong Wang

**Issuance:** 15.03.2023

**Supervisor:** M.Sc. Ruihang Dai

**Submission:** 31.12.2021

## **Setting:**

Laser-based Powder Bed Fusion of Metals (PBF-LB/M) is an additive manufacturing process which produces components with a laser by successively melting metal powders applied in layers. This additive manufacturing process offers the advantage of a complex lightweight design. However, complicated thermal histories during laser-metal interaction can lead to process defects such as keyholing. Since the process is thermally driven, acquiring the absolute temperature distribution in the laser-material interaction zone is vital to gain a deeper understanding of the process. However, no measurement system in PBF-LB/M is currently available to determine the absolute temperature due to unknown emissivity. Multispectral Imaging (MSI) has the potential to determine the absolute temperature and emissivity simultaneously by capturing multiple wavelengths of radiance from the melt pool.

## **Objective:**

This work aims to optimize the MSI algorithm to determine the absolute temperature accurately. Since the mapping between the digital value and radiance still needs to be investigated, direct optimization of the MSI algorithm based on the experimental data is challenging. Therefore, the first step is to develop a virtual experiment to obtain "ideal" radiance determined by the given temperature distribution and emissivity. This way, the MSI algorithm can be optimized based on the input and calculated temperature and emissivity. The virtual experiment platform will also allow for the investigation of various temperature distributions and emissivity models in a time- and cost-efficient manner.

## **Methodology:**

The content of the present thesis can be subdivided into the following tasks

- Literature review regarding MSI, material emissivity model and curve fitting algorithms
- Development of a virtual experiment platform
- Generate virtual experiments with various emissivity models and temperature fields
- Optimization of the MSI algorithm based on virtual experiments
- Scientific documentation of the results



# Declaration

I hereby confirm that this semester thesis was written independently by myself without the use of any sources beyond those cited, and all passages and ideas taken from other sources are cited accordingly.

.....  
Location, Date

.....  
Signature

With the supervision of Mr. Zhaoyong Wang by Mr. Ruihang Dai intellectual property of the Professorship Laser-based Additive Manufacturing (LBAM) flows into this work. A publication of the work or a passing on to third parties requires the permission of the head of the professorship. I agree to the archiving of the printed thesis in the LBAM library (which is only accessible to LBAM staff) and in LBAM's digital thesis database as a PDF document.

.....  
Location, Date

.....  
Signature

## Abstract

temperature is one of the most important parameters in PBF-LB/M. so, monitoring the temperature at melt pool necessary. in oder to archieve this, a numerical experiment platform is formed. then parameter is calculated

## Zusammenfassung

Hier könnte Ihre Kurzzusammenfassung stehen.

# Contents

<b>1</b>	<b>LaTeX-Tutorial</b>	<b>1</b>
1.1	Titelseite . . . . .	1
1.2	Zitation . . . . .	1
1.3	Abkürzungen . . . . .	2
1.4	Glossar . . . . .	2
1.5	Abbildungen . . . . .	2
<b>2</b>	<b>Introduction</b>	<b>5</b>
<b>3</b>	<b>State of the art</b>	<b>7</b>
3.1	Process monitoring . . . . .	7
3.2	Multispectral imaging . . . . .	7
3.3	Emissivity model . . . . .	7
3.4	Temperature field in Laser-based Powder Bed Fusion . . . . .	7
3.5	Motivation of this thesis . . . . .	7
<b>4</b>	<b>Theory and methodology</b>	<b>9</b>
4.1	Physical value of radiation . . . . .	9
4.2	Virtual experiment platform . . . . .	11
4.3	Camera model . . . . .	11
4.3.1	Frequency response . . . . .	11
4.3.2	Integration method . . . . .	13
4.3.3	Implementation . . . . .	14
4.4	Temperature estimation algorithm . . . . .	15
4.5	Emissivity model in temperature estimation algorithm . . . . .	16
<b>5</b>	<b>Application and validation</b>	<b>17</b>
5.1	Experiment data generation . . . . .	17
5.1.1	Temperature field . . . . .	18
5.1.2	Emissivity model . . . . .	19
5.1.3	Camera model . . . . .	22
5.2	Temperature estimation algorithm . . . . .	22
5.2.1	Rebuild physical value of spectral radiation intensity . . . . .	23
5.2.2	Emissivity model used for calculation . . . . .	23
5.2.3	Curve fit algorithm . . . . .	25
5.2.4	Parameters in calculation . . . . .	25
5.3	Validation . . . . .	25
<b>6</b>	<b>Calcualtion results and analysis</b>	<b>27</b>
6.1	Calculation results . . . . .	27
6.1.1	Temperature field . . . . .	27
6.1.2	Emissivity field . . . . .	27
6.2	Data analysis . . . . .	27
6.2.1	Sensitivity analysis of emissivity models . . . . .	27
6.2.2	Performance between different materials . . . . .	27

<b>A Appendices</b>	<b>29</b>
<b>Glossary</b>	<b>31</b>
<b>Bibliography</b>	<b>33</b>
<b>List of Abbreviations</b>	<b>35</b>



# 1 LaTeX-Tutorial

Dieses Tutorial liefert eine Kurzeinführung in die Verwendung von Latex.

## 1.1 Titelseite

Die Titelseite wird in `./main.tex` definiert. Der Studienarbeitstyp wird durch Ein- und Auskommentieren der Befehle

- `\IWbstudentthesisTitlePageCustomMastersThesis,`
- `\IWbstudentthesisTitlePageCustomBachelorsThesis` und
- `\IWbstudentthesisTitlePageCustomSemesterThesis`

ausgewählt und die Seite entsprechend der Argumente gesetzt. Die Professoren und Lehrstühle können mittels der Makros

- `\IWbnamesProfReinhart \newline \IWBlangChairMWIWBLBM` oder
- `\IWbnamesProfZaeh \newline \IWBlangChairMWIWBLWF`

ausgewählt werden.

## 1.2 Zitation

Zum Zitieren stehen die Standardbefehle `\textcite` und `\parencite` zur Verfügung. Soll der Autorename im Satz verwendet werden, eignet sich ersteres, z.B. **Bayerlein2018** bezieht sich auf **Bayerlein2016469**. Soll das Zitat in Klammern nach die Aussage gestellt werden empfiehlt sich zweiteres [**Zaeh2018385**]. Sammelzitationen am Satzende schreiben sich wie folgt [**Kleinwort2018658, Kleinwort20189, Kleinwort2018631**]. Die Zitation von Online-Quellen kann schwierig sein, da nicht immer der Autor und das Erscheinungsjahr verfügbar sind. Vergleicht man **Heuss2018** und **iwb-Startseite**, stellt man fest, dass bei zweiteren der Seitentitel statt des bekannten Schemas eingesetzt wird.

Normen werden als dargestellt. Im Bibtex-Export des verwendeten Literaturverwaltungsprogramm sind bestimmte Einstellungen vorzunehmen. Dokumententyp ist `“@book”` mit folgenden Einträgen:

- Normtyp und Nummer als `“title”`
- Langtitel als `“subtitle”`
- Verlag als `“publisher”`
- Jahr als `“date”`
- `“author”` darf nicht belegt werden!

## 1.3 Abkürzungen

In `./source/abbreviations.tex` können Abkürzungen definiert werden. Es gibt Besonderheiten zu Ausdrücken, deren Pluralendung nicht auf `s` endet. Hier müssen ggf. Kurz- und Langformen des Ausdrucks auch für den Plural definiert werden.

- `\gls{ros}`: schreibt beim ersten Auftreten im Dokument ausführlich Robot Operating System (ROS), ab dem zweiten Auftreten wird abgekürzt ROS
- `\glspl{ap}` verwendet den Plural in Langform Arbeitspakete (APs) und danach in Kurzform APs

## 1.4 Glossar

In `./source/glossary.tex` können Begriffe erklärt, abgegrenzt oder definiert werden. Begriffe erhalten einen Namen und eine Beschreibung als Glossareintrag sowie ein Label zum Referenzieren im Text. Ein Glossar ist Optional.

- `\gls{latex}`: Schreibt den Namen aus dem Glossarverzeichnis mit Verweis auf den Glossareintrag `Latex`

## 1.5 Abbildungen

Graphiken und Bilder können in beliebigen Dateiformaten eingebunden werden, vergleiche fig. 1. Vektorgraphiken sind im Allgemeinen Pixelgraphiken in Schärfe und Speicherbedarf überlegen.



Figure 1: Beschreibung des Bilds. Außerdem machen wir nun die Bildunterschrift unnötig lang um die Formatierung zu testen.




Figure 2: Beschreibung des Plots. Außerdem machen wir nun die Bildunterschrift unnötig lang um die Formatierung zu testen.

Für Nutzer mit perfektionistischen Anspruch empfiehlt sich die Nutzung von TikZ. Vorteil ist, dass die Erzeugung von Daten und die Darstellung komplett getrennt werden. Die Darstellung erfolgt einheitlich gemäß eines generischen Mark-Ups, vergleiche figs. 2 and 3.



Figure 3: Beschreibung des Plots. Außerdem machen wir nun die Bildunterschrift unnötig lang um die Formatierung zu testen.



## 2 Introduction

Additive Manufacturing (AM) is a different type of processing technology to conventional manufacturing methods. Instead of removing material from the raw part, additive manufacturing is usually described as "a process of joining materials to make objects layer by layer or element by element"[1]. It is a useful method for reducing the the duration from product design to product manufacturing and imporving the material utilization[2].

There are several AM technologies that can be sorted into different categories. Laser-based Powder Bed Fusion of Metals (PBF-LB/M), which also called Selective Laser Sintering (SLS), is one of the powder based AM processes[3]. In this process, a laser beam with high energy density is focused onto the surface of a metal powder bed, which was heated up to a temperature near the melt temperature. Then, the metal powder is melted and form the upper surface of the object. Last, the building platform will go downwards to build next layer. This process will be repeated until the desired object is built[4].

Since the process is based on the phase change of materials, processing parameters such as laser power, layer thickness, hatch distance and scanning strategies are critical for producing dense materials, minimize defects, improve surface quality and build rate[5]. The common denominator between them is that the parameters of the process are varied by controlling the temperature profile of the metal powder[2]. Thus, the importance of obtaining the temperature information on the surface layer is high.

The solidification front of metal powders moves with a high velocity (generally  $0.01 \sim 10 \text{ m/s}$ )[6], the cooling rate of material is normally at range of  $10^5 \sim 10^6 \text{ K/m}$ [5]. Thus, a contactless temperature measurement is required to obtain the temperature of the surface area.

Two different methods is used for monitoring the surface temperature in recent studies, namely conventional infrared irradiation temperature measurement methods and multi-wavelength techniques[7]. Infrared irradiation technique is cost-effective, but it requires information about the emissivity of the material[8]. On the contrary, a multi-color pyrometer with a specific wavelength range could be used in the case of changing emissivity[9]. In this thesis, a virtual experiment platform using a multispectral imaging algorithm is developed to simulate the output behavior of a spectral pyrometer.

After obtaining the radiation image, a curve fit algorithm is applied to estimate the temperature field of the image and emissivity field simultaneously. This semester thesis aims to develop a stable temperature estimation program based on curve-fit algorithm. With the results obtained from the virtual experiment platform, the performance of the temperature estimation algorithm is verified.



## 3 State of the art

haha[10]

3.1 Process monitoring

3.2 Multispectral imaging

3.3 Emissivity model

3.4 Temperature field in Laser-based Powder Bed Fusion

3.5 Motivation of this thesis





## 4 Theory and methodology

As mentioned in previous sections, forming a virtual experiment platform is necessary for investigating the temperature estimation algorithm. So, a virtual experiment platform is developed based on Planks'law, then, a virtual multi-spectral pyrometer is applied to obtain the digital value (also called image).

### 4.1 Physical value of radiation

Radiation is emitted from any object with a temperature above 0 K. In equation 4.1 can be found, that the radiation depends on the black body radiation  $B(\lambda, T)$  and emissivity  $\varepsilon(\lambda, T)$ . Both value are temperature  $T$  and wavelength  $\lambda$  dependent.

$$L(\lambda, T) = B(\lambda, T) \cdot \varepsilon(\lambda, T) \quad (4.1)$$

By Plank's Law, black body radiation can be described in Eq.4.2,

$$B(\lambda, T) = \frac{2hc^2}{\lambda^5} \cdot \left[ \exp\left(\frac{hc}{\lambda k_B T}\right) - 1 \right]^{-1} \quad (4.2)$$

With absolute temperature  $T$ , wavelength  $\lambda$ , speed of light  $c$ , Plank constant  $h$  and Boltzmann constant  $k_B$ . Black body radiation is irrelevant to the material itself, all materials at the same temperature have the same spectral black body radiation.




Figure 4: Black body radiation of materials with different temperature

Fig.4 illustrates the spectral radiation intensity of a blackbody at different temperatures. It can be observed that the spectral radiation intensity exhibits a peak at a specific wavelength.

According to Wien's displacement law, the relationship between the wavelength of the peak  $\lambda_{peak}$  and temperature  $T$  can be described in Eq.4.3:

$$\lambda_{peak} = \frac{b}{T} \quad (4.3)$$

With Wien's displacement constant  $b = 2898 \mu m \cdot K$ , it can be found that the wavelength of this peak decreases as the temperature rises.

From this, it can be concluded that the shape of the blackbody's spectral radiation intensity varies with temperature. This is evident in two aspects: firstly, the position at which the peak appears, and secondly, the distribution of spectral radiation intensity along the wavelength. Indeed, this characteristic provides the possibility to determine the temperature of a blackbody material in reverse, i.e., by calculating the temperature based on the known spectral radiation intensity.

On the contrary, emissivity varies from material to material. It is the ratio of the actual spectral intensity emitted by the object to the spectral intensity of the black body radiation. In the study of radiation, two idealized material models are generally used to describe the idealized properties of radiation, namely black body and grey body.




Figure 5: Black body radiation, emissivity and real radiation of an example normal material at 1000K

Black-body material emits electromagnetic black body radiation, which is irrelevant to the wavelength of the radiation and the shape of the material[11]. Which also means the emissivity of a black body is constantly 1. It could be used to validate the temperature estimation algorithm in following sections.

Unlike black-body materials, grey-body materials have an emissivity between 0 and 1. Not all of the thermal radiation could be emitted to the outside of the material. Different from

normal materials, the emissivity of a grey-body material is irrelevant to the wavelength of radiation.

In Fig.5 can be found, that the real spectral intensity of a normal material is lower than the black body spectral intensity. And the emissivity of the material varies with the increase of the radiation wavelength.

It can be seen that the construction of a reliable emissivity model is crucial to the accuracy of the virtual experimental platform. It is the key component used to generate the experimental data.

## 4.2 Virtual experiment platform

After obtaining the physical spectral intensity of the material, a virtual experiment platform is used to transform the physical value into digital value, which simulate the behavior of a real spectral pyrometer. As described in Fig.6a, a camera with a lens system focused on the surface of the powder bed is responsible for obtaining spectral radiation of the heated metal powder. It can be seen from Fig.6b, each pixel of the sensor contains 8 filters and thus be able to obtain 8 intensity digital values in different channels. Thus, a virtual experiment platform with the same structure as the real experiment platform is built.




Figure 6: Structure of the virtual experiment platform and Layout of a sensor pixel

## 4.3 Camera model

It can be found in Fig.6, The thermal radiation is emitted from the surface of powder bed, and passes through the lens system of the camera, finally, it reaches the sensor and be converted into digital values. The simplified process can be seen in Fig.7. As  $dA_m$  is the area of the focused surface and  $dA_{pixel}$  the area of the pixel in camera system,  $n_m$  is the normal vector of the surface.

### 4.3.1 Frequency response

After obtaining the virtual experiment platform and knowing the external setup of the sensor, the internal effects of the camera system should also be taken into account in the complete virtual experiment platform.




Figure 7: Radiative exchange between camera system and powder bed

In order to simulate real camera system, the frequency response of sensor and lens should be considered. In real camera systems, all spectral radiation will pass through the lens system of camera. Since the lens system is not an idealized system, the effect of the lens system is not negligible.




Figure 8: Frequency response of the lens system

It can be found in Fig.8 that system gain of lens system is not constant. In the wavelength range of 500 to 700 nanometers, the lens is more sensitive to the radiation with long wavelength. With the increasing wavelength, the system gain of the lens system keep constant at 0.853.

In addition to the fact that the lens system respond differently to radiation with different wavelengths, the sensor of the camera also have wavelength-dependent quantum efficiency. As mentioned in previous section, the acquisition of the spectral intensity by the sensor for different channels is based on the filter before the pixels.

Fig.9 shows the quantum efficiency of the camera sensor in different channels. Unlike an ideal sensor that receives only single wavelength radiation, the intensity information received by a real sensor is a combination of a spectral radiation and 8 filters with different frequency responses. Thus, the camera system is able to obtain the spectral radiation intensity in 8 channels simultaneously.

To make the virtual experiment platform more comparable to real experiments, it can be




Figure 9: Quantum efficiency of camera system in each channel

concluded that it is necessary to build a camera model that incorporates the effects of sensor quantum efficiency and lens transparency. Then, the physical value of the spectral radiation intensity could be calculated accurately by the digital value of spectral radiation intensity obtained from the virtual experiment platform.

#### 4.3.2 Integration method

As a result, the process of converting the physical values of radiation intensity into digital values needs to be accurately reproduced. Since the total efficiency of the camera ( $\eta_{camera}$ ) was delivered by quantum efficiency ( $\eta_{quantum}$ ) of the sensor and transparency of the lens system ( $\tau_{lens}$ ), the mathematical relationship could be described in Eq.4.4.

$$\eta_{camera} = \eta_{quantum} \cdot \tau_{lens} \quad (4.4)$$

Fig.10 shows the relationship between the incoming spectral radiation intensity and actual captured spectral radiation intensity by the camera system. It can be found that the wavelength of the spectral radiation intensity actually received by the sensor deviates from the wavelength of the spectral radiation intensity it supposed to receive.

Obtaining the physical value of spectral radiation intensity, the sensor is responsible for transforming the physical value into digital value for upcoming proceedings. The camera system used in real experiment platform uses Charge-coupled device (CCD) or Complementary Metal-oxide Semiconductor (CMOS) as their sensors. Both sensors transform the photon flux  $\phi(\lambda)$  incident on the semiconductor into photocurrent  $I_{ph}$  [12].

$$I_{ph} = q \int_{\lambda} \phi(\lambda) \cdot \eta_{camera}(\lambda) d\lambda \quad (4.5)$$

With a certain temperature  $T$ :

$$\phi(\lambda) = L(\lambda, T) \quad (4.6)$$




Figure 10: Actual received spectral radiation intensity by channel 1 at 1000K

Eq.4.5 is the mathematical description of the transformation. Where  $\phi(\lambda)$  denotes photon flux on the sensor, which is equal to the spectral radiation intensity on the sensor  $L(\lambda, T)$  as described in Eq.4.6, and  $\eta_{camera}(\lambda)$  denotes the total efficiency of the camera in Eq.4.4.  $q$  is the sensitivity parameter of the sensor.

### 4.3.3 Implementation

Similar to the method used to obtain the digital value of spectral radiation intensity in the real experiment, the virtual experiment platform calculates the intensity digital value in 8 channels using the virtual camera by entering the material properties of the point being measured.



Figure 11: Procedure of using virtual experiment platform to generate digital values

Fig.11 shows the working procedure of the virtual experiment platform. To enable the virtual experimental platform to run on various devices, the entire platform has been implemented using Python as the programming language and packaged into a .py file. Furthermore, all functions have been vectorized to facilitate the generation of image outputs resembling those captured by a physical camera. Additionally, the parallel computing package in Python has been utilized to minimize computation time.

## 4.4 Temperature estimation algorithm

After obtaining the experimental data calculated by the virtual experiment platform, a temperature estimation algorithm should be developed to calculate the temperature of the measured point based on the experimental data.

Similar to the set up in real experiments, the parameters of the camera model can be considered as known in the virtual experimental platform mentioned in this article. This will on the one hand improve the accuracy of the temperature estimation algorithm and on the other hand avoid some unnecessary complexity.

Thus, in this temperature estimation algorithm, the known variable is the digital value of spectral intensity captured by camera model in virtual experiment platform, the characteristic of the camera system. The variables to be estimated are the temperature of the measured point and its emissivity.




Figure 12: Procedure of temperature estimation algorithm

Fig.12 shows the proceeding procedure of the temperature estimation algorithm. The physical value of the spectral radiation intensity ( $I_{rec}(i)$ ) in the  $i_{th}$  channel should be reconstructed in Eq.4.7:

$$I_{rec}(i) = q \int B(\lambda, T) \cdot \varepsilon(\lambda, k, T) \cdot \eta_{camera}(i) d\lambda \quad (4.7)$$

With  $I_{rec}(i)$  the reconstructed physical value in  $i_{th}$  channel,  $B(\lambda, T)$  the black body radiation,  $\varepsilon(\lambda, k, T)$  the emissivity model in temperature estimation algorithm,  $\eta_{camera}(i)$  the total camera efficiency of  $i_{th}$  channel. It can be found that the emissivity model have an additional parameter  $k$ , this parameter is used for fitting the emissivity behavior of the measured material. More details can be found in the following section.

Once the reconstruction of the physical value is completed, it is necessary to convert this physical value into a digital value. This conversion process is dependent on the parameter settings of the sensor system, such as exposure time, aperture size of the lens, etc. For the purposes of this paper, it is assumed that the conversion relationship is linear.

Given an initial guess of the status parameters, namely temperature( $T_0$ ) and parameters in emissivity model( $k_0$ ). Then, an curve fit algorithm is applied to minimize the difference between the reconstructed digital value ( $I_{rec}$ ) and the actual digital value ( $I_{act}$ ) in Eq.4.8.

$$\min_{k, T} \sum_{i=1}^8 F(I_{rec}(i), I_{act}(i)) \quad (4.8)$$

$F(I_{rec}(i), I_{act}(i))$  is the cost function of the curve fit algorithm. In this application, Non-linear least squares method is used to obtain the optimum parameters as Eq.4.9.

$$F(I_{rec}(i), I_{act}(i)) = (I_{rec}(i) - I_{act}(i))^2 \quad (4.9)$$

After obtaining the estimated temperature ( $T_{estimate}$ ) and the parameter ( $k$ ) in the emissivity model, the data will be saved in a .xlsx file for potential operations.

#### 4.5 Emissivity model in temperature estimation algorithm

As an unknown quantity in the temperature estimation algorithm, the nature of emissivity as a function of wavelength also introduces an additional degree of freedom into the overall calculation process. In order to provide a more general description of the trend of emissivity with wavelength, an additional parameter ( $k$ ) in the emissivity model used for temperature estimation has been introduced.

Due to the inherent complexity of this trend, it is often impossible to describe the emissivity using a single parameter. Therefore, the parameter ( $k$ ) is normally represented as a vector composed of multiple variables. This approach allows for both a concise mathematical representation and the incorporation of more intricate emissivity models into the temperature estimation algorithm.



## 5 Application and validation

After the theoretical basis of the virtual experiment platform is known and the program of the virtual experiment platform is built, the application should be verified with experiment data generated based on the real experiment.




Figure 13: Complete procedure from data generation to model validation

Fig.13 shows the procedure of the application. Firstly, an experiment data set should be generated according to the parameters of the hypothetical material. Then, a temperature estimation algorithm is applied to estimate the temperature of the hypothetical material. Last, a validation procedure is used to check the accuracy and stability of the results of temperature estimation algorithm.

As mentioned in previous sections, these functions is implemented in three programmes. Namely virtual experiment platform, temperature estimation algorithm and validation procedure. Similar to conventional experiment methods, these steps are independent procedures, which means they do not interact with each other.

Accordingly, this chapter will be divided into three sections, which describe the implementation and the parameter settings of the virtual experiment platform, temperature estimation algorithm and validation procedure.

### 5.1 Experiment data generation

As the first of the three steps mentioned above, it is crucial to generate accurate experimental data correctly. It affects the comparability of the virtual experimental platform with real experiments on the one hand, and the accuracy of the temperature estimation algorithm on the other. As a result, the virtual experimental platform should be able to perform calculations for as many hypothetical materials with different properties as possible.

In order to be able to obtain image similar to image from real camera, the area that the virtual camera is able to capture is set to a 50\*50 pixel picture. Fig.14 shows the image obtained from real experiment and virtual experiment platform. The major difference between these two images is the coloring. In real experiment, the raw image was saved as a .tiff file, which obtain the spectral intensity received by the specific channel. Then, the intensity is expressed as brightness of the pixel in the display of the image. This results in the experiment data that is not intuitive and requires specialised software to open these data.

As a result, there are a number of optimisations that have been applied in this virtual

experiment platform. Firstly, the raw digital value of the received spectral intensity was saved in an .xlsx file, which simplifies the reading of the data as well as the conversion. In addition, a .jpg image of each channel similar to the real experiment data is also saved. Different from the real experiment data, colours are used here to indicate the value of the spectral intensity. This improves the readability of the experiment data.




Figure 14: Comparison between real experiment data at 1300K (a) and virtual experiment data at 1098K (b)

Thus, the observation area is obtained by initialization of the the virtual experiment platform. Temperature field, emissivity model of the hypothetical material and the integration method are the parameters to be defined as the next step.

### 5.1.1 Temperature field

As mentioned in previous sections, temperature is one of the most important parameters in the virtual experiment platform. In order to obtain results similar to real experiments, a temperature field exists in the observation area. For the purpose of simplifying the calculation process, this temperature field consists of two main regions, a background region at the edge of the observation area, where the temperature is uniformly set to 1000K, and an internal high temperature region, where the temperature follows a predefined distribution.

Fig.15 shows three different temperature distribution which are able to be generated by the virtual experiment platform. Namely linear distribution, gaussian distribution and sigmoid distribution. In order to simplify the visualization process, all temperature fields are generated based on the center point of the observation area. As the temperature of each point is calculated based on the normalized distance  $d_{rel}$  or absolute distance  $d_{abs}$  to the center point of the observation area.

Linear distribution means that the temperature increases linearly from the back ground area to the center point of the observation area. The details can be found in Eq.5.1. This distribution has the potential to demonstrate the spectral radiation behavior of the hypothetical material in different temperature.

$$t = t_{center} + (t_{background} - t_{center}) \cdot d_{rel} \quad (5.1)$$

Gaussian distribution is also called normal distribution. In this distribution type, the temperature field in observation area obeys gaussian distribution described in Eq.5.2. With the temperature of the center point in observation area equals the defined center




Figure 15: Temperature field of 3 different temperature distribution and the temperature profile in the middle line of the observation area. (a): Linear distribution. (b): Gaussian distribution. (c): sigmoid distribution

temperature. Due to energy input of the system and heat transfer in metal powder, this temperature distribution is more likely to simulate the real situation in experiment.

$$t = t_{center} + (t_{background} - t_{center}) \cdot \exp\left(-\frac{d_{abs}^2}{2 \cdot \sigma^2}\right) \quad (5.2)$$

Different to the temperature field mentioned before, the temperature in the center region of observation area remains constant. The mathematical expression can be found in Eq.5.3:

$$t = t_{center} + (t_{background} - t_{center}) \cdot \text{sigmoid}\left(\left(\frac{d_{abs}^2}{r_{set}^2} + 1\right) \cdot 1000\right) \quad (5.3)$$

With sigmoid function can be found in Eq.5.4:

$$\text{sigmoid}(x) = \left(1 + \exp\left(-\frac{x}{100}\right)\right) \quad (5.4)$$

Sigmoid function gives the opportunity to perform the temperature estimation algorithm in a stable temperature. Thus, the potential to investigate the consistency of the temperature estimation algorithm and performance of the noise cancellation program is given.

### 5.1.2 Emissivity model

Obtaining temperature field of the hypothetical material, an emissivity model is required to calculate the physical value of spectral radiation intensity emitted from the hypothetical material.




Figure 16: Raw emissivity data used in virtual experiment platform. (a), (b) are black body and gray body; (c) - (h) are hypothetical materials[13]; (i) - (l) are real materials[14].

Since the emissivity of metal powder is wavelength ( $\lambda$ ) and temperature ( $T$ ) relevant, the emissivity model in this virtual experiment platform is formed based on the Eq.5.5.

$$\varepsilon(\lambda, T) = \varepsilon_{raw}(\lambda) \cdot K_T(T) \quad (5.5)$$

The raw emissivity data  $\varepsilon_{raw}(\lambda)$  in Fig.16 are obtained by Wang et al.[13] and Taunay et al.[14]. These data sets could be used to simulate the radiation behavior of various hypothetical materials.

After obtaining the raw data on the relationship between emissivity and wavelength, the dependence of emissivity on temperature is characterised as a temperature factor  $K_T(T)$  in Eq.5.6.

$$K_T(T) = \begin{cases} 1 - T_{ref} \cdot 0.2 & T < T_{melt} \\ (1 - T_{ref} \cdot 0.2) \cdot 0.1 & T \geq T_{melt} \end{cases} \quad (5.6)$$

With

$$T_{ref} = \frac{T - T_{lb}}{T_{ub} - T_{lb}} \quad (5.7)$$

This temperature factor describes the tendency of emissivity to decrease with increasing temperature between  $T_{lb}$  and  $T_{ub}$ , on the other hand, it also describes the change of emissivity due to the phase change of the hypothetical material that occurs at melting temperature  $T_{melt}$ .




Figure 17: Emissivity value along wavelength and temperature calculated from model 9

Fig.17 shows the emissivity model based on model 9 in different temperature and wavelength. It can be found that the emissivity at a temperature below melting temperature (1700K) varies significantly with wavelength. This is caused due to the raw emissivity data. Then, at liquid phase of the hypothetical material, emissivity decreases to a value lower than 0.1.

Thus, the phase change phenomenon of hypothetical material is also characterized, which gives the virtual experiment platform more potential to simulate real experiments.

### 5.1.3 Camera model

After obtaining the temperature field and emissivity model of hypothetical material, the physical value of spectral radiation intensity should be calculated, then, the physical value of spectral radiation intensity is converted to digital value using camera model, which is the output of the complete virtual experiment platform.

To ensure consistency and scalability within the program for future feature additions, all calculations in the program are conducted using metric units. For instance, temperature is measured in Kelvin, and wavelength is measured in meters. Therefore, it is crucial to note that the unit of wavelength in the camera model's calculations is meters, not nanometers. This ensures dimensional correctness throughout the integration process.

As mentioned in Fig.10, the camera model is based on an integration method, which integrate the spectral intensity received by the sensor along the specific range of wavelength. However, due to the varying quantum efficiency of each channel in sensor, it means that for a virtual camera with 8 channels, each pixel requires 8 independent integration operations. This operation requires a large computational effort. So, in order to accelerate the generation speed and thus reduce the time cost of virtual experiment platform, a parallel computing strategy is introduced.




Figure 18: Shape of array used in camera model

The essence of parallel computing lies in decomposing a complex task into multiple tasks and utilizing multithreading techniques to execute these computational tasks simultaneously on different cores of the CPU. In this context, the camera model treats the integral computation on each pixel as an individual task, thereby significantly improving CPU utilization and substantially reducing computational time[15]. To facilitate task partitioning, the dimension of the temperature field mentioned earlier in this section needs to be reduced, from a  $50 \times 50$  matrix to a one-dimensional array of size  $2500 \times 1$ . This allows for obtaining 2500 parallel tasks. Once the calculations are completed, the resulting matrix of size  $2500 \times 8$  is then transformed back into a three-dimensional matrix of size  $50 \times 50 \times 8$ . In this manner, a digital value similar to the data obtained in real experiments is computed.

## 5.2 Temperature estimation algorithm

After obtaining the digital value of spectral radiation intensity, the tasks of this virtual experiment platform are considered complete, and the next step involves data processing

and calculations. The core of the temperature estimation algorithm lies in reconstructing the physical value of spectral radiation intensity based on the known digital values and the chosen parameters. Subsequently, through the implementation of a curve fitting algorithm, the estimated emissivity and temperature can be calculated.

### 5.2.1 Rebuild physical value of spectral radiation intensity

Hence, it is evident that the process of reconstructing the physical value holds significant importance in the temperature estimation algorithm. This reconstruction process represents the conversion of spectral radiation intensity from its physical value to a digital value. By analyzing the reconstructed results, the relationship between the physical value ( $I_{rec}$ ) and the parameters ( $T, k$ ) to be fitted can be established, where  $T$  and  $k$  are derived from Eq.4.7. Subsequently, by performing curve fit algorithm between the reconstructed physical value and the experimental data, we can obtain the parameters ( $T, k$ ) that best fit the real data. Therefore, it becomes apparent that the reconstruction of the physical value can affect the accuracy of the temperature prediction algorithm discussed in this thesis.

As mentioned in Eq.4.7, the reconstructed physical value of spectral radiation intensity is generated based on the integration method. It can be observed that the digital value can be considered as a function of temperature of hypothetical material  $T$  and parameters of emissivity model  $k$ .

$$I_{rec}^i(k, T) = q \int B(\lambda, T) \cdot \varepsilon(\lambda, k, T) \cdot \eta_{camera}^i d\lambda \quad (5.8)$$

Eq.5.8 shows the mathematical expression of reconstructed physical value of spectral radiation intensity of  $i_{th}$  channel. So, the current objective is to minimize the cost in Eq.4.8 by optimizing the values of  $k$  and  $T$ . In other words, the goal is to make the reconstructed spectral radiation intensity  $I_{rec}(k, T)$  as close as possible to the values obtained in virtual experiments. By minimizing the cost function, the temperature estimation algorithm aims to achieve a high level of accuracy and fidelity in calculating the temperature based on the reconstructed digital values.

### 5.2.2 Emissivity model used for calculation

In the previous section, it is evident that the temperature estimation algorithm is essentially performing a curve fit algorithm on the parameters of the emissivity model and temperature of the hypothetical material. Therefore, the choice of the emissivity model significantly impacts the accuracy of the temperature estimation algorithm. In order to enhance the generality of this temperature prediction algorithm and prevent overfitting, a hypothesis is proposed: the temperature prediction algorithm is unaware of the material's emissivity characteristics. Hence, it is necessary to use a different emissivity model from the one used in the virtual experiment platform to reconstruct the digital value of spectral radiation intensity.

Based on mentioned above, the temperature estimation algorithm introduced in this paper tested several different emissivity models, namely:

1. Linear model
2. Linear square model
3. Quadratic model

4. Exponential model
5. A combined model composed of the linear square and exponential models

These models are distinguished based on the relationship between emissivity and wavelength. Each model represents a different mathematical expression that describes how emissivity varies with wavelength. In order to simplify the calculation process and thus set boundary conditions of parameters  $k$  in emissivity model, all wavelength used in this emissivity model is normalized wavelength  $\lambda_{norm}$ . The mathematical expression can be described as followed:

$$\lambda_{norm} = \frac{\lambda - \lambda_{lb}}{\lambda_{ub} - \lambda_{lb}} \quad (5.9)$$

With the lower boundary of wavelength  $\lambda_{lb} = 500nm$  and the upper boundary of wavelength  $\lambda_{ub} = 1000nm$ . Thus, the input of the emissivity model used in temperature estimation algorithm is thus dimensionless number.

#### Linear model

Linear model refers to a linear relationship between emissivity and wavelength, which could be written as Eq.5.10:

$$\varepsilon(\lambda) = a \cdot \lambda_{norm} + b \quad (5.10)$$

The linear model represents the simplest and most straightforward emissivity model. It provides an easy way to visualize the calculated emissivity model and reduces complexity in defining various boundary conditions within the emissivity model.

#### Linear square model

The linear square model is distinct from the linear model, as it incorporates three parameters representing the coefficients of the quadratic term, the linear term, and the constant term. Its mathematical expression can be described as Eq.5.11:

$$\varepsilon(\lambda) = a \cdot \lambda_{norm}^2 + b \cdot \lambda_{norm} + c \quad (5.11)$$

The linear square model can be used to describe more intricate emissivity models for materials. With an additional parameter compared to the previous linear model, it offers increased degrees of freedom for curve fitting, enabling a better fit to complex shapes. Nevertheless, the augmented complexity may also lead to a higher risk of overfitting as well as increase of computational demand required.

#### Quadratic model

Consequently, in order to simplify the computation of the linear square model, the quadratic model was introduced. In this model, the coefficient of the linear term in the original linear square model is set to 0. This simplification leads to a reduction in the number of parameters within the emissivity model. The emissivity model can be expressed as Eq.5.12

$$\varepsilon(\lambda) = a \cdot \lambda_{norm}^2 + b \quad (5.12)$$



**5.2.3 Curve fit algorithm**

**5.2.4 Parameters in calculation**

quantum efficiency, lens factor

**5.3 Validation**



## 6 Calculation results and analysis

### 6.1 Calculation results

#### 6.1.1 Temperature field

#### 6.1.2 Emissivity field

### 6.2 Data analysis

#### 6.2.1 Sensitivity analysis of emissivity models

#### 6.2.2 Performance between different materials



## A Appendices

Hello, here is some text without a meaning. This text should show what a printed text will look like at this place. If you read this text, you will get no information. Really? Is there no information? Is there a difference between this text and some nonsense like “Huardest gefburn”? Kjift – not at all! A blind text like this gives you information about the selected font, how the letters are written and an impression of the look. This text should contain all letters of the alphabet and it should be written in of the original language. There is no need for special content, but the length of words should match the language.

This is the second paragraph. Hello, here is some text without a meaning. This text should show what a printed text will look like at this place. If you read this text, you will get no information. Really? Is there no information? Is there a difference between this text and some nonsense like “Huardest gefburn”? Kjift – not at all! A blind text like this gives you information about the selected font, how the letters are written and an impression of the look. This text should contain all letters of the alphabet and it should be written in of the original language. There is no need for special content, but the length of words should match the language.

And after the second paragraph follows the third paragraph. Hello, here is some text without a meaning. This text should show what a printed text will look like at this place. If you read this text, you will get no information. Really? Is there no information? Is there a difference between this text and some nonsense like “Huardest gefburn”? Kjift – not at all! A blind text like this gives you information about the selected font, how the letters are written and an impression of the look. This text should contain all letters of the alphabet and it should be written in of the original language. There is no need for special content, but the length of words should match the language.

After this fourth paragraph, we start a new paragraph sequence. Hello, here is some text without a meaning. This text should show what a printed text will look like at this place. If you read this text, you will get no information. Really? Is there no information? Is there a difference between this text and some nonsense like “Huardest gefburn”? Kjift – not at all! A blind text like this gives you information about the selected font, how the letters are written and an impression of the look. This text should contain all letters of the alphabet and it should be written in of the original language. There is no need for special content, but the length of words should match the language.

Hello, here is some text without a meaning. This text should show what a printed text will look like at this place. If you read this text, you will get no information. Really? Is there no information? Is there a difference between this text and some nonsense like “Huardest gefburn”? Kjift – not at all! A blind text like this gives you information about the selected font, how the letters are written and an impression of the look. This text should contain all letters of the alphabet and it should be written in of the original language. There is no need for special content, but the length of words should match the language.



# Glossary

Latex	Generische Mark-up-Sprache zum Erstellen wissenschaftlicher Texte. Sie ist in jeder Hinsicht Word überlegen, welches einem visuellen Mark-Up entspricht. Das X von $\text{\LaTeX}$ wird als ç (Stimmloser palataler Frikativ) ausgesprochen, vergleiche deutsche Aussprache von <i>ch</i> .
TikZ	Frontend-Paket, das auf PGF-Plot aufbaut und zum Erstellen von Graphiken dient.
Tutorial	Kurze Gebrauchsanleitung welche ein Thema, einen gewissen Vorgang oder eine Funktion erklärt. Hat nicht den Anspruch auf Vollständigkeit.





## Bibliography

- [1] Frazier, W. E., “Metal additive manufacturing: A review”, *Journal of Materials Engineering and Performance*, vol. 23, no. 6, pp. 1917–1928, 2014, ISSN: 1544-1024. DOI: 10.1007/s11665-014-0958-z. [Online]. Available: <https://link.springer.com/article/10.1007/s11665-014-0958-z>.
- [2] Swift, K. G. and Booker, J. D., “Rapid prototyping processes”, in *Manufacturing process selection handbook*, Swift, K. G. and Booker, J. D., Eds., Amsterdam: Elsevier, 2013, pp. 227–241, ISBN: 9780080993607. DOI: 10.1016/B978-0-08-099360-7.00008-2.
- [3] Kruth, J. P., “Material increment manufacturing by rapid prototyping techniques”, *CIRP Annals*, vol. 40, no. 2, pp. 603–614, 1991, ISSN: 0007-8506. DOI: 10.1016/S0007-8506(07)61136-6. [Online]. Available: <https://www.sciencedirect.com/science/article/pii/S0007850607611366>.
- [4] Revilla-León, M., Meyer, M. J., and Özcan, M., “Metal additive manufacturing technologies: Literature review of current status and prosthodontic applications”, *International Journal of Computerized Dentistry*, pp. 55–67, 2019.
- [5] Oliveríra, J., LaLonde, A., and Ma, J., “Processing parameters in laser powder bed fusion metal additive manufacturing”, *Materials & Design*, vol. 193, p. 108762, 2020, ISSN: 0264-1275. DOI: 10.1016/j.matdes.2020.108762. [Online]. Available: <https://www.sciencedirect.com/science/article/pii/S0264127520302963>.
- [6] DebRoy, T., Wei, H. L., Zuback, J. S., Mukherjee, T., Elmer, J. W., Milewski, J. O., Beese, A. M., Wilson-Heid, A., De, A., and Zhang, W., “Additive manufacturing of metallic components – process, structure and properties”, *Progress in Materials Science*, vol. 92, no. 5, pp. 112–224, 2018, ISSN: 00796425. DOI: 10.1016/j.pmatsci.2017.10.001.
- [7] Li, D., Liu, R., and Zhao, X., *Overview of in-situ temperature measurement for metallic additive manufacturing: How and then what*, 2019. DOI: 10.26153/TSW/17384.
- [8] Hagqvist, P., Sikström, F., and Christiansson, A.-K., “Emissivity estimation for high temperature radiation pyrometry on ti-6al-4v”, *Measurement*, vol. 46, no. 2, pp. 871–880, 2013, ISSN: 02632241. DOI: 10.1016/j.measurement.2012.10.019.
- [9] Pixner, F., Buzolin, R., Schönfelder, S., Theuermann, D., Warchomicka, F., and Enzinger, N., “Contactless temperature measurement in wire-based electron beam additive manufacturing ti-6al-4v”, *Welding in the World*, vol. 65, no. 7, pp. 1307–1322, 2021, ISSN: 1878-6669. DOI: 10.1007/s40194-021-01097-0. [Online]. Available: <https://link.springer.com/article/10.1007/s40194-021-01097-0>.
- [10] Bammer, F., Holzinger, B., Humenberger, G., Schuöcker, D., and Schumi, T., “Integration of high power lasers in bending tools”, *Physics Procedia*, vol. 5, pp. 205–209, 2010, ISSN: 18753892. DOI: 10.1016/j.phpro.2010.08.045.
- [11] Kuhn, T. S., *Black-Body Theory and the Quantum Discontinuity, 1894-1912*. University of Chicago Press, 1987, ISBN: 9780226458007.
- [12] Fossum, E. R. and Hondongwa, D. B., “A review of the pinned photodiode for ccd and cmos image sensors”, *IEEE Journal of the Electron Devices Society*, vol. 2, no. 3, pp. 33–43, 2014. DOI: 10.1109/JEDS.2014.2306412.

- [13] Wang, N., Shen, H., and Zhu, R., “Constraint optimization algorithm for spectral emissivity calculation in multispectral thermometry”, *Measurement*, vol. 170, p. 108 725, 2021, ISSN: 02632241. DOI: 10.1016/j.measurement.2020.108725.
- [14] Taunay, P.-Y. C. R. and Choueiri, E. Y., “Multi-wavelength pyrometry based on robust statistics and cross-validation of emissivity model”, *The Review of scientific instruments*, vol. 91, no. 11, p. 114 902, 2020. DOI: 10.1063/5.0019847.
- [15] Asanovic, K., Bodik, R., Demmel, J., Keaveny, T., Keutzer, K., Kubiawicz, J., Morgan, N., Patterson, D., Sen, K., Wawrzynek, J., Wessel, D., and Yelick, K., “A view of the parallel computing landscape”, *Communications of the ACM*, vol. 52, no. 10, pp. 56–67, 2009, ISSN: 0001-0782. DOI: 10.1145/1562764.1562783.

# List of Abbreviations

AM	Additive Manufacturing
AP	Arbeitspaket
CCD	Charge-coupled device
CMOS	Complementary Metal-oxide Semiconductor
LBAM	Professorship Laser-based Additive Manufacturing
MSI	Multispectral Imaging
PBF-LB/M	Laser-based Powder Bed Fusion of Metals
ROS	Robot Operating System
SLS	Selective Laser Sintering



# Disclaimer

I hereby declare that this thesis is entirely the result of my own work except where otherwise indicated. I have only used the resources given in the list of references.

Garching, July 31, 2023

---

(Signature)