

A large, tangled mass of raw, light brown wool fibers, showing the natural crimp and texture of the wool. The fibers are thick and fibrous, with a natural waviness (crimp) visible throughout the pile. The color is a warm, light tan or beige. The mass is irregular and voluminous, filling most of the frame. The background is a solid, bright yellow, which makes the wool stand out.

- Excellent thermal insulation
- Fire resistance
- Sound absorption
- Moisture resistance
- Lightweight

TECHNICAL DETAILS									
S.no	Characteristics	Standards	Value						
1.	Thermal Conductivity W/mK	IS 3677	Mean Temp.	50	100	150	200	250	300
			k value (W/mK)	0.036	0.042	0.051	0.06	0.071	0.081
2.	Maximum Service Temp	IS 3677	Upto 750°C						
3.	Leachable Chlorides Content	ASTM C871	10 ppm max						
4.	Shot Content	IS 3677	25% max includin all 3 sieve as 500 micron, 250 micron & 150 micron						
5.	Water Vapour Absorption	IS 3677	2 % max						
6.	Fibre Dia (microns)	IS 3677	7 Max						
7.	Heat Resistance	IS 3677	No Fusion of Fibres						