

- Dimensionally stable
- Corrosion resistance
- Lightweight
- Good compressive strength
- Low Thermal Properties

Range	Value
Standard Length	1200 mm
Thickness	25 mm – 100 mm
Diameter	0.5 inch – 14 inch
Density	128 & 144 kg/m ³

TECHNICAL DETAILS									
S.no	Characteristics	Standards	Value						
1.	Thermal Conductivity W/mK	IS 9842	Mean Temp.	50	100	150	200	250	300
			k value (W/mK)	0.036	0.042	0.051	0.06	0.071	0.081
2.	Maximum Service Temp	IS 9842	Upto 750°C						
3.	Leachable Chlorides Content	ASTM C871	10 ppm Max						
4.	Surface Burning Characteristics	ASTM E84	FSI: 0, SDI: 0						
5.	Shot Content	IS 9842	25% max includin all 3 sieve as 500 micron, 250 micron & 150 micron						
6.	Incombustibility (Loss of Weight %)	IS 9842	5 Max						
7.	Moisture Content (% weight)	IS 9842	2 Max						
8.	Water Vapour Absorption	IS 9842	2% Max						
9.	Fibre Dia (microns)	IS 9842	7 Max						
10.	Sulphur Content	IS 9842	0.2 % Max						
11.	Recovery after Compression	IS 9842	90% Min						
12.	Alkalanity (pH)	IS 9842	7-10						
13.	Heat Resistance	IS 9842	No Fusion of Fibres						
14.	Resin Content	IS 9842	3.5 % Max						
15.	Compressive Strength at 10% Deformation	ASTM D1621	240 kg/sqm Min						
16.	Linear Shrikage	IS 9842	2% Max						