

Shreeinsul Lightly Resin Bonded (LRB) Blanket offers an advanced solution for insulation needs, combining exceptional thermal efficiency with flexibility for different surface shapes and sizes. These matteresses are made of molten stone wool fibres bonded by a suitable resin and then stitching with GI wire mesh. This material complies to ASTM C592 & IS 8183.



- Superior Thermal Properties
- Water repellent
- Nominal Thermal Conductivity
- Easy to handle and install
- Fire Resistant

Range	Value
Density	80 - 160 kg/m³
Thickness	25 - 100 mm
Facing	GI Wire Mesh , SS Wire Mesh

TECHNICAL DETAILS									
S.no	Characteristics	Standards	Value						
1.	Thermal Conductivity W/mK	IS 8183	Mean Temp.	50	100	150	200	250	300
			Group III	0.036	0.042	0.051	0.064	0.073	0.084
			Group IV	0.036	0.042	0.052	0.060	0.071	0.081
2.	Maximum Service Temp	IS 8183	Upto 750°C						
3.	Leachable Chlorides Content	ASTM C871	10 ppm max						
4.	Surface Burning Characteristics	ASTM E84	FSI: 0, SDI: 0						
5.	Shot Content	IS 8183	25% max including all 3 sieve as 500 micron, 250 micron & 150 micron						
6.	Incombustibility (Loss of Weight %)	IS 8183	5 Max						
7.	Moisture Content (% weight)	IS 8183	2 Max						
8.	Water Vapour Absorption	IS 8183	2% max						
9.	Fibre Dia (microns)	IS 8183	7 Max						
10.	Sulphur Content	IS 8183	0.2 % Max						
11.	Recovery after Compression	IS 8183	90% Min						
12.	Alkalanity (pH)	IS 8183	7–10						
13.	Heat Resistance	IS 8183	No Fusion of Fibres						
14.	Resin Content	IS 8183	2 % Max						
15.	Compressive Strength at 10% Deformation	ASTM D1621	120 kg/sqm Min						
16.	Linear Shrikage	IS 8183	2% Max						