

Key Features

- Versatile applicability
- Excellent thermal insulation
- Fire resistance
- Sound absorption
- Moisture resistance
- Dimensionally stable

Range	Value
Density	48, 64, 96, 128, 144 kg/m³
Thickness	25 mm - 100 mm
Facing	Aluminium Foil
Standard Size	600 mm*1200 mm

Technical Details									
S.no	Characteristics	Standards	Value						
1.	Thermal Conductivity W/mK	IS 8183	Mean Temp.	50	100	150	200	250	300
			Group III	0.036	0.042	0.051	0.064	0.073	0.084
			Group IV	0.036	0.042	0.052	0.060	0.071	0.081
2.	Maximum Service Temp	IS 8183	Upto 750°C						
3.	Leachable Chlorides Content	ASTM C871	10 ppm Max						
4.	Surface Burning Characteristics	ASTM E84	FSI: 0, SDI: 0						
5.	Shot Content	IS 8183	25% max includin all 3 sieve as 500 micron, 250 micron & 150 micron						
6.	Incombustibility (Loss of Weight %)	IS 8183	5 Max						
7.	Moisture Content (% weight)	IS 8183	2 Max						
8.	Water Vapour Absorption	IS 8183	2% Max						
9.	Fibre Dia (microns)	IS 8183	7 Max						
10.	Sulphur Content	IS 8183	0.2 % Max						
11.	Recovery after Compression	IS 8183	90% Min						
12.	Alkalanity (pH)	IS 8183	7-10						
13.	Heat Resistance	IS 8183	No Fusion of Fibres						
14.	Resin Content	IS 8183	3.5 % Max						
15.	Compressive Strength at 10% Deformation	ASTM D1621	240 kg/sqm Min						
16.	Linear Shrikage	IS 8183	2% Max						