

Defect density vs L at fixed τ

