MAELAS code

User manual v1.0

Authors:

P. Nieves

S. Arapan

S.H. Zhang

A.P. Kądzielawa

R.F. Zhang

D. Legut



MAELAS: MAgneto-ELAStic properties calculation via computational high-throughput approach



NATIONAL SUPERCOMPUTING
CENTER





December 7, 2020

Email: pablo.nieves.cordones@vsb.cz

http://www.md-esg.eu/

Outline

- WHAT IS MAGNETOSTRICTION?
- WHAT IS MAELAS CODE?
- INSTALLATION
- HOW TO USE MAELAS CODE
- METHODOLOGY
- WORKFLOW
- BRIEF REVIEW OF KNOWN MAGNETOSTRICTIVE MATERIALS
- MAELAS TESTS
- VISUALIZATION TOOL MAELASviewer
- BIBLIOGRAPHY

WHAT IS MAGNETOSTRICTION?

Magnetostriction is a physical phenomenon in which the process of magnetization induces a change in shape or dimension of a magnetic material.




Figure 1: Magnetostriction of a single crystal under an external magnetic field ($\alpha \| H$) perpendicular to the measured length direction ($\beta \perp H$). Symbols M and M_s stand for macroscopic magnetization and saturation magnetization, respectively. Dash line on the right represents the original size of the demagnetized material. The magnetostriction effect has been magnified in order to help to visualize it easily, in real materials it is smaller ($\Delta l/l_0 \sim 10^{-3} - 10^{-6}$).

WHAT IS MAELAS CODE?

- MAELAS code is a software to calculate anisotropic magnetostrictive coefficients and magnetoelastic constants up to second order.
- ➤ It generates required input files for VASP code to perform Density Functional Theory calculations, and it deduces the value of magnetostrictive coefficients from the calculated energies given by VASP.
- If the elastic tensor is provided, then it can also calculate the magnetoelastic constants.
- MAELAS can also be used with other DFT codes instead of VASP, after file conversion to VASP format files.

INSTALLATION

The MAELAS code requires to have Python3(>=3.6). For example, in Ubuntu Linux machine you can check the installed version of python3 by opening a terminal and typing

python3 --version

In case you need to install python3 in your machine, you can type

sudo apt-get update sudo apt-get install python3

Note that in some HPC clusters you might need to load the Python module (ml Python). To install MAELAS code, download and extract the .zip file, go to the folder that contains the file setup.py and type

python3 setup.py install --user

This procedure will also install all required dependencies automatically


pymatgen(>=2020.4.29), scikit-learn(>=0.23.1), pyfiglet(>=0.8.post0), argparse(>=1.4.0), numpy(>=1.18.4), matplotlib(>=3.2.1), scipy(>=1.4.1), setuptools(>=40.8.0)

More available options for the installation can be found in the file INSTALL. By default, the executable file "maelas" is installed in the folder /home/\$USER/.local/bin/where \$USER is the name of your username folder. This folder should be included to the PATH variable by adding in the file /home/\$USER/.bashrc the following line

export PATH=/home/\$USER/.local/bin/:\$PATH

Then you should close the terminal and open the terminal again. If you need to install pip3 in Ubuntu Linux, then type

sudo apt-get update sudo apt-get install python3-pip



Step 1: Cell relaxation

If your initial POSCAR is not relaxed and you want to perform a cell relaxation before calculating the magnetostrictive coefficients, then you can use MAELAS code to generate INCAR and KPOINTS files to relax the structure with VASP. To do so, in the terminal you should copy your initial POSCAR in the same folder where you want to generate the input files for VASP, and after going to this folder then type

maelas -r -i POSCARO -k 40

where tag -r indicates that you want to generate VASP files for cell relaxation, -i POSCAR0 is the input non-relaxed POSCAR file (you can name it whatever you want) and -k 40 is the length parameter that determines a regular mesh of k-points. It will generate 4 files: POSCAR, INCAR, KPOINTS and vasp_jsub_rlx. Here, one still needs to copy manually the POTCAR file in this folder in order to have all required files for VASP run. The generated file vasp_jsub_rlx is a script to submit jobs in HPC facilities, one can specify some settings in this script by adding more tags in the command line. For instance,

maelas -r -i POSCARO -k 40 -t 48 -c 24 -q qprod -a OPEN-00-00 -f /scratch/example_rlx

where -t 48 indicates that the number of maximum CPU hours for the VASP calculation is 48 hours,-c 24 means that the number of cores for the VASP calculation is 24, -q qprod set the type of queue in HPC facilities, -a OPEN-00-00 is the project identification number for running jobs in HPC facilities and -f /scratch/example_rlx is the folder where you want to run VASP calculations. All these data are included in the vasp_jsub_rlx file, so one can submit this VASP job immediately in HPC facilities by typing

qsub vasp jsub rlx

This procedure might be helpful for high-throughput routines. Note that the user might need to modify vasp_jsub_rlx (it is in PBS Pro format) depending on the cluster or local computer batch scheduling. More options can be added in vasp_jsub_rlx file through the terminal command line, to see them just type

maelas –h

Note that generated INCAR and KPOINTS files contain standard setting for cell relaxation. The user might need to change these files in order to include more advanced settings. In case your structure is already relaxed or you do not want to perform a cell relaxation, then you can skip this step and move to step 2.

Step 2: Test MAE

Copy the relaxed POSCAR and POTCAR files in the same folder where you want to generate the input files for VASP jobs. In the terminal, after going to this folder then type

maelas -m -i POSCAR_rlx -k 70 -s1 1 0 0 -s2 0 0 1

where -m indicates that you want to generate input VASP files for the calculation of MAE, -i POSCAR_rlx is the initial relaxed POSCAR file (you can name it whatever you want), -k 70 is the length parameter that determines a regular mesh of k-points, -s1 1 0 0 is the first spin direction to calculate MAE: s1x s1y s1z and -s2 0 0 1 is the second spin direction to calculate MAE: s2x s2y s2z. It will generate the following files:

POSCAR_0_0 (it is the same POSCAR as)

INCAR_0_C (non-collinear calculation where C=1,2 is the spin orientation case)

INCAR_std (collinear calculation to generate the WAVECAR and CHGCAR files to run non-collinear calculations)

KPOINTS (file for the kpoint generation of VASP)

vasp_mae, vasp_mae_jsub and vasp_mae_0 (interconnected bash scripts to run VASP calculations automatically)

vasp_mae_cp_oszicar (bash script to get the calculated OSZICAR_0_0_C files after VASP calculation is finished)

The generated files vasp_mae, vasp_mae_jsub and vasp_mae_0 are interconnected scripts to submit jobs in HPC facilities. One needs only to execute the file vasp mae in order to run all VASP jobs automatically. You can specify some job settings in these scripts by adding more tags in the command line. For instance,

maelas -m -i POSCAR_rlx -k 70 -s1 1 0 0 -s2 0 0 1 -t 48 -c 24 -q qprod -a OPEN-00-00 -f /scratch/example_mag

where -t 48 indicates that the number of maximum CPU hours for the VASP calculation is 48 hours,-c 24 means that the number of cores for the VASP calculation is 24, -q qprod set to production queuethe type of queue in HPC facilities, -a OPEN-00-00 is the project identification number for running jobs in HPC facilities and -f /scratch/example_mag is the folder where you want to run VASP calculations. This procedure might be helpful for high-throughput routines. Note that the user might need to modify vasp_mae_jsub (it is in PBS Pro format) depending on the cluster or local computer batch scheduling. More options can be added in these script files through the terminal command line, to see them just type

maelas -h

Step 3: Generation of VASP files for the calculation of anisotropic magnetostrictive coefficients

Copy the relaxed POSCAR and POTCAR files in the same folder where you want to generate the input files for VASP run. In the terminal, after going to this folder then type

maelas -g -i POSCAR_rlx -k 70 -n 7 -s 0.1

where -g indicates that you want to generate input VASP files for the calculation of anisotropic magnetostrictive coefficients, -i POSCAR_rlx is the initial relaxed POSCAR file (you can name it whatever you want), -k 70 is the length parameter that determines a regular mesh of k-points, -n 7 means that it will generate 7 distorted states for each magentostriction mode and-s 0.1 is the maximum strain applied for distorting the structure. It will generate the following files:

POSCAR_A_B (volume-conserving distorted cell where A=magnetostriction mode, B=1,...,n distorted cell for each magentostriction mode)

INCAR A C (non-collinear calculation where A=magnetostriction mode, C=1,2 is the spin orientation case)

INCAR_std (collinear calculation to generate the WAVECAR and CHGCAR files to run non-collinear calculations)

KPOINTS

vasp_maelas, vasp_jsub and vasp_0 (interconnected bash scripts to run VASP calculations automatically)

vasp_cp_oszicar (bash script to get the calculated OSZICAR_A_B_C files after VASP calculation is finished)

The generated files vasp_maelas, vasp_jsub and vasp_0 are interconnected scripts to submit jobs in HPC facilities, one can specify some job settings in these scripts by adding more tags in the command line. For instance,

maelas -g -i POSCAR_rlx -k 70 -n 7 -s 0.1 -t 48 -c 24 -q qprod -a OPEN-00-00 -f /scratch/example_mag

where -t 48 indicates that the number of maximum CPU hours for the VASP calculation is 48 hours,-c 24 means that the number of cores for the VASP calculation is 24, -q aprod set the type of queue in HPC facilities, -a OPEN-00-00 is the project identification number for running jobs in HPC facilities and -f /scratch/example_mag is the folder where you want to run VASP calculations. This procedure might be helpful for high-throughput routines. Note that the user might need to modify vasp_jsub (it is in PBS Pro format) depending on the cluster or local computer batch scheduling. More options can be added in these script files through the terminal command line, to see them just type

maelas –h

Step 4: Run VASP calculations

For each generated POSCAR_A_B one should run first a collinear calculation using INCAR_std and use the generated WAVECAR and CHGCAR files to run non-collinear calculations for each INCAR_A_C (C=1,2) using the same POSCAR_A_B. This procedure can be automatically done in HPC facilities just by running the generated bash script

./vasp_maelas

This will launch independent jobs for each POSCAR_A_B. Each job will run 3 VASP calculations: a collinear one (VASP executable "vasp_std") to generate WAVECAR and CHGCAR files, and two non-collinear (VASP executable "vasp_ncl") for INCAR_A_1 and INCAR_A_2. The jobs will be executed in subfolders P_A_B inside the folder indicated by tag -f in the step 2. Note that the user might need to modify vasp_jsub depending on the cluster or local computer queuing system.

Once all jobs are finished, then one can easily get calculated non-collinear OSZICAR files (needed in step 4), by running the bash script

./vasp_cp_oszicar

it will copy these OSZICAR files and name them as OSZICAR A B C (C=1,2) in the same folder where this script is executed.

VASP executables:

"vasp_std" is the standard version of vasp without spin-orbit coupling (LNONCOLLINEAR = .FALSE., LSORBIT = .FALSE.)

"vasp_ncl" is for non-collinear calculations for instance to perform fully non-collinear magnetic structure calculations or to include spin-orbit interactions in the calculations (LSORBIT = .TRUE.)

Step 5: Derivation of anisotropic magnetostrictive coefficients and magnetoelastic constants

Finally, to derive the anisotropic magnetostrictive coefficients one needs to have in the same folder the following files:

POSCAR_rlx (the relaxed POSCAR file used as input in step 3)
POSCAR_A_B (distorted POSCAR generated in step 3)
OSZICAR_A_B_C (non-collinear OSZICAR files calculated in step 4 for each POSCAR_A_B and INCAR_A_C)

Next, in the terminal go to this folder a type

maelas -d -i POSCAR_rlx -n 7

where -d indicates that you want to derive the spin-dependent magnetostrictive coefficients from the calculated OSZICAR files, -i POSCAR_rlx is the relaxed POSCAR file used as input in step 3 (you can name it whatever you want) and -n 7 is the number of distorted states for each magentostriction mode used in step 3.

It will derive and print the calculated anisotropic magnetostrictive coefficients in the terminal. If you want to print it in a file (for example, "results.out"), then you can type

maelas -d -i POSCAR_rlx -n 7 > results.out

Additionally, the energy values extracted from OSZICAR_A_B_C files are shown in generated files ene_A_C.dat and fit_ene_A_C.png. The energy difference between the two spin configurations for each magnetostriction mode are shown in Fig. dE_A.png. If the elastic tensor is provided as input, then MAELAS can also calculate the magnetoelastic constants. To do so, one needs to add tags -b and -e with the name of the file containing the elastic tensor with the same format and units (GPa) as it is written by AELAS code (file ELADAT). Hence, you could type

maelas -d -i POSCAR rlx -n 7 -b -e ELADAT

where ELADAT is the name of the file (it could be whatever name you want) with the elastic tensor data.

Elastic tensor: Format of the 262.03 186.20 186.20 0.00 elastic tensor file 186.20 262.03 186.20 0.00 186.20 186.20 262.03 0.00 0.00 0.00 0.00 116.63 0.00 0.00 0.00 0.00 116.63 0.00 0.00 0.00 0.00 116.63 diffist of arguments in MALLAS code

User can see all possible optional arguments by typing

maelas -h

The optional arguments are the following:

```
-h, --help
            Show this help message and exit
-i POS
            Name of the initial non-distorted POSCAR file (default: POSCAR)
            Number of distorted states for each magnetostriction mode (default: 7)
-n NDIST
-s STRAIN
            Maximum value of the parameter epsilon for the strain tensor to generate the distorted POSCAR files (default: 0.01)
-k KP
            VASP automatic k-point mesh generation to create the KPOINTS file (default: 60)
            Generation of required VASP files for the calculation of magnetostrictive coefficients.
-g
-d
            Derivation of magnetostrictive coefficients from the energy written in the OSZICAR files.
            Generation of required VASP files for the cell relaxation
-r
            Generation of required VASP files to test MAE
-m
-s1 s1x s1y s1z First spin direction to calculate MAE
-s2 s2x s2y s2z Second spin direction to calculate MAE
-b
            Calculation of the magnetoelastic constants from the calculated magnetostrictive coefficients and provided elastic tensor.
            File with the elastic tensor data in the same format and units (GPa) as it is written by ELAS code (file ELADAT).
-e ELAS
-sp SYMPRE
               Tolerance for symmetry finding (default: 0.01)
               Angle tolerance for symmetry finding (default: 5.0)
-sa SYMANG
-sg SG0
            Space group number 1-230. If it is equal to 0, then it will be determined by a symmetry analysis (default: 0)
-c CORE
            Number of cores for the VASP calculation (default: 24)
            Number of maximum CPU hours for the VASP calculation (default: 48)
-t TIME
-f VASP FOLD Folder where you will run VASP calculations (default: /scratch)
-mp MPI
             Command for mpi run of VASP (default: mpiexec.hydra)
            Project id for running jobs in HPC facilities (default: OPEN-X-X)
-a P ID
```

-l LOAD MODULE Module of VASP that should be loaded (default: VASP/5.4.4-intel-2017c-mkl=cluster)

-q QUEUE Type of gueue to be used for VASP calculations in HPC facilities (default: gprod)

HOW TO USE MAFLAS CODE

Summary: In a nutshell

Step 1: Cell relaxation

maelas -r -i POSCARO -k 40

qsub vasp_jsub_rlx

Step 2: Test MAE

maelas -m -i POSCAR_rlx -k 70 -s1 1 0 0 -s2 0 0 1

./vasp_mae

./vasp_mae_cp_oszicar

Step 3: Generate VASP inputs for calculation of magnetostrictive coefficients

maelas -g -i POSCAR_rlx -k 70 -n 7 -s 0.1

Step 4: Run VASP calculations

./vasp_maelas

./vasp_cp_oszicar


Step 5: Derivation of anisotropic magnetostrictive coefficients

maelas -d -i POSCAR rlx -n 7

Step 5: Derivation of anisotropic magnetostrictive coefficients and magnetoelastic constants

maelas -d -i POSCAR_rlx -n 7 -b -e ELADAT

See all optional arguments: maelas -h




Using MAELAS with other DFT codes instead of VASP

MAELAS has been designed to read and write files for VASP code automatically. However, it is possible to use MAELAS with other DFT codes instead of VASP, after file conversion to VASP format files. Although, this process might require some extra work for the user. Namely, converting initial and distorted POSCAR files into the other DFT code format, reading the spin direction of each state from INCAR_A_C files (variable SAXIS) and write the calculated energies in a OSZICAR-like file (called OSZICAR_A_B_C) on the penultimate line and third column with same format as in VASP (this is the place where MAELAS reads the energy value of each OSZICAR_A_B_C file). For instance, in the following OSZICAR-like file, one should write the calculated energy value at "**Energy_DFT_code**":

	N	E	dE	d eps	ncg	rms	rms(c)	
DAV:	1	-0.219086777516E+02	-0.21909E+02	0. J9185E+02**	****	0.709E+00		
DAV:	2	-0.219092777733E+02	-0.60002E-03	-0.60002E-03**	****	0.452E-01		
DAV:	3	-0.219092846144E+02	-0.684115-05	-0.68405E-05**	****	0.485E-02		
DAV:	4	-0.219092847670E+02	-0.15258E-06	-0.15274E-06**	****	0.641E-03		
DAV:	5	-0.219092847725E+02	0.55161E-08	-0.52995E-08**	****	0.117E-03		
DAV:	6	**Energy DFT code**	-0.19827E-09	-0.11530E-0986	58760	0.143E-04		
1	F=	21909285E+02 E0=219	09330E+02 d E =	0.135168E-03 r	nag=	0.0000	0.0000	2.5077

Interface between LAMMPS and MAELAS



See folder: Examples/LAMMPS/MAELAS


More details can be found in reference: P. Nieves et al. "Spin-lattice model for cubic crystals" arXiv (2020)

Crystal systems supported by MAELAS v1.0

Table 1: Number of independent second-order elastic constants of each crystal system. Number of independent magnetoelastic and magnetostriction coefficients up to second-order of the direction cosine polynomial in the first-order magnetoelastic energy. In the last column we specify which crystal systems are supported by the current version of MAELAS.


Crystal system	Point groups	Space groups	Elastic constants (c_{ij})	Magnetoelastic constants (b)	Magnetostriction coefficients (λ)	MAELAS
Triclinic	$1, \overline{1}$	1-2	21	36	36	No
Monoclinic	2, m, 2/m	3 - 15	13	20	20	No
Orthorhombic	222,2mm,mmm	16 - 74	9	12	12	Yes
Tetragonal (II)	$4, \bar{4}, 4/m$	75 - 88	7	10	10	No
Tetragonal (I)	$4mm, 422, \bar{4}2m, 4/mmm$	89 - 142	6	7	7	Yes
Trigonal (II)	$3,\bar{3}$	143 - 148	7	12	12	No
Trigonal (I)	$32, 3m, \bar{3}m$	149 - 167	6	8	8	Yes
Hexagonal(II)	$6,\bar{6},6/m$	168 - 176	5	8	8	No
Hexagonal (I)	$6mm, 622, \bar{6}2m, 6/mmm$	177 - 194	5	6	6	Yes
Cubic (II)	$23, m\bar{3}$	195 - 206	3	4	4	No
Cubic (I)	$432,\bar{4}3m,m\bar{3}m$	207 - 230	3	3	3	Yes

The crystal systems not supported by MAELAS might be included in the new versions of the code



Methodology


$$\begin{split} \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}^i}^{\pmb{\alpha}_1^i} - \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}^i}^{\pmb{\alpha}_2^i} &= \eta^i \lambda^i \\ \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}^i}^{\pmb{\alpha}_1^i} - \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}^i}^{\pmb{\alpha}_2^i} &= \frac{l_1 - l_0}{l_0} - \frac{l_2 - l_0}{l_0} = \frac{2(l_1 - l_2)}{(l_1 + l_2) \left[1 - \frac{l_1 + l_2 - 2l_0}{l_1 + l_2}\right]} \\ &= \frac{2(l_1 - l_2)}{l_1 + l_2} \left[1 + \frac{l_1 + l_2 - 2l_0}{l_1 + l_2} + \dots \right] \approx \frac{2(l_1 - l_2)}{l_1 + l_2} \end{split}$$



Fitting to a quadratic function

$$E(l) \Big|_{\beta}^{\alpha_j} = A_j l^2 + B_j l + C_j, \quad j = 1, 2$$

Minimum: $l_{1(2)} = -B_{1(2)}/(2A_{1(2)})$



Cell length along $\beta = \left[\frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}\right]$

Table 2: Implemented distortion (β) and spin directions (α_1 , α_2) in MAELAS to calculate the anisotropic magnetostriction coefficients according to Eq.30. The second column presents the equation of the relative length change that we used in Eq.30 for each crystal system. In the last column we show the value of parameter η that is defined in Eq.30. The symbols a, b, c correspond to the lattice parameters of the relaxed (not distorted) unit cell.

Crystal system	$\frac{\Delta l}{l_0}$	Magnetostriction coefficient	β	α_1	α_2	η η
Cubic (I)	Eq.10	λ_{001}	(0,0,1)	(0,0,1)	(1,0,0)	3 2 3
		λ_{111}	$\left(\frac{1}{\sqrt{3}},\frac{1}{\sqrt{3}},\frac{1}{\sqrt{3}}\right)$	$\left(\frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}\right)$	$\left(\frac{1}{\sqrt{2}},0,\frac{-1}{\sqrt{2}}\right)$	$\frac{3}{2}$
Hexagonal (I)	Eq.16	$\lambda^{\alpha 1,2}$	(1,0,0)	$\left(\frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}\right)$	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	$\frac{1}{3}$
		$\lambda^{\alpha 2,2}$	(0,0,1)	(0,0,1)	(1,0,0)	1
		$\lambda^{\gamma,2}$	(1,0,0)	(1,0,0)	(0,1,0)	1
		$\lambda^{\epsilon,2}$	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$\left(\frac{1}{\sqrt{2}}, 0, \frac{1}{\sqrt{2}}\right)$	$\left(\frac{-1}{\sqrt{2}},0,\frac{1}{\sqrt{2}}\right)$	$\frac{2ac}{a^2+c^2}$
Trigonal (I)	Eq.20	$\lambda^{\alpha 1,2}$	(1,0,0)	(0,0,1)	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	1
		$\lambda^{\alpha 2,2}$	(0,0,1)	(0,0,1)	(1,0,0)	1
		$\lambda^{\gamma,1}$	(1,0,0)	(1,0,0)	(0,1,0)	1
		$\lambda^{\gamma,2}$	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$\left(\frac{1}{\sqrt{2}}, 0, \frac{1}{\sqrt{2}}\right)$	$\left(\frac{1}{\sqrt{2}},0,\frac{-1}{\sqrt{2}}\right)$	$\frac{ac}{a^2+c^2}$
		λ_{12}	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$(0, \frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}})$	$\left(0, \frac{1}{\sqrt{2}}, \frac{-1}{\sqrt{2}}\right)$	$\frac{a^2}{2(a^2+c^2)}$
		λ_{21}	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	$\left(\frac{1}{\sqrt{2}}, \frac{-1}{\sqrt{2}}, 0\right)$	$\frac{ac}{a^2+c^2}$
Tetragonal (I)	Eq.24	$\lambda^{\alpha 1,2}$	(1,0,0)	$\left(\frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}\right)$	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	1/3
		$\lambda^{\alpha 2,2}$	(0,0,1)	(0,0,1)	(1,0,0)	1
		$\lambda^{\gamma,2}$	(1,0,0)	(1,0,0)	(0,1,0)	1
		$\lambda^{\epsilon,2}$	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$\left(\frac{1}{\sqrt{2}}, 0, \frac{1}{\sqrt{2}}\right)$	$\left(\frac{-1}{\sqrt{2}}, 0, \frac{1}{\sqrt{2}}\right)$	$\frac{2ac}{a^2+c^2}$
		$\lambda^{\delta,2}$	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	$\left(\frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	$\left(\frac{-1}{\sqrt{2}}, \frac{1}{\sqrt{2}}, 0\right)$	1
Orthorhombic	Eq.27	λ_1	(1,0,0)	(1,0,0)	(0,0,1)	1
		λ_2	(1,0,0)	(0,1,0)	(0,0,1)	1
		λ_3	(0,1,0)	(1,0,0)	(0,0,1)	1
		λ4	(0,1,0)	(0,1,0)	(0,0,1)	1
		λ_5 λ_6	(0,0,1) (0,0,1)	(1,0,0) (0,1,0)	(0,0,1) (0,0,1)	1
			(a,b,0)	(1 1 0)	(0,0,1) (0,0,1)	$(a-b)(a[\lambda_1+\lambda_2]-b[\lambda_3+\lambda_4])+4ab\lambda_7$
		λ_7	$\sqrt{a^2+b^2}$	$\sqrt{\sqrt{2}}, \sqrt{2}, \sqrt{2}$,	$2(a^2+b^2)\lambda_7$ $(a-c)(a\lambda_1-c\lambda_5)+4ac\lambda_8$
		λ_8	$\frac{(a,0,c)}{\sqrt{a^2+c^2}}$	$\left(\frac{1}{\sqrt{2}},0,\frac{1}{\sqrt{2}}\right)$	(0,0,1)	$2(a^2+c^2)\lambda_8$
		λ_9	$\frac{(0,b,c)}{\sqrt{b^2+c^2}}$	$(0, \frac{1}{\sqrt{2}}, \frac{1}{\sqrt{2}})$	(0,0,1)	$\frac{(b-c)(b\lambda_4-c\lambda_6)+4bc\lambda_9}{2(b^2+c^2)\lambda_9}$

CUBIC (I)

SG 207-230

Cubic (I)

Workflow

Elastic energy

$$E_{el}^{cub} = \frac{c_{11}}{2} (\varepsilon_{xx}^2 + \varepsilon_{yy}^2 + \varepsilon_{zz}^2) + c_{12} (\varepsilon_{xx} \varepsilon_{yy} + \varepsilon_{xx} \varepsilon_{zz} + \varepsilon_{yy} \varepsilon_{zz}) + \frac{c_{44}}{2} (\varepsilon_{xy}^2 + \varepsilon_{yz}^2 + \varepsilon_{xz}^2)$$











 $\lambda^{\alpha} = \frac{-b_0 - \frac{1}{3}b_1}{c_{11} + 2c_{12}}$

 $+3\lambda_{111}(\alpha_x\alpha_y\beta_x\beta_y+\alpha_y\alpha_z\beta_y\beta_z+\alpha_x\alpha_z\beta_x\beta_z)$

 $\frac{\Delta l}{l_0} \bigg|_{\boldsymbol{\beta}}^{\boldsymbol{\alpha}} = \lambda^{\alpha} + \frac{3}{2} \lambda_{001} \left(\alpha_x^2 \beta_x^2 + \alpha_y^2 \beta_y^2 + \alpha_z^2 \beta_z^2 - \frac{1}{3} \right)$

$$\lambda_{001} = \frac{-2b_1}{3(c_{11} - c_{12})}$$

$$\lambda_{111} = \frac{-b}{3c_4}$$

Magnetoelastic energy



$$E_{me}^{cub(I)} = b_0(\varepsilon_{xx} + \varepsilon_{yy} + \varepsilon_{zz}) + b_1(\alpha_x^2 \varepsilon_{xx} + \alpha_y^2 \varepsilon_{yy} + \alpha_z^2 \varepsilon_{zz}) + b_2(\alpha_x \alpha_y \varepsilon_{xy} + \alpha_x \alpha_z \varepsilon_{xz} + \alpha_y \alpha_z \varepsilon_{yz})$$

$$\frac{\Delta l}{l_0} \Big|_{\boldsymbol{\beta}}^{\boldsymbol{\alpha}} = \lambda^{\alpha} + \frac{3}{2} \lambda_{001} \left(\alpha_x^2 \beta_x^2 + \alpha_y^2 \beta_y^2 + \alpha_z^2 \beta_z^2 - \frac{1}{3} \right) + 3 \lambda_{111} (\alpha_x \alpha_y \beta_x \beta_y + \alpha_y \alpha_z \beta_y \beta_z + \alpha_x \alpha_z \beta_x \beta_z)$$

space group: 201-230

POSCAR 1 X (N POSCAR: Distortion along [0,0,1])

INCAR std (1 INCAR: collinear w/o SOC)

INCAR 1 1 (1 INCAR: non-collinear with SOC, SPIN=[0,0,1])

INCAR 1 2 (1 INCAR: non-collinear with SOC, SPIN=[1,0,0])

OSZICAR_1_X_1 OSZICAR_1_X_2

Cubic (I)

 λ_{111}

 λ_{001}

POSCAR 2 X (N POSCAR: Distortion along [1,1,1])

INCAR_std (1 INCAR: collinear w/o SOC)

INCAR 2 1 (1 INCAR: non-collinear with SOC, SPIN=[1,1,1])


INCAR 2 2 (1 INCAR: non-collinear with SOC, SPIN=[1,0,-1])

OSZICAR_2_X_1

OSZICAR_2_X_2

POSCAR

Symmetry analysis




$$\underline{\boldsymbol{\varepsilon}}\Big|_{\boldsymbol{\beta} = \left(\frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}, \frac{1}{\sqrt{3}}\right)}^{\lambda_{111}} = \zeta \begin{pmatrix} 1 & \frac{\varepsilon}{2} & \frac{\varepsilon}{2} \\ \frac{\varepsilon}{2} & 1 & \frac{\varepsilon}{2} \\ \frac{\varepsilon}{2} & \frac{\varepsilon}{2} & 1 \end{pmatrix}$$

Fitting: $E(l) = Al^2 + Bl + C$

cell length along B

Minimum: $l_{1(2)} = -B_{1(2)}/(2A_{1(2)})$



Volume-conserving transformations (determinant of transformation matrix = 1)

$$\underline{\boldsymbol{\varepsilon}}\Big|_{\boldsymbol{\beta}=(0,0,1)}^{\lambda_{001}} = \begin{pmatrix} \frac{1}{\sqrt{1+\epsilon}} & 0 & 0\\ 0 & \frac{1}{\sqrt{1+\epsilon}} & 0\\ 0 & 0 & 1+\epsilon \end{pmatrix}, \quad \underline{\boldsymbol{\varepsilon}}\Big|_{\boldsymbol{\beta}=\left(\frac{1}{\sqrt{3}},\frac{1}{\sqrt{3}},\frac{1}{\sqrt{3}}\right)}^{\lambda_{111}} = \zeta\begin{pmatrix} 1 & \frac{\epsilon}{2} & \frac{\epsilon}{2}\\ \frac{\epsilon}{2} & 1 & \frac{\epsilon}{2}\\ \frac{\epsilon}{2} & \frac{\epsilon}{2} & 1 \end{pmatrix}$$

The maximum value of ε is set with tag-s


HEXAGONAL (I)

SG 177-194

Workflow

Elastic energy

$$E_{el}^{hex} = \frac{1}{2}c_{11}(\varepsilon_{xx}^2 + \varepsilon_{yy}^2) + c_{12}\varepsilon_{xx}\varepsilon_{yy} + c_{13}(\varepsilon_{xx} + \varepsilon_{yy})\varepsilon_{zz} + \frac{1}{2}c_{33}\varepsilon_{zz}^2 + \frac{1}{2}c_{44}(\varepsilon_{yz}^2 + \varepsilon_{xz}^2) + \frac{1}{4}(c_{11} - c_{12})\varepsilon_{xy}^2.$$



Magnetoelastic energy

$$\begin{split} E_{me}^{hex(I)} &= b_{11}(\varepsilon_{xx} + \varepsilon_{yy}) + b_{12}\varepsilon_{zz} + b_{21}\left(\alpha_z^2 - \frac{1}{3}\right)(\varepsilon_{xx} + \varepsilon_{yy}) + b_{22}\left(\alpha_z^2 - \frac{1}{3}\right)\varepsilon_{zz} \\ &+ \frac{1}{2}b_3[(\alpha_x^2 - \alpha_y^2)(\varepsilon_{xx} - \varepsilon_{yy}) + 2\alpha_x\alpha_y\varepsilon_{xy}] + b_4(\alpha_x\alpha_z\varepsilon_{xz} + \alpha_y\alpha_z\varepsilon_{yz}). \end{split}$$

$$\begin{split} \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}}^{\pmb{\alpha}} &= \lambda^{\alpha 1,0} (\beta_x^2 + \beta_y^2) + \lambda^{\alpha 2,0} \beta_z^2 + \lambda^{\alpha 1,2} \left(\alpha_z^2 - \frac{1}{3} \right) (\beta_x^2 + \beta_y^2) \\ &+ \lambda^{\alpha 2,2} \left(\alpha_z^2 - \frac{1}{3} \right) \beta_z^2 + \lambda^{\gamma,2} \left[\frac{1}{2} (\alpha_x^2 - \alpha_y^2) (\beta_x^2 - \beta_y^2) + 2\alpha_x \alpha_y \beta_x \beta_y \right] \\ &+ 2\lambda^{\varepsilon,2} (\alpha_x \alpha_z \beta_x \beta_z + \alpha_y \alpha_z \beta_y \beta_z), \end{split}$$

$$\lambda^{\alpha 1,0} = \frac{b_{11}c_{33} + b_{12}c_{13}}{c_{33}(c_{11} + c_{12}) - 2c_{13}^{2}},$$


$$\lambda^{\alpha 2,0} = \frac{2b_{11}c_{13} - b_{12}(c_{11} + c_{12})}{c_{33}(c_{11} + c_{12}) - 2c_{13}^{2}},$$

$$\lambda^{\alpha 1,2} = \frac{-b_{21}c_{33} + b_{22}c_{13}}{c_{33}(c_{11} + c_{12}) - 2c_{13}^{2}},$$


$$\lambda^{\alpha 2,2} = \frac{2b_{21}c_{13} - b_{22}(c_{11} + c_{12})}{c_{33}(c_{11} + c_{12}) - 2c_{13}^{2}},$$

$$\lambda^{\gamma,2} = \frac{-b_{3}}{c_{11} - c_{12}},$$

$$\lambda^{\epsilon,2} = \frac{-b_{4}}{2c_{44}}.$$



Distorted states




$$|\boldsymbol{\alpha}| = 1, |\boldsymbol{\beta}| = 1$$


strain along x-axis: $\beta = (1,0,0)$


$$\underline{\boldsymbol{\varepsilon}}\Big|_{\boldsymbol{\beta}=(1,0,0)}^{\boldsymbol{\lambda}^{\alpha 1,2}} = \begin{pmatrix} 1+\boldsymbol{\varepsilon} & 0 & 0\\ 0 & \frac{1}{\sqrt{1+\boldsymbol{\varepsilon}}} & 0\\ 0 & 0 & \frac{1}{\sqrt{1+\boldsymbol{\varepsilon}}} \end{pmatrix}$$


$$\lambda^{\alpha 1,2}$$



volume-conserving








$$A = \begin{pmatrix} a1 & 0 & 0 \\ b1 & b2 & 0 \\ 0 & 0 & c3 \end{pmatrix}$$


Distorted states



$$|\boldsymbol{\alpha}| = 1, |\boldsymbol{\beta}| = 1$$


strain along z-axis: $\beta = (0.0.1)$


$$\mathbf{\underline{\varepsilon}}\Big|_{\mathbf{\beta}=(0,0,1)}^{\mathbf{\lambda}^{\alpha2,2}} = \begin{pmatrix} \frac{1}{\sqrt{1+\epsilon}} & 0 & 0\\ 0 & \frac{1}{\sqrt{1+\epsilon}} & 0\\ 0 & 0 & 1+\epsilon \end{pmatrix}$$




volume-conserving

 $\lambda^{\alpha 2,2}$






a



$$A = \begin{pmatrix} a1 & 0 & 0 \\ b1 & b2 & 0 \\ 0 & 0 & c3 \end{pmatrix}$$

Distorted states





$$|\boldsymbol{\alpha}| = 1, |\boldsymbol{\beta}| = 1$$


$$\mathbf{\underline{\varepsilon}}\Big|_{\mathbf{\beta}=(1,0,0)}^{\lambda^{\gamma,2}} = \begin{pmatrix} 1+\epsilon & 0 & 0\\ 0 & \frac{1}{\sqrt{1+\epsilon}} & 0\\ 0 & 0 & \frac{1}{\sqrt{1+\epsilon}} \end{pmatrix}$$

volume-conserving

$$\lambda^{\gamma,2}$$








 $A = \begin{pmatrix} A & A \\ A & A \end{pmatrix}$


Distorted states



$$|\boldsymbol{\alpha}| = 1, |\boldsymbol{\beta}| = 1$$

shear along xz: $\beta = \left(\frac{1}{\sqrt{2}}, 0, \frac{1}{\sqrt{2}}\right)$

a and c are the lattice parameters of the relaxed (not distorted) unit cell.







$$\omega = \sqrt[3]{4/(4-\epsilon^2)}$$

volume-conserving


$$\mathsf{p} - \frac{}{|a+c|} - \frac{}{|a'+c'|}$$









S=(1,0,1)





Relation between different notations



Clark

 $\lambda_{11}^{\alpha} = 2\lambda_1^{\alpha,0} + \lambda_2^{\alpha,0} + 2\lambda_1^{\alpha,2} + \lambda_2^{\alpha,2}$ $(\sqrt{3}/2)\lambda_{12}^{\alpha}=2\lambda_{1}^{\alpha,2}+\lambda_{2}^{\alpha,2}$ $2\lambda_{21}^{\alpha} = -\lambda_1^{\alpha,0} + \lambda_2^{\alpha,0}$ $\sqrt{3}\lambda_{22}^{\alpha} = -\lambda_1^{\alpha,2} + \lambda_2^{\alpha,2}$. $\lambda \gamma = \lambda \gamma^2$

The calculated magnetostrictive coefficients are written in Clark, Mason, Birss and Callen notation in MAELAS code

MAELAS notation

TRIGONAL (I)


SG 149-167

Trigonal (I)

Workflow

Elastic energy


$$\begin{split} E_{el}^{trig(I)} &= \frac{1}{2}c_{11}(\varepsilon_{xx}^2 + \varepsilon_{yy}^2) + c_{12}\varepsilon_{xx}\varepsilon_{yy} + c_{13}(\varepsilon_{xx} + \varepsilon_{yy})\varepsilon_{zz} + \frac{1}{2}c_{33}\varepsilon_{zz}^2 \\ &\quad + \frac{1}{2}c_{44}(\varepsilon_{xz}^2 + \varepsilon_{yz}^2) + \frac{1}{4}(c_{11} - c_{12})\varepsilon_{xy}^2 + c_{14}(\varepsilon_{xy}\varepsilon_{xz} + \varepsilon_{xx}\varepsilon_{yz} - \varepsilon_{yy}\varepsilon_{yz}) \end{split}$$



Magnetoelastic energy

$$\begin{split} E_{me}^{trig(I)} &= b_{11}(\varepsilon_{xx} + \varepsilon_{yy}) + b_{12}\varepsilon_{zz} + b_{21}\left(\alpha_z^2 - \frac{1}{3}\right)(\varepsilon_{xx} + \varepsilon_{yy}) + b_{22}\left(\alpha_z^2 - \frac{1}{3}\right)\varepsilon_{zz} \\ &+ \frac{1}{2}b_3[(\alpha_x^2 - \alpha_y^2)(\varepsilon_{xx} - \varepsilon_{yy}) + 2\alpha_x\alpha_y] + b_4(\alpha_x\alpha_z\varepsilon_{xz} + \alpha_y\alpha_z\varepsilon_{yz}) \\ &+ b_{14}\left[\frac{1}{2}(\alpha_x^2 - \alpha_y^2)\varepsilon_{yz} + \alpha_x\alpha_y\varepsilon_{xz}\right] + b_{34}\left[\frac{1}{2}\alpha_y\alpha_z(\varepsilon_{xx} - \varepsilon_{yy}) + \alpha_x\alpha_z\varepsilon_{xy}\right]. \end{split}$$

$$\begin{split} \frac{\Delta l}{l_0} \Bigg|_{\pmb{\beta}}^{\pmb{\alpha}} &= \lambda^{\alpha 1,0} (\beta_x^2 + \beta_y^2) + \lambda^{\alpha 2,0} \beta_z^2 + \lambda^{\alpha 1,2} \left(\alpha_z^2 - \frac{1}{3}\right) (\beta_x^2 + \beta_y^2) \\ &+ \lambda^{\alpha 2,2} \left(\alpha_z^2 - \frac{1}{3}\right) \beta_z^2 + \lambda^{\gamma,1} \left[\frac{1}{2} (\alpha_x^2 - \alpha_y^2) (\beta_x^2 - \beta_y^2) + \alpha_x \alpha_y \beta_x \beta_y \right] \\ &+ \lambda^{\gamma,2} (\alpha_x \alpha_z \beta_x \beta_z + \alpha_y \alpha_z \beta_y \beta_z) + \lambda_{12} \left[\frac{1}{2} \alpha_y \alpha_z (\beta_x^2 - \beta_y^2) + \alpha_x \alpha_z \beta_x \beta_y \right] \\ &+ \lambda_{21} \left[\frac{1}{2} (\alpha_x^2 - \alpha_y^2) \beta_y \beta_z + \alpha_x \alpha_y \beta_x \beta_z \right], \\ \lambda^{\alpha 1,0} &= \frac{b_{11} c_{13} + b_{12} c_{13}}{c_{33} (c_{11} + c_{12}) - 2c_{13}^2}, \\ \lambda^{\alpha 2,0} &= \frac{2b_{11} c_{13} - b_{12} (c_{11} + c_{12})}{c_{33} (c_{11} + c_{12}) - 2c_{13}^2}, \\ \lambda^{\alpha 1,2} &= \frac{-b_{21} c_{33} + b_{22} c_{13}}{c_{33} (c_{11} + c_{12}) - 2c_{13}^2}, \\ \lambda^{\alpha 2,2} &= \frac{2b_{21} c_{13} - b_{22} (c_{11} + c_{12})}{c_{33} (c_{11} + c_{12}) - 2c_{13}^2}, \\ \lambda^{\gamma,1} &= \frac{c_{14} b_{14} - c_{44} b_3}{\frac{1}{2} c_{44} (c_{11} - c_{12}) - c_{14}^2}, \\ \lambda^{\gamma,2} &= \frac{\frac{1}{2} b_4 (c_{11} - c_{12}) - c_{14}^2}{\frac{1}{2} c_{44} (c_{11} - c_{12}) - c_{14}^2}, \\ \lambda_{12} &= \frac{c_{14} b_4 - c_{44} b_{34}}{\frac{1}{2} c_{44} (c_{11} - c_{12}) - c_{14}^2}, \\ \lambda_{21} &= \frac{\frac{1}{2} b_{14} (c_{11} - c_{12}) - b_{3} c_{14}}{\frac{1}{2} c_{44} (c_{11} - c_{12}) - c_{14}^2}. \end{split}$$




TETRAGONAL (I)

SG 89-142

Tetragonal (I)

Elastic energy

$$\begin{split} E_{el}^{tet} &= \frac{1}{2} c_{11} (\varepsilon_{xx}^2 + \varepsilon_{yy}^2) + c_{12} \varepsilon_{xx} \varepsilon_{yy} + c_{13} (\varepsilon_{xx} + \varepsilon_{yy}) \varepsilon_{zz} + \frac{1}{2} c_{33} \varepsilon_{zz}^2 \\ &+ \frac{1}{2} c_{44} (\varepsilon_{xz}^2 + \varepsilon_{yz}^2) + \frac{1}{2} c_{66} \varepsilon_{xy}^2. \end{split}$$



Magnetoelastic energy


$$\begin{split} E_{\textit{me}}^{\textit{tet}(I)} &= b_{11}(\varepsilon_{\textit{xx}} + \varepsilon_{\textit{yy}}) + b_{12}\varepsilon_{\textit{zz}} + b_{21}\left(\alpha_z^2 - \frac{1}{3}\right)(\varepsilon_{\textit{xx}} + \varepsilon_{\textit{yy}}) + b_{22}\left(\alpha_z^2 - \frac{1}{3}\right)\varepsilon_{\textit{zz}} \\ &+ \frac{1}{2}b_3(\alpha_x^2 - \alpha_y^2)(\varepsilon_{\textit{xx}} - \varepsilon_{\textit{yy}}) + b_3'\alpha_x\alpha_y\varepsilon_{\textit{xy}} + b_4(\alpha_x\alpha_z\varepsilon_{\textit{xz}} + \alpha_y\alpha_z\varepsilon_{\textit{yz}}). \end{split}$$

$$\frac{\partial (E_{el} + E_{me})}{\partial \varepsilon_{ij}} = 0$$

$$\varepsilon_{ij}^{eq}(\mathbf{\alpha})$$

$$\frac{\Delta l}{l_0} \Big|_{\mathbf{\beta}}^{\mathbf{\alpha}} = \sum_{i,j=x,y,z} \varepsilon_{ij}^{eq}(\mathbf{\alpha}) \beta_i \beta_j$$


$$\begin{split} \frac{\Delta l}{l_0} \bigg|_{\pmb{\beta}}^{\pmb{\alpha}} &= \lambda^{\alpha 1,0} (\beta_x^2 + \beta_y^2) + \lambda^{\alpha 2,0} \beta_z^2 + \lambda^{\alpha 1,2} \left(\alpha_z^2 - \frac{1}{3}\right) (\beta_x^2 + \beta_y^2) \\ &+ \lambda^{\alpha 2,2} \left(\alpha_z^2 - \frac{1}{3}\right) \beta_z^2 + \frac{1}{2} \lambda^{\gamma,2} (\alpha_x^2 - \alpha_y^2) (\beta_x^2 - \beta_y^2) + 2 \lambda^{\delta,2} \alpha_x \alpha_y \beta_x \beta_y \\ &+ 2 \lambda^{\epsilon,2} (\alpha_x \alpha_z \beta_x \beta_z + \alpha_y \alpha_z \beta_y \beta_z), \\ \lambda^{\alpha 1,0} &= \frac{b_{11} c_{33} + b_{12} c_{13}}{c_{33} (c_{11} + c_{12}) - 2 c_{13}^2}, \\ \lambda^{\alpha 2,0} &= \frac{2b_{11} c_{13} - b_{12} (c_{11} + c_{12})}{c_{33} (c_{11} + c_{12}) - 2 c_{13}^2}, \\ \lambda^{\alpha 1,2} &= \frac{-b_{21} c_{33} + b_{22} c_{13}}{c_{33} (c_{11} + c_{12}) - 2 c_{13}^2}, \\ \lambda^{\alpha 2,2} &= \frac{2b_{21} c_{13} - b_{22} (c_{11} + c_{12})}{c_{33} (c_{11} + c_{12}) - 2 c_{13}^2}, \\ \lambda^{\gamma,2} &= \frac{-b_3}{c_{11} - c_{12}}, \\ \lambda^{\delta,2} &= \frac{-b_3}{2c_{66}}, \\ \lambda^{\epsilon,2} &= \frac{-b_4}{2c_{44}}. \end{split}$$



Space group: 75-142

Tetragonal

 $\lambda^{\delta,2}$



same files as the hexagonal case

POSCAR analysis a1 = b2

Symmetry

INCAR_5_1 (1 INCAR: non-collinear with SOC, SPIN=[1,1,0]) INCAR_5_2 (1 INCAR: non-collinear with SOC, SPIN=[-1,1,0])

Fitting: $E(l) = Al^2 + Bl + C$ Minimum: $l_{1(2)} = -B_{1(2)}/(2A_{1(2)})$


OSZICAR_5_X_1

Relation between different notations

Tetragonal (I)

Cullen

$$\begin{split} \frac{\Delta l}{l_0} \Bigg|_{\boldsymbol{\beta}}^{\boldsymbol{\alpha}} &= \lambda^{\alpha 1,0} (\beta_x^2 + \beta_y^2) + \lambda^{\alpha 2,0} \beta_z^2 + \lambda^{\alpha 1,2} \left(\alpha_z^2 - \frac{1}{3} \right) (\beta_x^2 + \beta_y^2) \\ &+ \lambda^{\alpha 2,2} \left(\alpha_z^2 - \frac{1}{3} \right) \beta_z^2 + \frac{1}{2} \lambda^{\gamma,2} (\alpha_x^2 - \alpha_y^2) (\beta_x^2 - \beta_y^2) + 2 \lambda^{\delta,2} \alpha_x \alpha_y \beta_x \beta_y \\ &+ 2 \lambda^{\epsilon,2} (\alpha_x \alpha_z \beta_x \beta_z + \alpha_y \alpha_z \beta_y \beta_z), \end{split}$$



$$\begin{split} \frac{\Delta l}{l_0} \Bigg|_{\pmb{\beta}}^{\pmb{\alpha}} &= \lambda_{Mason}^{\alpha 1,0} (\beta_x^2 + \beta_y^2) + \lambda_{Mason}^{\alpha 2,0} \beta_z^2 + \frac{1}{2} \lambda_1 [(\alpha_x \beta_x - \alpha_y \beta_y)^2 - (\alpha_x \beta_y + \alpha_y \beta_x)^2 \\ &+ (1 - \beta_z^2) (1 - \alpha_z^2) - 2 \alpha_z \beta_z (\alpha_x \beta_x + \alpha_y \beta_y)] + 4 \lambda_2 \alpha_z \beta_z (\alpha_x \beta_x + \alpha_y \beta_y) \\ &+ 4 \lambda_3 \alpha_x \alpha_y \beta_x \beta_y + \lambda_4 [\beta_z^2 (1 - \alpha_z^2) - \alpha_z \beta_z (\alpha_x \beta_x + \alpha_y \beta_y)] \\ &+ \frac{1}{2} \lambda_5 [(\alpha_x \beta_y - \alpha_y \beta_x)^2 - (\alpha_x \beta_x + \alpha_y \beta_y)^2 + (1 - \beta_z^2) (1 - \alpha_z^2)]. \end{split}$$

$$\begin{split} \lambda_{Mason}^{\alpha 1,0} &= \lambda^{\alpha 1,0} + \frac{2}{3} \lambda^{\alpha 1,2} \\ \lambda_{Mason}^{\alpha 2,0} &= \lambda^{\alpha 2,0} + \frac{2}{3} \lambda^{\alpha 2,2} \\ \lambda_{1} &= -\lambda^{\alpha 1,2} + \frac{1}{2} \lambda^{\gamma,2} \\ \lambda_{2} &= \frac{1}{2} \lambda^{\epsilon,2} - \frac{1}{4} \lambda^{\alpha 2,2} - \frac{1}{4} \lambda^{\alpha 1,2} + \frac{1}{8} \lambda^{\gamma,2} \\ \lambda_{3} &= \frac{1}{2} \lambda^{\delta,2} - \lambda^{\alpha 1,2} \\ \lambda_{4} &= -\lambda^{\alpha 2,2} \\ \lambda_{5} &= -\lambda^{\alpha 1,2} - \frac{1}{2} \lambda^{\gamma,2}. \end{split}$$

Workflow

ORTHORHOMBIC


SG 16-74

Orthorhombic

Workflow

Elastic energy

$$\begin{split} E_{el}^{ortho} &= \frac{1}{2} c_{11} \varepsilon_{xx}^2 + \frac{1}{2} c_{22} \varepsilon_{yy}^2 + c_{12} \varepsilon_{xx} \varepsilon_{yy} + c_{13} \varepsilon_{xx} \varepsilon_{zz} + c_{23} \varepsilon_{yy} \varepsilon_{zz} + \frac{1}{2} c_{33} \varepsilon_{zz}^2 \\ &\quad + \frac{1}{2} c_{44} \varepsilon_{yz}^2 + \frac{1}{2} c_{55} \varepsilon_{xz}^2 + \frac{1}{2} c_{66} \varepsilon_{xy}^2. \end{split}$$



Magnetoelastic energy

$$\begin{split} E_{me}^{ortho} &= b_{01}\varepsilon_{xx} + b_{02}\varepsilon_{yy} + b_{03}\varepsilon_{zz} + b_{1}\alpha_{x}^{2}\varepsilon_{xx} + b_{2}\alpha_{y}^{2}\varepsilon_{xx} + b_{3}\alpha_{x}^{2}\varepsilon_{yy} + b_{4}\alpha_{y}^{2}\varepsilon_{yy} \\ &+ b_{5}\alpha_{x}^{2}\varepsilon_{zz} + b_{6}\alpha_{y}^{2}\varepsilon_{zz} + b_{7}\alpha_{x}\alpha_{y}\varepsilon_{xy} + b_{8}\alpha_{x}\alpha_{z}\varepsilon_{xz} + b_{9}\alpha_{y}\alpha_{z}\varepsilon_{yz}, \end{split}$$

$$\begin{split} \frac{\Delta l}{l_0} \bigg|_{\boldsymbol{\beta}}^{\boldsymbol{\alpha}} &= \lambda^{\alpha 1,0} \beta_x^2 + \lambda^{\alpha 2,0} \beta_y^2 + \lambda^{\alpha 3,0} \beta_z^2 + \lambda_1 (\alpha_x^2 \beta_x^2 - \alpha_x \alpha_y \beta_x \beta_y - \alpha_x \alpha_z \beta_x \beta_z) \\ &+ \lambda_2 (\alpha_y^2 \beta_x^2 - \alpha_x \alpha_y \beta_x \beta_y) + \lambda_3 (\alpha_x^2 \beta_y^2 - \alpha_x \alpha_y \beta_x \beta_y) \\ &+ \lambda_4 (\alpha_y^2 \beta_y^2 - \alpha_x \alpha_y \beta_x \beta_y - \alpha_y \alpha_z \beta_y \beta_z) + \lambda_5 (\alpha_x^2 \beta_z^2 - \alpha_x \alpha_z \beta_x \beta_z) \\ &+ \lambda_6 (\alpha_y^2 \beta_z^2 - \alpha_y \alpha_z \beta_y \beta_z) + 4\lambda_7 \alpha_x \alpha_y \beta_x \beta_y + 4\lambda_8 \alpha_x \alpha_z \beta_x \beta_z + 4\lambda_9 \alpha_y \alpha_z \beta_y \beta_z. \end{split}$$

$$b_{01} = -c_{11}\lambda^{\alpha 1,0} - c_{12}\lambda^{\alpha 2,0} - c_{13}\lambda^{\alpha 3,0}$$

$$b_{02} = -c_{12}\lambda^{\alpha 1,0} - c_{22}\lambda^{\alpha 2,0} - c_{23}\lambda^{\alpha 3,0}$$

$$b_{03} = -c_{13}\lambda^{\alpha 1,0} - c_{23}\lambda^{\alpha 2,0} - c_{33}\lambda^{\alpha 3,0}$$

$$b_{1} = -c_{11}\lambda_{1} - c_{12}\lambda_{3} - c_{13}\lambda_{5}$$

$$b_{2} = -c_{11}\lambda_{2} - c_{12}\lambda_{4} - c_{13}\lambda_{6}$$

$$b_{3} = -c_{12}\lambda_{1} - c_{22}\lambda_{3} - c_{23}\lambda_{5}$$

$$b_{4} = -c_{12}\lambda_{2} - c_{22}\lambda_{4} - c_{23}\lambda_{6}$$


$$b_{5} = -c_{13}\lambda_{1} - c_{23}\lambda_{3} - c_{33}\lambda_{5}$$

$$b_{6} = -c_{13}\lambda_{2} - c_{23}\lambda_{4} - c_{33}\lambda_{6}$$

$$b_{7} = c_{66}(\lambda_{1} + \lambda_{2} + \lambda_{3} + \lambda_{4} - 4\lambda_{7})$$

$$b_{8} = c_{55}(\lambda_{1} + \lambda_{5} - 4\lambda_{8})$$

$$b_{9} = c_{44}(\lambda_{4} + \lambda_{6} - 4\lambda_{9}).$$




Cubic systems: Itenerant magnets


R.Q. Wu et al. | Journal of Magnetism and Magnetic Materials 177-181 (1998) 1216-1219


	a (a.u.)	σ	$M_s(\mu_B)$	$M_L(\mu_B)$	λ ₀₀₁ (10 ⁻⁶)
bcc Fe					
LDA	5.20	-0.409	2.05	0.048	52
GGA	5.37	-0.486	2.17	0.045	29
EXP	5.41	-0.368	2.22	0.08	21
fcc Co					
LDA	6.48	-0.374	1.59	0.076	92
GGA	6.67	-0.396	1.66	0.073	56
EXP	6.70		1.72	0.12	79
fee Ni					
LDA	6.46	-0.332	0.62	0.049	-63
GGA	6.64	-0.3376	0.66	0.050	-56
EXP	6.66	-0.376	0.57	0.05	-49

,	R. C. O'Handley,		2 K	Room Temperature			
Modern magnetic materials, Wiley, 2000.		$\lambda_{100}(\lambda^{\gamma,2})$	$\lambda_{111}(\lambda^{\epsilon,2})$	$\lambda_{100}(\lambda^{\gamma,2})$	$\lambda_{111}(\lambda^{\varepsilon,2})$	Polycrystal λ_s	
			3d Metal	s			
1	BCC-Fe	26	-30	21	-21	-7	
]	HCP-Co"	(-150)	(45)	(-140)	(50)	(-62)	
]	FCC-Ni	-60	-35	-46	-24	-34	
]	BCC-FeCo	_	_	140	30		
£	$-Fe_{80}B_{20}$	48 (isotropic)	_	_	_	+32	
	a-Fe ₄₀ Ni ₄₀ B ₂₀	+20	_		_	+14	
	$a-Cos_{80}B_{20}$	-4	_			-4	



Cubic systems: Itenerant magnets






G. Engdahl, Handbook of giant magnetostrictive materials, Academic Press, 1999

Cubic systems: Rare-Earth magnets

M. Gibbs, Modern trends in magnetostriction, Springer, 2001.

C15 cubic Laves phase

	Theory	Experiment
λ ₀₀₁ (GdCo ₂)	-407	-1200
λ_{111} (GdCo ₂)	19	< 10
λ_{001} (SmCo ₂)	-290	
λ ₀₀₁ (ErCo ₂)	-516	-1000
λ_{001} (GdFe ₂)	44	39






Table 16-10. Low-temperature magnetostriction constants for RCo₂ crystals [from Levitin and Markosyan (1990) unless otherwise noted].

C _c (K) ^a
409
256
159
85
36
18

Table 1.6. Magnetostriction of Cubic Laves Phase Compounds with Rare Earths at T=0

Compound	$\lambda_{111}(10^{-6})$	$\lambda_{100}(10^{-6})$	T_c (K
NdAl ₂	_	- 700	61
TbAl ₂	- 3000	_	114
DyAl ₂	-	- 1700	68
TbMn ₂	- 3000		40
TbFe ₂	4000, 4500	_	711
DyFe ₂	_	- 70	635
HoFe ₂		- 750	612
TmFe ₂	-3500, -2600	_	610
TbCo ₂	4400	_	256
DyCo ₂	_	- 2000	159
HoCo ₂	_	- 2200	85
ErCo ₂	- 2500	_	36
TbNi ₂	1500	_	45
DyNi ₂	_	- 1300	30
HoNi ₂	_	- 1000	22

Table 1.7. Magnitudes of Single-Crystal Magnetostriction in Rare Earth-Fe₂ Compounds

Compound	$\frac{3}{2}\lambda_{111} \ (10^{-6})$ (calculated at 0 K)	$\frac{3}{2}\lambda_{111}~(10^{-6})$ (measured at room temperature)	$T_{\rm e}$
SmFe ₂	- 4800	- 3150	676
TbFe ₂	6600	3690	697, 711
DyFe ₂	6300	1890	635
HoFe ₂	2400	288	606
ErFe ₂	- 2250	- 450	590, 597
TmFe ₂	- 5550	-315	560

TABLE 6
Magnetostriction coefficients at zero Kelvin in units of 10⁻³

Hexagonal Rare-Earth

Element	λ ^{α,2}	λ 2,2	λ γ,2	λ ^{ε,2}	$\lambda_{i}^{\alpha,0} - \frac{1}{3}\lambda_{i}^{\alpha,2}$	$\lambda_2^{\alpha,0} - \frac{1}{3}\lambda_2^{\alpha,2}$	λ γ.4
Gadolinium ^{a)}	0.14	-0.13	0.11	0.02	-	-	_
Terbium ^{b)}	-2.6°)	9.0°)	8.7	15.0°)	- 0.8	4.3	-2.1
Dysprosium ^{b)}	_	_	9.4	5.5	- 2.0	7.3	1.5
Holmium ^{b)}	_		2.5°)	***	-3.9	7.1	_
Erbium ^{b)}	-	-	-5.1°	-	+0.3	6.2	-

a) After Mishima et al. (1976).

R. C. O'Handley, Modern magnetic materials, Wiley, 2000.

Oxide magnets

	T = 4	4.2 K	Room Temperature			
	$\lambda_{100}(\lambda^{\gamma,2})$	$\lambda_{111}(\lambda^{\varepsilon,2})$	$\lambda_{100}(\lambda^{\gamma,2})$	$\lambda_{111}(\lambda^{\varepsilon,2})$	Polycrystal λ_s	
		Spinel Ferrit	es		-	
Fe_3O_4	0	50	-15	56	+40	
$MnFe_2O_4^u$	*****	_	(-54)	(10)	_	
CoFe ₂ O ₄	_	_	-670	120	-110	
		Garnets				
YIG	-0.6	-2.5	-1.4	-1.6	-2	

b) After Rhyne (1972).

c) Extrapolated from paramagnetic range using single-ion theory.

MAELAS TESTS

Table 3: Anisotropic magnetostrictive coefficients and MAE calculated using the program MAE-LAS and measured in experiment ($T \approx 0$ K) for a set of magnetic materials. In parenthesis we show the magnetostrictive coefficients with Mason's definitions obtained using the relations given by Eq. A.2.

by Eq. /	1.4.							
Material	Crystal system	DFT method	Magnetostriction coefficient	MAELAS (×10 ⁻⁶)	Expt. (×10 ⁻⁶)	MAE	MAELAS (μeV/atom)	Expt. (µeV/atom)
BCC Fe	Cubic (I) SG 229	GGA	λ ₀₀₁ λ ₁₁₁	23 19	26 ^a -30 ^a	E(110) - E(001) E(111) - E(001)	0.1 0.21	1.0 ^b 1.3 ^b
HCP Co	Hexagonal (I) SG 194	SCAN	$\lambda^{\alpha 1,2} (\lambda_A)$ $\lambda^{\alpha 2,2} (\lambda_B)$ $\lambda^{\gamma,2} (\lambda_C)$ $\lambda^{\epsilon,2} (\lambda_D)$	85 (-78) -115 (-92) 15 (115) -19 (-1)	95 (-66) ^c -126 (-123) ^c 57 (126) ^c -286 (-128) ^c	E(100) – E(001)	53	61 ^b
YCo5	Hexagonal (I) SG 191	LSDA+U	$\lambda^{\alpha 1,2}$ $\lambda^{\alpha 2,2}$ $\lambda^{\gamma,2}$ $\lambda^{\epsilon,2}$	-90 115 76 141	$\begin{array}{l} \lambda^{\alpha 1,2} < 100^d \\ \lambda^{\alpha 2,2} < 100^d \end{array}$	E(100) – E(001)	365	567 ^e
Fe ₂ Si	Trigonal (I) SG 164	GGA	$\lambda^{\alpha 1,2}$ $\lambda^{\alpha 2,2}$ $\lambda^{\gamma,1}$ $\lambda^{\gamma,2}$ λ_{12}	-9 15 8 28 -3 -13		E(100) – E(001)	-38	
L1 ₀ FePd	Tetragonal (I) SG 123	GGA	$\begin{matrix} \lambda^{\alpha 1,2} \\ \lambda^{\alpha 2,2} \\ \lambda^{\gamma,2} \\ \lambda^{\xi,2} \\ \lambda^{\delta,2} \\ \lambda^{\alpha 1,0} - \frac{\lambda^{\alpha 1,2}}{3} + \frac{\lambda^{\gamma,2}}{2} \end{matrix}$	-21 79 31 28 106	100 ^g	E(100) – E(001)	106	181 ^f
YCo	Orthorhombic SG 63	LSDA+U	λ ₁ λ ₂ λ ₃ λ ₄ λ ₅ λ ₆ λ ₇ λ ₈	-11 32 70 -74 -30 7 36 -20 35		E(100) – E(001) E(010) – E(001)	22 -23	

More details can be found in P. Nieves, S. Arapan, S.H. Zhang, A.P. Kądzielawa, R.F. Zhang and D. Legut, "MAELAS: MAgneto-ELAStic properties calculation via computational high-throughput approach", 2020, arXiv:2009.01638

MAELAS TESTS

Table 4: Elastic and magnetoelastic constants calculated using the interface between AELAS and MAELAS codes. The third column shows the DFT method used to compute the elastic constants. The experimental elastic constants of BCC Fe and HCP Co were measured at $T\approx 0~{\rm K}$ and $T\approx 300~{\rm K}$, respectively. The experimental magnetoelastic constants were estimated using the experimental elastic constants (seventh column) and the experimental magnetostrictive coefficients in Table 3 via the relations given in Section 2. The sixth column presents calculations of the elastic constants available in the Materials Project database [49, 50].

Material	Crystal system	DFT method	Elastic constant	AELAS (GPa)	Mat.Proj. (GPa)	Expt. (GPa)	Magnetoelastic constant	MAELAS (MPa)	Expt. (MPa)
BCC Fe	Cubic (I)	GGA	c_{11}	286	247 ^a	243 ^b	b_1	-4.6	-4.1
	SG 229		c_{12}	152	150^{a}	138^{b}	b_2	-5.9	10.9
			C44	103	97a	122^{b}			
HCP Co	Hexagonal (I)	GGA	c_{11}	459	358^{c}	307^{d}	b_{21}	-39.1	-31.9
	SG 194		c_{12}	179	165^{c}	165^{d}	b_{22}	33.6	25.5
			c_{13}	132	114^{c}	103^{d}	b_3	-4.2	-8.1
			C33	487	409^{c}	358^{d}	b_4	4.5	42.9
			C44	118	95^c	75^d			
		SCAN	c_{11}	648			b_{21}	-51.3	
			c ₁₂	212			b_{22}	40.5	
			c ₁₃	189			<i>b</i> ₃	6.4	
			C33	633			b_4	8.9	
			C44	239					
YCo ₅	Hexagonal (I)	GGA	c_{11}	208	192 ^e		b ₂₁	14.9	
	SG 191		c_{12}	103	123^e		b_{22}	-10.4	
			c ₁₃	114	113^{e}		b_3	-8.0	
			C33	270	262^{e}		b_4	-13.6	
			C44	49	48^e				
		LSDA+U	c_{11}	-63			b_{21}	13.9	
			c ₁₂	363			b_{22}	-7.9	
			c ₁₃	115			b_3	32.5	
			C33	249			b_4	-12.4	
			c ₄₄	44					


Table 5: Elastic and magnetoelastic constants calculated using the interface between AELAS and MAELAS codes. The third column shows the DFT method used to compute the elastic constants. The experimental elastic constants of L1₀ FePd were measured at $T \approx 300$ K. The sixth column presents calculations of the elastic constants available in the Materials Project database [49, 50].

Material	Crystal system	DFT method	Elastic constant	AELAS (GPa)	Mat.Proj. (GPa)	Expt. (GPa)	Magnetoelastic constant	MAELAS (MPa)	Expt. (MPa)
Fe ₂ Si	Trigonal (I)	GGA	c_{11}	428	415a		b ₂₁	3.1	
-	SG 164		c ₁₂	164	169^{a}		b ₂₂	-4.2	
			c ₁₃	133	133^{a}		b_3	-0.7	
			c ₁₄	-27	-25^{a}		b_4	3.3	
			C33	434	428^{a}		b_{14}	-1.4	
			C44	118	107 ^a		b ₃₄	-0.4	
L1 ₀ FePd	Tetragonal (I)	GGA	c_{11}	324	293^{b}	214^c	b_{21}	-2.4	
	SG 123		c ₁₂	67	62^{b}	143^{c}	b_{22}	-15.2	
			c_{13}	133	125^{b}	143^{c}	b_3	-7.9	
			c33	264	254^{b}	227^{c}	b_3'	-7.9	
			C44	101	99^b	92^c	b_4	-5.6	
			C ₆₆	37	38^b	93 ^c			
YCo	Orthorhombic	GGA	c_{11}	76	94^d		b_1	-0.9	
	SG 63		c_{12}	45	61^d		b_2	0.6	
			c ₁₃	48	44^d		b_3	-5.0	
			C22	102	93 ^d		b_4	5.7	
			c_{23}	55	56 ^d		b_5	0.9	
			C33	141	121 ^d		b_6	1.5	
			C44	40	38^{d}		b_7	-5.0	
			C55	27	29^{d}		b_8	1.1	
			c ₆₆	39	41 ^d		b_9	-8.2	
		LSDA+U	c ₁₁	101			b_1	-1.7	
			c ₁₂	65			b_2	1.2	
			c ₁₃	58			b_3	-3.8	
			c_{22}	94			b_4	4.3	
			C23	70			b_5	-0.1	
			C33	138			b_6	2.3	
			C44	42			b_7	-4.4	
			C55	29			b_8	1.1	
			c ₆₆	35			<i>b</i> ₉	-8.7	


MAELAS TESTS: HCP Co

Experimental results

Z. Physik 224, 148-155 (1969)



Calculation of $\lambda^{\alpha 1,2}$ for HCP Co using MAELAS



More details can be found in P. Nieves, S. Arapan, S.H. Zhang, A.P. Kądzielawa, R.F. Zhang and D. Legut, "MAELAS: MAgneto-ELAStic properties calculation via computational high-throughput approach", 2020, arXiv:2009.01638

Visualization tool MAELASviewer


We have also developed an online visualization tool called MAELASviewer that is available at

https://maelasviewer.herokuapp.com

This interactive applet shows the magnetostriction for the supported crystal systems of MAELAS. Users can simulate the Joule and Wiedemann effects.

More details of this application can be found in:

Nieves, P.; Arapan, S.; Kądzielawa, A.P.; Legut, D. MAELASviewer: An Online Tool to Visualize Magnetostriction. Sensors 2020, 20, 6436.



Bibliography

- P. Nieves, S. Arapan, S.H. Zhang, A.P. Kądzielawa, R.F. Zhang and D. Legut, "MAELAS: MAgneto-ELAStic properties calculation via computational high-throughput approach", 2020, arXiv:2009.01638
- J. R. Cullen, A. E. Clark, and K. B. Hathaway, in Materials, Science and Technology (VCH Publishings, 1994), pp. 529 565.
- R.Q. Wu et al. Journal of Magnetism and Magnetic Materials 177-181 (1998) 1216-1219.
- M.R.J.Gibbs, Modern Trends in Magnetostriction, Springer Netherlands (2001).
- Göran Engdahl, Isaak D. Mayergoyz, Handbook of Giant Magnetostrictive Materials, Academic Press (1999).