
silicon: fixed structure / gth-dzvp-molopt-sr / gth-pbe
k=(2, 1, 1), FFT=(21, 21, 21); numerical cross-checks passed, discretization not converged
PBE
Sampled path gap 0.300 eV
PBE0
Sampled path gap 1.936 eV
Band energy relative to each declared reference (eV)
10.0
7.5
5.0
2.5
0.0
−2.5
−5.0
−7.5
−10.0
Γ
X
W
K
Γ
L
Wavevector path