
silicon: fixed structure / gth-dzvp-molopt-sr / gth-pbe
k=(2, 2, 2), FFT=(31, 31, 31); numerical cross-checks passed, discretization not converged
LDA
Sampled path gap 0.291 eV
PBE
Sampled path gap 0.525 eV
R2SCAN
Sampled path gap 0.692 eV
Band energy relative to each declared reference (eV)
10.0
7.5
5.0
2.5
0.0
−2.5
−5.0
−7.5
−10.0
Γ
X
W
K
Γ
L
Wavevector path