



X-RAY LABORATORIES LTD

WELDER'S QUALIFICATION TEST CERTIFICATE

AS/NZS ISO 9606.1:2017 Qualification testing of welders - Fusion welding - Part 1: Steels

Designations: ISO 9606-1 111 P BW FM1 B t12 PA bs ml
ISO 9606-1 111 P FW FM1 B t12 PB ss sl (supplementary fillet)

Certificate No. **16587A**

WPS - Reference: 4711HD
Welder: Adam Green
Identification: NZDL DH912208
Date of birth: 29/04/1988
Employer: Lateral Engineering
Testing standard: AS/NZS ISO 9606.1:2017 & AS/NZS 2980:2018

Job knowledge: Not tested
Date of test: 16/08/2022
Supervisor: Greg Kershaw



	Test piece		Range of qualification	
Welding process	111	MMAW	111	Manual metal arc welding
Transfer mode	NA	Not applicable	NA	Not applicable
Product type	P	Plate	P / T	Plate & Tube
Type of weld	BW	Butt with supplementary fillet	BW / FW	Butt and fillet welds
Parent material group + subgroup	1.2	Low carbon steel	NA	Non-essential variable
Filler material group	FM1	Non-alloy/fine grain steels	FM1 / FM2	High strength & non alloy/fine grain steels
Filler material (Designation)	B	Basic covering	B / A / RA / R / RB / RC / RR	Basic, rutile, & other
Shielding gas	NA	Nil	NA	Non-essential variable
Auxiliaries	NA	Nil	NA	Non-essential variable
Current type and polarity	DCEP	Direct current electrode+	NA	Non-essential variable
Material thickness	12	12mm	≥3	≥3mm
Outside pipe diameter	NA	Not applicable (plate)	≥500mmØ fixed	≥75mmØ rotated PA, PB
Welding positions	PA	Flat butt	PA/PB	Flat
Weld details	bs	Welded from both sides	bs/ss,mb	Material backing or from both sides
Multi-layer/single layer	ml	Multi-layer	sl / ml	Single or multi-layer welds

Supplementary fillet weld test Complies

Type of test	Results	
Visual examination	Complies	Test Report 16587A1
Radiographic testing	Complies	Test Report 16587A1
Fracture test	Complies	Test Report 16587A1
Bend test	Not required	NA
Notch tensile test	Not required	NA
Macroscopic examination	Not required	NA

Examining body: X-Ray Laboratories Ltd, AKL, NZ
Examiner: I O Hughes
Signed: 



Date of issue: 19 August 2022

The above testing was conducted in accordance with the requirements of ISO 9606-1 under the laboratory's IANZ accreditation.

According to 9.3 a) The skill of the welder can be periodically verified by having the welder retested every 3 years

Revalidation 9.3 a)	Valid until 17/08/25	Revalidation 9.3 b)	Valid until 17/08/24	Revalidation 9.3 c)	Valid until 17/02/23
------------------------	-------------------------	------------------------	-------------------------	------------------------	-------------------------

Revalidation for qualification by examiner or test body for the following two years [refer to 9.3b)]

Date	Signature	Position or title

Confirmation of validity by employer/welding co-ordinator/examiner or examining body for the following six months [refer to 9.2)]

Date	Signature	Position or title



X-RAY LABORATORIES LTD

PO BOX 12650, PENROSE, AKL 1642 43A LEONARD RD, MT WELLINGTON, AKL 1060
PHONE 09 5794972 WWW.XRAYLABS.CO.NZ XRAYLABS@XRAYLABS.CO.NZ

WELDER QUALIFICATION TEST REPORT

TEST REPORT No.	16587A1	Page 1 of 1
Client:	Welding Specialties Ltd	
Reference:	Inspection and testing of welder qualification test samples at our Mt Wellington premises.	
Identification:	Adam Green WPS Ref: 4711HD Welded: 16/08/22	
Weld process:	MMAW	Parent material: Low carbon steel
Weld positions:	Butt welds PA Supplementary fillet PB	Material thicknesses: 12mm
VISUAL EXAMINATIONS: (all test welds)		
Date of inspection:	16/08/2022	Test Procedure: XRL045
Technique Standard:	AS/NZS ISO 17637:2019 AS 3978:2003	Acceptance Standards: ISO 5817:2019 Levels B & C AS/NZS 2980:2018 Table B3.2(A)
Surface condition:	As welded bare steel	Viewing conditions: Natural & incandescent, >1000lux
Technician:	I O Hughes	Qualification: AS 2214
Findings:	No unacceptable imperfections	Result: COMPLIES
RADIOGRAPHIC EXAMINATIONS:		
Date of test:	18/08/22	Test Procedure: XRL017
Technique Standards:	EN ISO 17636-1:2013 AS 2177:2006	Acceptance Standards: ISO 5817:2019 Level B AS/NZS 2980:2018 Table B3.6.3
Radiation source:	186kV	Focal spot: 2.0mm ²
IQI:	10FEEN, source side	Screens: 0.125mm Pb
Technique:	XR2/S	FFD: 700mm
Film type:	Fuji IX100	Processing: Manual @ 20°C, 5min dev
Density:	≥2.0 & ≤4.0	Sensitivity: <2%
Restrictions/variations:	Nil	Other: NA
Technician:	I O Hughes	Qualification: AINDT RT2
Film ID:	Interpretation:	Result:
16587 AG 111 PA	No unacceptable weld imperfections indicated	COMPLIES
FILLET FRACTURE TEST:		
Breakover and examination of entire length of PB position equal leg fillet:		
Date of test:	18/08/22	Test procedure: XRL M7
Test standard:	BS EN ISO 9017:2018 AS/NZS 2205.4.1:2019	Acceptance standard: ISO 5817:2019 Level B AS/NZS 2980:2018 Clause B3.4.2
Fusion & penetration	Complete, to/past root	Notes: None
Technician:	I O Hughes	Results: COMPLIES
Notes:	None.	
Signed:		 I O Hughes 19 August 2022