Table S1. Dataset.

Soil (%)	Cement (%)	Lime (%)	LL (%)	PL (%)	PI (%)	USCS	MDD (kN/m³)	OMC (%)	UCS (kN/m²)	Work
100	0	0	49	24	25	CL	1670	20	55.31	(Aytekin and Nas 1998)
93	0	7	37	33.5	3.5	ML	1720	18.3	351.67	
85	0	15	38	34.3	3.7	ML	1640	21.3	369.42	
70	0	30	38.4	32	6.4	ML	1590	22.8	461.89	
93	7	0	40	34.1	5.9	ML	1720	17	1803.44	
85	15	0	41	35.9	5.1	ML	1740	17.5	2284.95	
70	30	0	39	32.2	6.8	ML	1770	18	3297	
100	0	0	44.5	35	9.5	ML	1420	29	69.43	
93	0	7	46.5	42.3	4.2	ML	1480	22.8	1305.27	
85	0	15	47	39	8	ML	1470	26.3	1147.38	
70	0	30	48	42	6	ML	1390	28.8	1090.5	
93	7	0	48	40.3	7.7	ML	1560	22.5	609.97	
85	15	0	49	40.7	8.3	ML	1530	26.3	2545.81	
70	30	0	46	41	5	ML	1500	30	3936.39	
100	0	0	84	40	44	MH	1290	36	87.08	
70	30	0	57	41.5	15.5	MH	1390	36.8	2076.95	
100	0	0	77	45	32	MH	1410	29	360	(Bell 1989)
96	0	4	102	47	55	MH	1353	31	1180	
100	0	0	60	37	23	MH	1400	31	520	
92	0	8	73	43	30	MH	1340	35	3400	
100	0	0	86	54	32	MH	1220	22	85	
94	0	6	80	58	22	MH	1200	33	180	
100	0	0	84.8	32.78	52.02	CH	1407	28.3	55.6	(Harichane et al. 2010; 2011)
96	0	4	78.73	57.26	21.47	MH	1346	30.4	1032.2	
92	0	8	78.16	58.24	19.92	MH	1315	31.1	1050.7	
100	0	0	47.79	23.23	24.56	CL	1723	15.3	222.5	
96	0	4	58.97	36.34	22.63	MH	1672	17.8	692.2	
92	0	8	57.03	37.35	19.68	MH	1652	17.4	716.9	
100	0	0	86	37	49	CH	1290	36.5	149	(Hasan et al. 2016)
100	0	0	84	26	58	CH	1353	29.83	190	(Phanikumar and Ramanjaneya Raju 2020)
100	0	0	75	28	47	CH	1406	31.82	663	
97	0	3	54	24	30	CH	1564	19.9	1100	(Siddique and Hossain 2011)
94	0	6	53	28	25	CH	1538	23.8	1820	
91	0	9	54	32	22	MH	1504	25.6	1930	

88	0	12	57	37	20	MH	1472	27.7	2300	
85	0	15	59	40	19	MH	1438	29.9	2650	
97	3	0	18	14	4	ML	2080	8.5	4400	
94	6	0	18	14	4	ML	2080	8.5	4400	
94	4	2	19	14	5	CL-ML	1960	7.8	2540	
95	5	0	19	14	5	CL-ML	1960	7.8	2540	
94	4	2	20	20	0	ML	1890	7.3	3200	
95	5	0	20	20	0	ML	1890	7.3	3200	
95	5	0	20	19	1	ML	1650	8.3	1900	
96	4	0	20	19	1	ML	1650	8.3	1900	
96	4	0	21	17	4	ML	2080	8.5	4700	
94	6	0	21	17	4	ML	2080	8.5	4700	
96	4	0	22	22	0	ML	2200	8.7	3900	
95	5	0	22	17	5	CL-ML	2120	8.4	4200	
94	6	0	22	17	5	CL-ML	2120	8.4	4200	
94	6	0	22	19	3	ML	1720	9.9	2950	
95	5	0	22	19	3	ML	1720	9.9	2950	
94	6	0	22	19	3	ML	1920	11.4	2700	
94	4	2	22	19	3	ML	1920	11.4	2700	
92	4	4	23	18	5	CL-ML	1900	10	3100	
95	5	0	23	18	5	CL-ML	1900	10	3100	
94	4	2	23	15	8	CL	1830	13.5	1800	(Burroughs 2001)
94	3	3	23	15	8	CL	1830	13.5	1800	
90	6	4	23	18	5	CL-ML	2000	11.5	2900	
94	4	2	23	18	5	CL-ML	2000	11.5	2900	
94	6	0	23	18	5	CL-ML	2000	11.5	2900	
94	6	0	23	18	5	CL-ML	2000	11.5	2900	
94	2	4	23	22	1	ML	1730	9.8	1100	
94	6	0	23	22	1	ML	1730	9.9	1100	
96	4	0	24	20	4	ML	2000	7.7	4100	
94	6	0	24	20	4	ML	2000	7.7	4100	
94	6	0	24	21	3	ML	1750	10.8	2300	
94	4	2	24	21	3	ML	1750	10.8	2300	
95	0	5	25	12	13	CL	1670	10.1	1860	
94	0	6	25	12	13	CL	1670	10.1	1860	
94	6	0	25	12	13	CL	1670	10.1	2700	
95	5	0	25	21	4	ML	1980	7.9	4100	
94	6	0	25	21	4	ML	1980	7.9	4100	
94	3	3	26	19	7	CL	1860	12.7	2300	
95	5	0	26	19	7	CL	1860	12.7	2300	
94	3	3	27	16	11	CL	1930	8.7	2050	

94	2	4	27	16	11	CL	1930	8.7	2050
94	2	4	27	24	3	ML	1450	16.3	1200
94	4	2	27	24	3	ML	1450	16.3	1200
96	2	2	28	19	9	CL	2150	6	3300
94	4	2	28	19	9	CL	2150	6	3300
93	5	2	28	19	9	CL	1840	12.8	2930
92	4	4	28	19	9	CL	1840	12.8	2930
94	4	2	29	16	13	CL	2010	9.7	2000
96	0	4	29	16	13	CL	2010	9.7	2000
94	4	2	29	20	9	CL	1610	12.6	2000
94	6	0	29	20	9	CL	1610	12.6	2000
94	6	0	29	20	9	CL	1610	12.6	2050
95	0	5	29	12	17	CL	1990	12.3	2960
94	6	0	29	12	17	CL	1990	12.3	2960
94	0	6	29	18	11	CL	1900	10.1	4600
94	4	2	29	18	11	CL	1900	10.1	4600
95	5	0	29	22	7	CL	1970	8.1	3250
94	6	0	29	22	7	CL	1970	8.1	3250
94	6	0	29	14	15	CL	1690	11.4	2200
92	2	6	29	12	17	CL	2090	11.2	1820
94	6	0	29	12	17	CL	2090	11.2	1820
96	0	4	29	14	15	CL	1690	11.4	2620
94	4	2	29	22	7	CL	1780	18.5	2200
96	4	0	29	22	7	CL	1780	18.5	2200
92	4	4	30	18	12	CL	1970	10.1	3000
96	0	4	30	18	12	CL	1970	10.1	3000
92	2	6	30	14	16	CL	1830	9.4	3000
94	4	2	30	14	16	CL	1830	9.4	3000
95	5	0	31	25	6	ML	1940	7.3	3800
94	6	0	31	25	6	ML	1940	7.3	3800
95	0	5	31	14	17	CL	2120	8.8	3900
94	6	0	31	14	17	CL	2120	8.8	3900
92	2	6	32	17	15	CL	1820	6.9	2950
94	6	0	32	17	15	CL	1820	6.9	2950
97	0	3	32	12	20	CL	1960	8.2	1930
94	6	0	32	12	20	CL	1960	8.2	1930
94	3	3	32	24	8	ML	1920	9.3	2150
95	5	0	32	24	8	ML	1920	9.3	2150
97	0	3	32	17	15	CL	1950	13	3100
92	4	4	32	17	15	CL	1950	13	3100
94	0	6	32	13	19	CL	1690	8.8	1980

94	4	2	32	13	19	CL	1690	8.8	1980
94	0	6	33	12	21	CL	1810	16	2450
92	6	2	33	12	21	CL	1810	16	2450
95	0	5	33.5	18	15.5	CL	1700	5.4	2010
94	6	0	33.5	18	15.5	CL	1700	5.4	2010
94	3	3	35	27	8	ML	2210	8.2	4200
96	4	0	35	27	8	ML	2210	8.2	4200
94	4	2	35	15	20	CL	1650	11.7	1600
95	0	5	35	15	20	CL	1650	11.7	2300
94	6	0	35	15	20	CL	1650	11.7	2300
94	6	0	35	21	14	CL	2100	8	2270
95	0	5	35	21	14	CL	2100	8	2270
94	4	2	35	29	6	ML	2040	8.8	3210
95	5	0	35	29	6	ML	2040	8.8	3210
94	6	0	35	17	18	CL	1890	10.9	2870
94	0	6	36	17	19	CL	1900	7	2800
94	6	0	36	17	19	CL	1900	7	2800
94	6	0	36	17	19	CL	2150	7	2900
95	0	5	36.4	19	17.4	CL	1920	9.4	2020
94	6	0	36.4	19	17.4	CL	1920	9.4	2020
92	2	6	37	16	21	CL	1900	12.4	4900
92	6	2	37	16	21	CL	1900	12.4	4900
94	4	2	37	14	23	CL	1470	10.6	1500
94	0	6	38	23	15	CL	1930	7.9	2000
94	6	0	38	23	15	CL	1930	7.9	2000
96	0	4	38	17	21	CL	1820	10.5	1880
94	6	0	38	17	21	CL	1820	10.5	1880
94	4	2	38	17	21	CL	1780	9.1	2300
94	6	0	39	25	14	CL	1860	12	3000
92	2	6	40	20	20	CL	1980	7.1	1610
94	6	0	40	20	20	CL	1980	7.1	1610
94	6	0	40	15	25	CL	1970	9.2	3980
94	4	2	40	18	22	CL	1920	7.8	2990
94	4	2	40	17	23	CL	1780	10.9	2300
96	0	4	41	21	20	CL	1700	19	1690
94	6	0	41	21	20	CL	1700	19	1690
95	0	5	42	23	19	CL	1440	9.3	2300
94	6	0	42	23	19	CL	1440	9.3	2300
94	6	0	42	20	22	CL	1860	9.7	2790
92	6	2	42	15	27	CL	1980	12.2	2960
94	6	0	43.3	15	28.3	CL	1760	16.5	1820

94	6	0	44	22	22	CL	2010	8.7	3200	
94	4	2	44	18	26	CL	1790	8.9	2250	
94	6	0	45	12	33	CL	1760	14.8	1980	
94	4	2	45	26	19	CL	1820	10.5	1750	
92	2	6	45	26	19	CL	1820	10.5	2450	
94	2	4	45	26	19	CL	1820	10.5	2450	
94	4	2	45	27	18	ML	1820	12.5	1900	
93	5	2	45	27	18	ML	1820	12.5	4100	
92	2	6	45	27	18	ML	1820	12.5	4100	
94	6	0	46	16	30	CL	1520	14.8	1800	
92	4	4	46	16	30	CL	1520	14.8	1820	
94	2	4	50	15	35	CH	1940	10.2	3000	
94	6	0	51	25	26	CH	2150	7.9	4020	
94	6	0	52	34	18	MH	2010	8.7	5400	
94	6	0	55	20	35	CH	1520	14	1200	
94	6	0	55	23	32	CH	1550	15.5	1570	
94	6	0	55	30	25	MH	1870	16	3300	
94	6	0	57	36	21	MH	2100	9	3400	
94	0	6	58	16	42	CH	1600	22.7	1350	
94	2	4	65	14	51	CH	1600	20	1500	
94	0	6	66	24	42	CH	1520	28	1250	
94	4	2	72	23	49	CH	1600	11.2	1300	
94	4	2	72	23	49	CH	1600	11.2	1500	
94	4	2	73	25	48	CH	1590	16	1700	
94	6	0	73	25	48	CH	1590	16	1900	
94	2	4	89	19	70	CH	1510	25.5	1400	
100	0	0	42.25	19.3	22.95	CL	1720	14.5	1025	(Workie and Alam 2019)
98	0	2	37.11	20.6	16.51	CL	1730	15.1	1120	
96	0	4	31.78	21	10.78	CL	1750	13.8	1154	
100	0	0	39	18	21	CL	1772	16.5	193.05	(Solanki, Khoury, and Zaman 2009)
100	0	0	37	26	11	ML	1632	23	165.47	
100	0	0	58	29	29	CH	1661	20.3	206.84	

References

Aytekin, Mustafa, and Evin Nas. 1998. "Soil Stabilization with Lime and Cement." *Teknik Dergi/Technical Journal of Turkish Chamber of Civil Engineers* 9 (1): 1573–85.

Bell, F G. 1989. "Lime Stabilisation of Clay Soils." *Bulletin of the International Association of Engineering Geology*, no. 30: 67–74.

Burroughs, Van Stephan. 2001. "Quantitative Criteria for the Selection and Stabilisation of Soils for Rammed Earth Wall

Construction." University of New South Wales.

Harichane, Khelifa, Mohamed Ghrici, Said Kenai, and Khaled Grine. 2011. "Use of Natural Pozzolana and Lime for Stabilization of Cohesive Soils." *Geotechnical and Geological Engineering* 29 (5): 759–69. https://doi.org/10.1007/s10706-011-9415-z.

Harichane, Khelifa, Mohamed Ghrici, Wiem Khebizi, and Hanifi Missoum. 2010. "Effect of the Combination of Lime and Natural Pozzolana on the Durability of Clayey Soils." *Electronic Journal of Geotechnical Engineering* 15: 1194–1209.

Hasan, Hayder, Liet Dang, Hadi Khabbaz, Behzad Fatahi, and Sergei Terzaghi. 2016. "Remediation of Expansive Soils Using Agricultural Waste Bagasse Ash." *Procedia Engineering* 143: 1368–75. https://doi.org/10.1016/j.proeng.2016.06.161.

Phanikumar, B. R., and E. Ramanjaneya Raju. 2020. "Compaction and Strength Characteristics of an Expansive Clay Stabilised with Lime Sludge and Cement." *Soils and Foundations* 60 (1): 129–38. https://doi.org/10.1016/j.sandf.2020.01.007.

Siddique, Abu, and M. Alomgir Hossain. 2011. "Effects of Lime Stabilisation on Engineering Properties of an Expansive Soil for Use in Road Construction." *Journal of Society for Transportation and Traffic Studies* 2 (4): 1–8.

Solanki, Pranshoo, Naji N. Khoury, and Musharraf M Zaman. 2009. "Engineering Properties of Stabilized Subgrade Soils for Implementation of the AASHTO 2002 Pavement Design Guide." Norman, Oklahoma.

Workie, Asres Getnet, and Shamshad Alam. 2019. "Effect of Lime and Fly Ash on Load Bearing Capacity of Expansive Clay Soil." *International Journal of Innovative Technology and Exploring Engineering* 8 (11): 554–63. https://doi.org/10.35940/ijitee.K1573.0881119.