

NASICON-type $\text{Na}_3\text{V}_2(\text{PO}_4)_3$

Igor V. Zatonvsky

Department of Inorganic Chemistry, Taras Shevchenko National University, 64
Volodymyrska str., 01601 Kyiv, Ukraine
Correspondence e-mail: zvigo@yandex.ru

Received 19 December 2009; accepted 22 January 2010

Key indicators: single-crystal X-ray study; $T = 293\text{ K}$; mean $\sigma(\text{P}-\text{O}) = 0.001\text{ \AA}$; disorder in solvent or counterion; R factor = 0.032; wR factor = 0.075; data-to-parameter ratio = 36.0.

Single crystals of the title compound, trisodium divanadium(III) tris(orthophosphate), were grown from a self-flux in the system $\text{Na}_4\text{P}_2\text{O}_7\text{--NaVP}_2\text{O}_7$. $\text{Na}_3\text{V}_2(\text{PO}_4)_3$ belongs to the family of NASICON-related structures and is built up from isolated $[\text{VO}_6]$ octahedra (3. symmetry) and $[\text{PO}_4]$ tetrahedra (.2 symmetry) interlinked *via* corners to establish the framework anion $[\text{V}_2(\text{PO}_4)_3]^{3-}$. The two independent Na^+ cations are partially occupied [site-occupancy factors = 0.805 (18) and 0.731 (7)] and are located in channels with two different oxygen environments, *viz* sixfold coordination for the first ($\bar{3}$. symmetry) and eightfold for the second (.2 symmetry) Na^+ cation.

Related literature

For structures and properties of complex phosphates with general formula $\text{Na}_3M^{\text{III}}_2(\text{PO}_4)_3$ ($M^{\text{III}} = \text{Sc, Fe, Cr}$), see: Collin *et al.* (1986); Genkina *et al.* (1991); Lazoryak *et al.* (1980); Lucazeau *et al.* (1986); Masquelier *et al.* (1992); Susman *et al.* (1983). For preparation of NaVP_2O_7 which was used as an educt for crystal growth of the title compound, see: Zatonvsky *et al.* (1999).

Experimental

Crystal data

$\text{Na}_3\text{V}_2(\text{PO}_4)_3$	$Z = 6$
$M_r = 455.76$	Mo $K\alpha$ radiation
Trigonal, $R\bar{3}c$	$\mu = 2.66\text{ mm}^{-1}$
$a = 8.7288\text{ (2)\AA}$	$T = 293\text{ K}$
$c = 21.8042\text{ (7)\AA}$	$0.20 \times 0.15 \times 0.10\text{ mm}$
$V = 1438.73\text{ (7)\AA}^3$	

Data collection

Oxford Diffraction Xcalibur-3 CCD diffractometer	12580 measured reflections
Absorption correction: multi-scan (Blessing, 1995)	1331 independent reflections
$T_{\min} = 0.635$, $T_{\max} = 0.780$	1153 reflections with $I > 2\sigma(I)$
	$R_{\text{int}} = 0.063$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.032$	37 parameters
$wR(F^2) = 0.075$	$\Delta\rho_{\max} = 1.12\text{ e \AA}^{-3}$
$S = 1.1$	$\Delta\rho_{\min} = -0.74\text{ e \AA}^{-3}$
1331 reflections	

Table 1

Selected bond lengths (\AA).

$\text{V1}-\text{O2}^{\text{i}}$	1.9693 (10)	$\text{Na2}-\text{O2}^{\text{iii}}$	2.6280 (16)
$\text{V1}-\text{O1}^{\text{ii}}$	2.0271 (9)	$\text{Na2}-\text{O2}^{\text{iv}}$	2.8352 (19)
$\text{Na1}-\text{O1}$	2.5045 (11)	$\text{P1}-\text{O2}^{\text{v}}$	1.5227 (12)
$\text{Na2}-\text{O1}^{\text{ii}}$	2.3883 (12)	$\text{P1}-\text{O1}$	1.5358 (10)
$\text{Na2}-\text{O1}^{\text{i}}$	2.4448 (19)		

Symmetry codes: (i) $-y + 1, x - y + 1, z$; (ii) $-x + y, -x + 1, z$; (iii) $-x + \frac{4}{3}, -x + y + \frac{2}{3}, -z + \frac{1}{6}$; (iv) $-y + \frac{4}{3}, -x + \frac{5}{3}, z + \frac{1}{6}$; (v) $x - \frac{2}{3}, x - y + \frac{2}{3}, z + \frac{1}{6}$.

Data collection: *CrysAlis CCD* (Oxford Diffraction, 2006); cell refinement: *CrysAlis CCD*; data reduction: *CrysAlis RED* (Oxford Diffraction, 2006); program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *DIAMOND* (Brandenburg, 1999); software used to prepare material for publication: *WinGX* (Farrugia, 1999) and *enCIFer* (Allen *et al.*, 2004).

The author is grateful to Professor Vyacheslav N. Baumer from STC "Institute for Single Crystals", NAS of Ukraine, Kharkiv, Ukraine, for the single-crystal measurements.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: WM2293).

References

- Allen, F. H., Johnson, O., Shields, G. P., Smith, B. R. & Towler, M. (2004). *J. Appl. Cryst.* **37**, 335–338.
- Blessing, R. H. (1995). *Acta Cryst.* **A51**, 33–38.
- Brandenburg, K. (1999). *DIAMOND*. Crystal Impact GbR, Bonn, Germany.
- Collin, G., Comes, R., Boilot, J. P. & Colomban, P. (1986). *J. Phys. Chem. Solids*, **47**, 843–854.
- Farrugia, L. J. (1999). *J. Appl. Cryst.* **32**, 837–838.
- Genkina, E. A., Kalinin, V. B., Maksimov, B. A. & Golubev, A. M. (1991). *Kristallografiya*, **36**, 1126–1130.
- Lazoryak, B. I., Kalinin, V. B., Stefanovich, S. Yu. & Efremov, V. A. (1980). *Dokl. Akad. Nauk SSSR*, **250**, 861–864.
- Lucazeau, G., Barj, M., Soubeyroux, J. L., Dianoux, A. J. & Delmas, C. (1986). *Solid State Ionics*, **1819**, 959–963.
- Masquelier, C., Wurm, C., Rodriguez-Carvajal, J., Gaubicher, J. & Nazar, L. (1992). *Phase Trans.* **38**, 127–220.
- Oxford Diffraction (2006). *CrysAlis CCD* and *CrysAlis RED*. Oxford Diffraction Ltd, Abingdon, England.
- Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.
- Susman, S., Delbecq, C. J., Brun, T. O. & Prince, E. (1983). *Solid State Ionics*, **9**, 839–844.
- Zatonvsky, I. V., Slobodyanik, N. S., Lisnyk, V. V. & Stratiychuk, D. A. (1999). *Ukr. Khim. Zh.* **65**, 98–103.

supporting information

Acta Cryst. (2010). E66, i12 [https://doi.org/10.1107/S1600536810002801]

NASICON-type $\text{Na}_3\text{V}_2(\text{PO}_4)_3$

Igor V. Zatovsky

S1. Comment

The structures and properties of complex phosphates with general formula $\text{Na}_3M^{\text{III}}_2(\text{PO}_4)_3$ (M^{III} - Sc, Fe, Cr) have been intensively investigated, for instance: (Collin *et al.*, 1986; Genkina *et al.*, 1991; Lazoryak *et al.*, 1980; Lucazeau *et al.*, 1986; Masquelier *et al.*, 1992; Susman *et al.*, 1983). The structure of NASICON-type $\text{Na}_3\text{V}_2(\text{PO}_4)_3$, (I), is reported here.

In the asymmetric unit of (I) (Fig. 1) there is one V and one P atom, while other atoms (Na and O) are represented in two distinct positions each. The main building block of (I) (Fig. 2) involves two VO_6 octahedra interlinked by three phosphate groups lying along the c axis. As a result of the block aggregation, a three-dimensional framework with an overall composition of $[\text{V}_2(\text{PO}_4)_3]^{3-}$ is organized (Fig. 3).

Sodium atoms are located in the voids of the framework with six- (position 6b) and eightfold (18b) coordination when a cut-off distance of 2.9 Å is considered.

S2. Experimental

Crystals of (I) were obtained in the system $\text{Na}_4\text{P}_2\text{O}_7$ — NaVP_2O_7 using a high-temperature crystallization technique. Initial NaVP_2O_7 was prepared in accordance to Zatovsky *et al.* (1999). A thoroughly ground mixture of $\text{Na}_4\text{P}_2\text{O}_7$ and NaVP_2O_7 (ratio 1:3) was heated up to 1343 K and then kept for 2 h in a sealed silica tube under vacuum. Then it was cooled down to 823 K with a rate of 5 K/h and left in the furnace to reach room temperature. The final product, green prismatic crystals, was leached out from the solidified melt with boiling water.

S3. Refinement

After refinement of a basic model and an accurate definition of the atom positions, the occupancy of Na1 and Na2 sites were refined freely and were finally restrained to meet the criterion for charge balance. The highest peak and the deepest hole in the final difference map is located at 0.00 Å from Na1 (1.12 e/Å³) and 0.60 from Na2 (-0.74 e/Å³) respectively.




Figure 1

The asymmetric unit of $\text{Na}_3\text{V}_2(\text{PO}_4)_3$ with displacement ellipsoids at the 50% probability level.




Figure 2

The central building block $[\text{V}_2(\text{PO}_4)_3]$ in the structure of compound (I).




Figure 3

The view of the structure of compound (I) on the *ab* plane.

trisodium divanadium(III) tris(orthophosphate)

Crystal data

$\text{Na}_3\text{V}_2(\text{PO}_4)_3$

$M_r = 455.76$

Trigonal, $R\bar{3}c$

Hall symbol: $-\text{R } 3\ 2''c$

$a = 8.7288\ (2)\ \text{\AA}$

$c = 21.8042\ (7)\ \text{\AA}$

$V = 1438.73\ (7)\ \text{\AA}^3$

$Z = 6$

$F(000) = 1320$

$D_x = 3.156\ \text{Mg m}^{-3}$

Mo $K\alpha$ radiation, $\lambda = 0.71073\ \text{\AA}$

Cell parameters from 12580 reflections

$\theta = 3.3\text{--}45.0^\circ$

$\mu = 2.66\ \text{mm}^{-1}$

$T = 293\ \text{K}$

Prism, green

$0.20 \times 0.15 \times 0.10\ \text{mm}$

Data collection

Oxford Diffraction Xcalibur-3 CCD
diffractometer

Radiation source: fine-focus sealed tube

Graphite monochromator

φ and ω scans

Absorption correction: multi-scan
(Blessing, 1995)

$T_{\min} = 0.635$, $T_{\max} = 0.780$

12580 measured reflections

1331 independent reflections

1153 reflections with $I > 2\sigma(I)$

$R_{\text{int}} = 0.063$

$\theta_{\max} = 45^\circ$, $\theta_{\min} = 3.3^\circ$

$h = -17 \rightarrow 16$

$k = -17 \rightarrow 17$

$l = -43 \rightarrow 41$

Refinement

Refinement on F^2

Least-squares matrix: full

$R[F^2 > 2\sigma(F^2)] = 0.032$

$wR(F^2) = 0.075$

$S = 1.1$

1331 reflections

37 parameters

0 restraints

Primary atom site location: structure-invariant
direct methods

Secondary atom site location: difference Fourier
map

$w = 1/[\sigma^2(F_o^2) + (0.0264P)^2 + 5.1429P]$

where $P = (F_o^2 + 2F_c^2)/3$

$(\Delta/\sigma)_{\max} < 0.001$

$\Delta\rho_{\max} = 1.12\ \text{e \AA}^{-3}$

$\Delta\rho_{\min} = -0.74\ \text{e \AA}^{-3}$

Extinction correction: *SHELXL97* (Sheldrick,
2008)

Extinction coefficient: 0.0056 (4)

Special details

Geometry. All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R -factor wR and goodness of fit S are based on F^2 , conventional R -factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > \sigma(F^2)$ is used only for calculating R -factors(gt) etc. and is not relevant to the choice of reflections for refinement. R -factors based on F^2 are statistically about twice as large as those based on F , and R -factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

	<i>x</i>	<i>y</i>	<i>z</i>	$U_{\text{iso}}^*/U_{\text{eq}}$	Occ. (<1)
V1	0.3333	0.6667	0.019498 (13)	0.00690 (6)	
Na1	0.3333	0.6667	0.1667	0.149 (5)	0.805 (18)
Na2	0.6667	0.96726 (19)	0.0833	0.0522 (10)	0.731 (7)
P1	−0.04273 (5)	0.3333	0.0833	0.00866 (8)	
O1	0.14193 (13)	0.49765 (14)	0.07762 (5)	0.01643 (16)	
O2	0.54047 (16)	0.84480 (17)	−0.02643 (7)	0.0259 (2)	

Atomic displacement parameters (\AA^2)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
V1	0.00643 (7)	0.00643 (7)	0.00784 (10)	0.00321 (4)	0	0
Na1	0.218 (8)	0.218 (8)	0.0111 (14)	0.109 (4)	0	0
Na2	0.0224 (8)	0.0170 (5)	0.119 (2)	0.0112 (4)	−0.0354 (11)	−0.0177 (5)
P1	0.00635 (10)	0.00714 (14)	0.01276 (15)	0.00357 (7)	0.00152 (5)	0.00305 (11)
O1	0.0089 (3)	0.0130 (3)	0.0220 (4)	0.0015 (3)	0.0048 (3)	0.0057 (3)
O2	0.0185 (4)	0.0223 (5)	0.0322 (6)	0.0067 (4)	0.0143 (4)	0.0151 (4)

Geometric parameters (\AA , $^\circ$)

V1—O2 ⁱ	1.9693 (10)	Na2—O1 ⁱⁱ	2.3883 (12)
V1—O2	1.9693 (11)	Na2—O1 ^{vi}	2.3883 (12)
V1—O2 ⁱⁱ	1.9693 (10)	Na2—O1 ⁱ	2.4448 (19)
V1—O1 ⁱⁱ	2.0271 (9)	Na2—O1 ^{vii}	2.4449 (19)
V1—O1	2.0271 (9)	Na2—O2 ^{viii}	2.6280 (16)
V1—O1 ⁱ	2.0271 (9)	Na2—O2	2.6281 (16)
V1—Na2 ⁱ	3.1070 (6)	Na2—O2 ^{ix}	2.8352 (19)
V1—Na2	3.1070 (7)	Na2—O2 ^x	2.8352 (19)
V1—Na2 ⁱⁱ	3.1070 (6)	Na2—P1 ^{xi}	2.9222 (11)
V1—Na1	3.2096 (3)	Na2—P1 ⁱⁱ	2.9222 (11)
Na1—O1	2.5045 (11)	Na2—P1 ⁱ	2.9968 (17)
Na1—O1 ⁱⁱⁱ	2.5045 (11)	P1—O2 ^{xii}	1.5227 (12)
Na1—O1 ⁱ	2.5045 (11)	P1—O2 ^{xiii}	1.5227 (12)
Na1—O1 ⁱⁱⁱ	2.5045 (11)	P1—O1	1.5358 (10)
Na1—O1 ^{iv}	2.5045 (11)	P1—O1 ^{xiv}	1.5359 (10)
Na1—O1 ^v	2.5046 (11)	P1—Na2 ^{xv}	2.9222 (11)
Na1—V1 ^{iv}	3.2081 (2)	P1—Na2 ⁱ	2.9222 (11)

Na1—Na2 ⁱ	3.3193 (6)	P1—Na2 ⁱⁱ	2.9968 (17)
Na1—Na2 ^v	3.3193 (6)	O1—Na2 ⁱ	2.3883 (12)
Na1—Na2	3.3193 (6)	O1—Na2 ⁱⁱ	2.4448 (19)
Na1—Na2 ⁱⁱ	3.3205 (6)		
O2 ⁱ —V1—O2	96.44 (6)	O1 ⁱⁱ —Na2—O2	68.20 (4)
O2 ⁱ —V1—O2 ⁱⁱ	96.44 (6)	O1 ^{vi} —Na2—O2	115.98 (4)
O2—V1—O2 ⁱⁱ	96.44 (6)	O1 ⁱ —Na2—O2	66.40 (4)
O2 ⁱ —V1—O1 ⁱⁱ	88.22 (5)	O1 ^{vii} —Na2—O2	93.51 (6)
O2—V1—O1 ⁱⁱ	89.72 (5)	O2 ^{viii} —Na2—O2	157.25 (9)
O2 ⁱⁱ —V1—O1 ⁱⁱ	171.80 (6)	O1 ⁱⁱ —Na2—O2 ^{ix}	54.99 (4)
O2 ⁱ —V1—O1	89.72 (5)	O1 ^{vi} —Na2—O2 ^{ix}	108.39 (6)
O2—V1—O1	171.80 (6)	O1 ⁱ —Na2—O2 ^{ix}	115.94 (4)
O2 ⁱⁱ —V1—O1	88.22 (5)	O1 ^{vii} —Na2—O2 ^{ix}	151.11 (4)
O1 ⁱⁱ —V1—O1	85.05 (5)	O2 ^{viii} —Na2—O2 ^{ix}	85.67 (3)
O2 ⁱ —V1—O1 ⁱ	171.80 (6)	O2—Na2—O2 ^{ix}	112.13 (5)
O2—V1—O1 ⁱ	88.22 (5)	O1 ⁱⁱ —Na2—O2 ^x	108.39 (6)
O2 ⁱⁱ —V1—O1 ⁱ	89.72 (5)	O1 ^{vi} —Na2—O2 ^x	54.99 (4)
O1 ⁱⁱ —V1—O1 ⁱ	85.05 (5)	O1 ⁱ —Na2—O2 ^x	151.10 (4)
O1—V1—O1 ⁱ	85.05 (5)	O1 ^{vii} —Na2—O2 ^x	115.94 (4)
O1—Na1—O1 ⁱⁱ	66.33 (3)	O2 ^{viii} —Na2—O2 ^x	112.13 (5)
O1—Na1—O1 ⁱ	66.33 (3)	O2—Na2—O2 ^x	85.67 (3)
O1 ⁱⁱ —Na1—O1 ⁱ	66.33 (3)	O2 ^{ix} —Na2—O2 ^x	80.45 (7)
O1—Na1—O1 ⁱⁱⁱ	113.67 (3)	O2 ^{xii} —P1—O2 ^{xiii}	111.67 (12)
O1 ⁱⁱ —Na1—O1 ⁱⁱⁱ	180	O2 ^{xii} —P1—O1	106.07 (7)
O1 ⁱ —Na1—O1 ⁱⁱⁱ	113.67 (3)	O2 ^{xiii} —P1—O1	112.18 (7)
O1—Na1—O1 ^{iv}	180	O2 ^{xii} —P1—O1 ^{xiv}	112.19 (7)
O1 ⁱⁱ —Na1—O1 ^{iv}	113.67 (3)	O2 ^{xiii} —P1—O1 ^{xiv}	106.07 (7)
O1 ⁱ —Na1—O1 ^{iv}	113.67 (3)	O1—P1—O1 ^{xiv}	108.74 (9)
O1 ⁱⁱⁱ —Na1—O1 ^{iv}	66.33 (3)	P1—O1—V1	145.95 (7)
O1—Na1—O1 ^v	113.67 (3)	P1—O1—Na2 ⁱ	93.73 (6)
O1 ⁱⁱ —Na1—O1 ^v	113.67 (3)	V1—O1—Na2 ⁱ	89.05 (5)
O1 ⁱ —Na1—O1 ^v	180	P1—O1—Na2 ⁱⁱ	94.93 (5)
O1 ⁱⁱⁱ —Na1—O1 ^v	66.33 (3)	V1—O1—Na2 ⁱⁱ	87.50 (4)
O1 ^{iv} —Na1—O1 ^v	66.33 (3)	Na2 ⁱ —O1—Na2 ⁱⁱ	169.09 (5)
O1 ⁱⁱ —Na2—O1 ^{vi}	160.52 (9)	P1—O1—Na1	124.53 (6)
O1 ⁱⁱ —Na2—O1 ⁱ	69.07 (5)	V1—O1—Na1	89.52 (4)
O1 ^{vi} —Na2—O1 ⁱ	130.40 (6)	Na2 ⁱ —O1—Na1	85.40 (5)
O1 ⁱⁱ —Na2—O1 ^{vii}	130.40 (6)	Na2 ⁱⁱ —O1—Na1	84.23 (4)
O1 ^{vi} —Na2—O1 ^{vii}	69.07 (5)	P1 ^{xvi} —O2—V1	151.38 (10)
O1 ⁱ —Na2—O1 ^{vii}	61.41 (6)	P1 ^{xvi} —O2—Na2	120.77 (8)
O1 ⁱⁱ —Na2—O2 ^{viii}	115.98 (4)	V1—O2—Na2	83.72 (5)
O1 ^{vi} —Na2—O2 ^{viii}	68.20 (4)	P1 ^{xvi} —O2—Na2 ^{xvii}	77.85 (5)
O1 ⁱ —Na2—O2 ^{viii}	93.51 (6)	V1—O2—Na2 ^{xvii}	107.30 (6)
O1 ^{vii} —Na2—O2 ^{viii}	66.40 (4)	Na2—O2—Na2 ^{xvii}	113.64 (7)

Symmetry codes: (i) $-y+1, x-y+1, z$; (ii) $-x+y, -x+1, z$; (iii) $x-y+2/3, x+1/3, -z+1/3$; (iv) $-x+2/3, -y+4/3, -z+1/3$; (v) $y-1/3, -x+y+1/3, -z+1/3$; (vi) $x-y+4/3, -y+5/3, -z+1/6$; (vii) $y+1/3, x+2/3, -z+1/6$; (viii) $-x+4/3, -x+y+2/3, -z+1/6$; (ix) $-y+4/3, -x+5/3, z+1/6$; (x) $y, -x+y+1, -z$; (xi) $x+1, y+1, z$; (xii) $x-2/3, x-y+2/3, z+1/6$; (xiii) $y-1, -x+y, -z$; (xiv) $x-y+1/3, -y+2/3, -z+1/6$; (xv) $x-1, y-1, z$; (xvi) $x-y+1, x+1, -z$; (xvii) $x-y+1, x, -z$.