ChemCritic 文献证据卡

PMC12305527 | Buchwald – Hartwig 胺化 | 采集状态 imported_unchecked

标题	Application of palladium nanoparticles supported on ordered mesoporous oxides for C – N and C <svg xmlns="http://www.w3.org/2000/svg" version="1.0" width="23.636364pt" height="16.000000pt" viewBox="0 0 23.636364 16.000000"
作者	Maqunga N., Ndolomingo M., Bingwa N., Meijboom R.
出处	RSC Advances 2025
DOI	10.1039/d5ra02824h
原文链接	https://pmc.ncbi.nlm.nih.gov/articles/PMC12305527/
许可	https://creativecommons.org/licenses/by/3.0/This article is licensed under a Creative Commons Attribution 3.0 Unported L

摘要（原文节选）

This study sought to synthesize supported palladium nanocatalysts that are, in general, convenient to synthesize, suitable for mild conditions, recyclable, and stable in water. The sol – gel procedure was successfully extended to synthesize mesoporous metal oxides with well-dispersed palladium nanoparticles. The resulting catalysts were extensively characterized using techniques such as TEM, powder XRD, SEM-EDX, thermogravimetric analysis, and BET surface area measurements. The catalytic activity of the prepared hete ⋯

数据表 · Table 3（5 行，含数值行 5 行）

The yield, conversion and selectivity obtained for each reaction during the catalyst screening study

Entry	Catalyst	GC yield (%)	Conversion (%)	Selectivity (%)
1	Pd – Co3O4	24	30	50
2	Pd – Mn3O4	82	88	100
3	Pd – NiO	20	32	33
4	Pd – CeO2	97	100	100
5	Pd – TiO2	61	65	100

正文对应句（逐字）：Table 3 and Fig. S3† additionally showed the comparison by GC yield of the 4-methylbiphenylamine produced when Pd – NiO, Pd – Co3O4, Pd – Mn3O4, Pd – TiO2 and Pd – CeO2 were used as catalysts for the model reaction. Amongst all the evaluated catalysts, the Pd – CeO2 produced the highest yield (97%) of the 4-met

数据表 · Table 4（9 行，含数值行 9 行）

Evaluation of the optimal reaction parameters, including bases and temperaturea

Entry	Catalyst	Temperature (° C)	Base	GC yield (%)	Conversion (%)	Selectivity (%)
1	No catalyst	80	K2CO3	No reaction	No reaction	No reaction
2	CeO2	80	K2CO3	No reaction	No reaction	No reaction
3	Pd – CeO2	25	K2CO3	24	30	100
4	Pd – CeO2	50	K2CO3	60	63	100
5	Pd – CeO2	80	K2CO3	97	100	100
6	Pd – CeO2	80	KOH	61	70	100
7	Pd – CeO2	80	NEt3	23	32	80
8	Pd – CeO2	80	Cs2CO3	55	60	33
9	Pd – CeO2	80	Na2CO3	63	66	100

脚注（逐字）：aReaction conditions: aniline (1.2 equiv., 1.2 mmol), 4-bromotoluene (1 equiv., 1 mmol), catalyst (50 mg) and base (2 equiv., 1.5 mmol), 6 h.

正文对应句（逐字）：Table 3 and Fig. S3† additionally showed the comparison by GC yield of the 4-methylbiphenylamine produced when Pd – NiO, Pd – Co3O4, Pd – Mn3O4, Pd – TiO2 and Pd – CeO2 were used as catalysts for the model reaction. Amongst all the evaluated catalysts, the Pd – CeO2 produced the highest yield (97%) of the 4-met

本卡为 NCBI PMC 开放获取 XML
的逐字摘录（标题、作者、表格行列、脚注、正文句均未改写），用于参照集候选与覆盖面登记；未逐条人工核验，标记 imported_unchecked，不写入判定记录、不参与 ChemCritic 引擎的可比性判定。对外引用一律回到 DOI 原文核对页码与表号。