ChemCritic 文献证据卡

PMC8123656 | CuAAC 点击化学 | 采集状态 imported_unchecked

标题	A Facile Strategy for the High Yielding, Quantitative Conversion of Polyglycol End-Groups to Amines
作者	Yan J., Marina P., Blencowe A., Yusa S.
出处	Polymers 2021
DOI	10.3390/polym13091403
原文链接	https://pmc.ncbi.nlm.nih.gov/articles/PMC8123656/
许可	https://creativecommons.org/licenses/by/4.0/Licensee MDPI, Basel, Switzerland. This article is an open access article di

摘要（原文节选）

Amino end-group functionalised polyglycols are important intermediates in the synthesis of sophisticated polymeric architectures and biomaterials. Herein, we report a facile strategy for the end-group conversion of hydroxyl-terminated polyglycols to amino-terminated polyglycols in high isolated yields and with excellent end-group fidelity. Following traditional conversion of polyglycol hydroxyl end-groups to azides via the corresponding mesylate, reduction with zinc in the presence of ammonium chloride afforded a r ⋯

数据表 · Table 1（9 行，含数值行 8 行）

Isolated yield and end-group conversion of the functionalized polyglycols.

Polymer	Isolated Yield (%)	End-Group Conversion (%) a			
Mesylate	Azide	Amine	Overall		
MeOPEG5k	96.9	98.6	94.4	90.3	>99
PEG1.5k	99.9	77.4	99.3	76.8	>99
PEG4.0k	99.9	95.3	94.5	90.0	>99
PEG10k	99.6	92.2	81.9	75.3	>99
PEG35k	98.9	84.8	88.9	74.6	>99
4-Armed PEG10k	98.6	96.8	93.1	88.8	>99
PEG-PPG-PEG13k	98.1	96.1	84.6	79.8	>99
nBuOPPG0.3k	96.6	98.6	92.8	88.4	>99

脚注（逐字）：a Conversion of hydroxyl to amine end-group determined from 1H NMR spectroscopy.

正文对应句（逐字）：The cost of amino-terminated PEGs can be prohibitively expensive compared to their hydroxy-terminated counterparts, which may make them inaccessible for some laboratories, or limit large-scale synthesis and use. For the purpose of obtaining larger quantities of amino-terminated polyglycols, we scree

本卡为 NCBI PMC 开放获取 XML
的逐字摘录（标题、作者、表格行列、脚注、正文句均未改写），用于参照集候选与覆盖面登记；未逐条人工核验，标记
imported_unchecked，不写入判定记录、不参与 ChemCritic 引擎的可比性判定。对外引用一律回到 DOI 原文核对页码与表号。