ChemCritic 文献证据卡

PMC9224514 | 催化氢化 | 采集状态 imported_unchecked

标题	Development of High-Efficiency, Magnetically Separable Palladium-Decorated Manganese-Ferrite Catalyst for Nitrobenzene Hydrogenation
作者	Hajdu V., Mur á nszky G., Nagy M., Kopcsik E., Krist á ly F., Fiser B. 等 9 人
出处	International Journal of Molecular Sciences 2022
DOI	10.3390/ijms23126535
原文链接	https://pmc.ncbi.nlm.nih.gov/articles/PMC9224514/
许可	https://creativecommons.org/licenses/by/4.0/Licensee MDPI, Basel, Switzerland. This article is an open access article di

摘要（原文节选）

Aniline (AN) is one of the most important compounds in the chemical industry and is prepared by the catalytic hydrogenation of nitrobenzene (NB). The development of novel, multifunctional catalysts which are easily recoverable from the reaction mixture is, therefore, of paramount importance. Compared to conventional filtration, magnetic separation is favored because it is cheaper and more facile. For satisfying these requirements, we developed manganese ferrite (MnFe2O4) – supported, magnetically separable palladium ⋯

数据表 · Table 1（7 行，含数值行 6 行）

Summary table for the physical and chemical properties of the magnetic nanoparticles prepared: mean particle sizes and the phase composition of the manganese ferrite and magnetite based on XRD results, the palladium contents based on ICP-OES analysis, ADA spec

	MnFe2O4	Fe3O4	Pd	ADAm2/g	Xmax, (t) (%)	Ymax.(t) (%)	Smax.(t) (%)	
d (nm)	wt%	d (nm)	wt%	d (nm)	wt%			
MnFe2O4 (573 K)	11 ± 3	100	⌀	⌀	⌀	⌀	⌀	34.3 a
MnFe2O4 (623 K)	12 ± 2	61.1	14 ± 3	38.9	⌀	⌀	⌀	93.4 a
MnFe2O4 (673 K)	13 ± 2	41.8	12 ± 3	48.2	⌀	⌀	⌀	94.8 a
Pd/MnFe2O4 (573 K)	10 ± 3	89.1	35 ± 5	3.3	4 ± 1	4.20	74	99.9(180 min)(303 K)
Pd/MnFe2O4 (623 K)	8 ± 2	66.0	15 ± 3	25.7	4 ± 1	4.64	69	99.9(40 min)(323 K)
Pd/MnFe2O4 (673 K)	10 ± 3	64.3	13 ± 2	20.3	6 ± 1	4.61	78	99.9(120 min)(323 K)

脚注（逐字）：a These parameters were measured at 240 min and 323 K.

正文对应句（逐字）：To check the catalytic activity of the supports, the palladium-free manganese ferrite samples were tested in nitrobenzene hydrogenation at 323 K temperature and 20 bar hydrogen pressure. All the samples turned out to be catalytically active. The highest nitrobenzene conversion (94.8 n/n%) was reache

本卡为 NCBI PMC 开放获取 XML
的逐字摘录（标题、作者、表格行列、脚注、正文句均未改写），用于参照集候选与覆盖面登记；未逐条人工核验，标记 imported_unchecked，不写入判定记录、不参与 ChemCritic 引擎的可比性判定。对外引用一律回到 DOI 原文核对页码与表号。