ChemCritic 文献证据卡

PMC9820898 | 烯烃复分解 | 采集状态 imported_unchecked

标题	Ring-Opening Metathesis Polymerization and Related Olefin Metathesis Reactions in Benzotrifluoride as an Environmentally Advantageous Medium †
作者	Kov á cs E., Balterer B., Anh Duc N., Szarka G., Owen M., Domj á n A. 等 9 人
出处	International Journal of Molecular Sciences 2022
DOI	10.3390/ijms24010671
原文链接	https://pmc.ncbi.nlm.nih.gov/articles/PMC9820898/
许可	https://creativecommons.org/licenses/by/4.0/Licensee MDPI, Basel, Switzerland. This article is an open access article di

摘要（原文节选）

A tremendous number of solvents, either as liquids or vapors, contaminate the environment on a daily basis worldwide. Olefin metathesis, which has been widely used as high-yielding protocols for ring-opening metathesis polymerization (ROMP), ring-closing metathesis (RCM), and isomerization reactions, is typically performed in toxic and volatile solvents such as dichloromethane. In this study, the results of our systematic experiments with the Grubbs G1, G2, and Hoveyda-Grubbs HG2 catalysts proved that benzotrifluor ⋯

数据表 · Table 2（6 行，含数值行 6 行）

The solvent, the catalyst type, the conversion, and the turnover number for the ring-opening metathesis polymerization of norbornene (c0 = 106 mM) conducted in benzotrifluoride and dichloromethane under a nitrogen atmosphere for 78 h.

Solvent	Catalyst	Conversion *	Turnover Number *
BTF	G1	0.77	385,100
DCM	G1	0.95	477,100
BTF	G2	>0.99	499,900
DCM	G2	>0.99	499,500
BTF	HG2	0.96	481,200
DCM	HG2	>0.99	499,800

脚注（逐字）：* Determined by 1H NMR measurements using anisole as an internal standard.

数据表 · Table 3（6 行，含数值行 6 行）

The solvent, the catalyst, rate constant, and the conversions after 20 min and 24 h in the ring-closing metathesis reactions of diethyl 2,2-diallylmalonate (c0 = 35.6 mM) in benzotrifluoride (BTF) and dichloromethane (DCM) using 1 mol% G1, G2, or HG2 as cataly

Solvent	Catalyst	k1(min − 1)	Conversion at20 min (%)	Conversion at24 h (%)
BTF	G1	0.019	21	55
DCM	G1	0.202	47	>99
BTF	G2	0.024	34	96
DCM	G2	0.005	7	>99
BTF	HG2	0.033	43	80
DCM	HG2	0.075	78	>99

本卡为 NCBI PMC 开放获取 XML
的逐字摘录（标题、作者、表格行列、脚注、正文句均未改写），用于参照集候选与覆盖面登记；未逐条人工核验，标记 imported_unchecked，不写入判定记录、不参与 ChemCritic 引擎的可比性判定。对外引用一律回到 DOI 原文核对页码与表号。