

## CORROSION ALLOWANCE AND REMAINING LIFE - STANDARD CS-12

Scope: carbon-steel pressure equipment in hydrocarbon service.

### 1. REMAINING LIFE

Remaining life (years) =  $(t_{\text{actual}} - t_{\text{min}}) / \text{corrosion rate (mm/year)}$ .

Use the thinnest reading at each condition monitoring location (CML).

### 2. INSPECTION INTERVAL

Next inspection interval = the lesser of half the remaining life and 10 years.

### 3. ACCEPTANCE

Equipment with remaining life under 2 years requires an engineering assessment and a documented approval before continued operation.