

PRESSURE VESSEL V-204 - UT THICKNESS SURVEY

Survey No: UT-2026-0311 Date: 03 Jul 2026 Surveyor: M. Iyer (Level II UT)
Vessel: V-204 LPG knock-out drum. MAWP 16.0 barg. Nominal shell thickness 14.0 mm.
Minimum required thickness (t-min) 10.9 mm. Corrosion allowance 3.0 mm.

READINGS

CML	LOCATION	2023 (mm)	2026 (mm)
CML-1	Top head	13.6	13.4
CML-2	Shell, north	13.1	12.6
CML-3	Shell, south	12.9	12.3
CML-4	Bottom head	12.2	11.6

FINDINGS

Worst case CML-4: loss of 0.6 mm in 3 years, corrosion rate 0.2 mm/year.
Remaining margin at CML-4 is 0.7 mm; remaining life 3.5 years.
Internal inspection recommended at the 2027 shutdown. Instrument nozzle N5 shows sensor fouling consistent with the PT-4471 calibration drift.