
	GILES CHEMICAL ~ PREMIER MAGNESIA		
	Company Form		
	Title: Film Check - Tech Film 50 Kg Checklist	Number: Q12-PR-100-022b	
	Owner: Louis Martin	Revision: 1	
	Effective Date: 01/30/07	Page: 1 of 1	

GILES CHEMICAL CORPORATION
WAYNESVILLE, NC

PAGE 1 OF 1

REPLACES:

POLY FILM SPECIFICATION

50 lb/22.7kg TEC EPSOM SALT

Material: 6.0 mil (0.006") $\pm 10\%$
White opaque co-extruded polyethylene sheeting with UV inhibitor and differential slip. LLDPE blend with mLLDPE in the skins and HDPE in the core.

Coefficient of Friction, Film-to-Film:	Inside:	0.20 to 0.35
	Outside:	0.40 to 0.60

Size Film Width = 35-1/2" $\pm 1/4$ "
Repeat Length = 25"- 1/4 $\pm 1/4$ "

Inks: PMS REFLEX BLUE BLACK

Use low-slip inks that are scuff and fade resistant.

Printing: 2 colors face.
Unwind Style #2
Do not treat 3" along each edge of the film.
Skip treat between impressions: 2 1/2" border on top and bottom equaling 5" of untreated area between print impressions

UPC code = 6 62835 11050 9

Photo-eye: 1/2" x 3" in Black,
Located 12-1/4" from center of film and 9- 1/2" from bottom of Imprint

Perforations: 100 Micron perforations; two 3-5" strips, 4-1/2" to 9-1/2" from each edge.

Rolls: 23-1/2" OD Rolls (approx 500 lb, 2670 impressions)
Wind on 3" ID cardboard cores, 35-1/2 wide. Roll edges to be flush with edge of core.