

## **SECTION 06 10 53 - MISCELLANEOUS ROUGH CARPENTRY**

### **PART 1 - GENERAL**

#### **1.1 SUMMARY**

- A. Provide the work of this Section in accordance with requirements of the Contract Documents.
- B. This Section includes, but is not limited to the following:
  - 1. Wood blocking and nailers.
  - 2. Wood furring and grounds.
  - 3. Plywood backing panels.

#### **1.2 DEFINITIONS**

- A. Miscellaneous Rough Carpentry: Carpentry work not specified in other Sections and not exposed, unless otherwise indicated.
- B. Dimension Lumber: Lumber of 2 inches nominal (38 mm actual) or greater size but less than 5 inches nominal (114 mm actual) size in least dimension.

#### **1.3 ACTION SUBMITTALS**

- A. Product Data: For each type of process and factory-fabricated product. Indicate component materials and dimensions and include construction and application details.
  - 1. Include data for wood-preservative treatment from chemical treatment manufacturer and certification by treating plant that treated materials comply with requirements. Indicate type of preservative used and net amount of preservative retained.
  - 2. Include data for fire-retardant treatment from chemical treatment manufacturer and certification by treating plant that treated materials comply with requirements. Include physical properties of treated materials based on testing by a qualified independent testing agency.
  - 3. For fire-retardant treatments, include physical properties of treated lumber both before and after exposure to elevated temperatures, based on testing by a qualified independent testing agency according to ASTM D5664.
  - 4. For products receiving a waterborne treatment, include statement that moisture content of treated materials was reduced to levels specified before shipment to Project site.
- B. Sustainable Design Submittals:
  - 1. Building Product Disclosure and Optimization - Sourcing of Raw Materials:
    - a. Leadership Extraction Practices
      - 1) Extended Producer Responsibility (EPR): Submit documentation indicating that manufacturers have a take back or recycling program for the product purchased.
      - 2) Wood Products: Certified by Forest Stewardship Council or USGBC approved equivalent.

- a) Chain-of-Custody Certificates: For certified wood products. Include statement of costs.
      - b) Chain-of-Custody Qualification Data: For manufacturer and vendor.
    - 3) Recycled Content: For products having recycled content, indicate percentages by weight of post-consumer and pre-consumer recycled content.
      - a) Include statement indicating costs for each product having recycled content.
    - b. Sourcing of Raw Materials: For products that are required to comply with requirements for regional materials, indicating location of material manufacturer and point of extraction, harvest, or recovery for each raw material.
      - 1) Include statement indicating distance to Project, cost for each regional material and the fraction by weight that is considered regional.
      - 2) Product Certificates: For materials manufactured within 100 miles of Project, indicating location of material manufacturer and point of extraction, harvest, or recovery for each raw material. Include distance to Project and cost for each raw material.
  - 2. Indoor Environmental Quality, Low Emitting Materials: Building Products must be tested and compliant with the California Department of Public-Health (CDPH) Standard Method V1.1-2010, using the applicable exposure scenario.
    - a. Paints, and Coatings: For wet applied on site products, include printed statement of VOC content, showing compliance with the applicable VOC limits of the California Air Resources Board (CARB) 2007, Suggested Control Measure (SCM) for Architectural Coatings, or the South Coast Air Quality Management District (SCAQMD) Rule 1113, effective June 3, 2011.
    - b. Adhesives and Sealants: For wet applied on site products, submit printed statement showing compliance with the applicable chemical content requirements of SCAQMD Rule 1168, effective July 1, 2005 and rule amendment date of January 7, 2005.
      - 1) Product Data: For installation adhesives, indicating VOC content.
    - c. Alternative tests for VOC above include ASTM D2369-10; ISO 11890 part 1; ASTM D6886-03; or ISO 11890-2.
    - d. Methylene Chloride and perchloroethylene may not be added to paints, coating, adhesive or sealants
    - e. Composite Wood: Submit documentation showing that wood used in the project has low formaldehyde emissions that meet the California Air Resources Board ATCM for formaldehyde requirements for ultra-low emitting formaldehyde (ULEF) resins or no added formaldehyde resins.
  - 3. Laboratory Test Reports: For installation adhesives, indicating compliance with requirements for low-emitting materials.
- C. Fabrication Engineering and Design Data Submittal: Submit for rough carpentry to verify compliance with performance requirements and design criteria, including analysis data signed and sealed by the qualified professional engineer responsible for their preparation.

#### 1.4 INFORMATIONAL SUBMITTALS

- A. Evaluation Reports: For the following, from ICC-ES:
  - 1. Preservative-treated wood.
  - 2. Fire-retardant-treated wood.
  - 3. Power-driven fasteners.

4. Post-installed anchors.
5. Metal framing anchors.

B. Sustainable Design Submittals:

1. Building Product Disclosure and Optimization - Environmental Product Declarations
  - a. Submit product specific type III EPDs or Industry wide (generic) EPDs, USGBC approved program declaration or products with a publicly available, critically reviewed life-cycle assessment conforming to ISO 14044 that have at least a cradle to gate scope.
2. Building Product Disclosure and Optimization - Material Ingredients
  - a. Material Ingredient Reporting: Submit documentation confirming chemical inventory of products to at least 0.1 % (1000ppm) with at least one of the following:
    - 1) Submit published manufacturer inventory of ingredients identified by name and Chemical Abstract Service Registration Number (CASRN)
    - 2) Submit documentation that product has been certified as Cradle-to-Cradle v3 at the Bronze Level or better
    - 3) Submit Declare product label indicating that all ingredients have been disclosed down to 1000 ppm or designated as Red List Free or Declared
    - 4) Living Product Challenge
    - 5) Product Lens Certification
    - 6) USGBC approved program.
  - b. Material Ingredient Optimization: Submit documentation confirming chemical inventory of products to at least 0.01 % (100ppm) and/or that has a compliant material ingredient optimization report with at least one of the following:
    - 1) Submit GreenScreen V1.2 Benchmark: Third party report prepared by a licensed GreenScreen List Translator, or a full GreenScreen Assessment.
    - 2) Submit third-party verified documentation that product has been certified as Cradle-to-Cradle v3 at the Bronze Level or better
    - 3) Submit third-party verified Cradle to Cradle v3 Material Health certificate at the Bronze Level or better
    - 4) Submit third-party verified Declare product label indicating that all ingredients have been disclosed down to 100 ppm
    - 5) Submit third-party verified documentation that product is Living Product Challenge certified with a Red List Free or LBC Red List Free Declare label.
    - 6) Submit documentation that product has a manufacturer prepared action plan with material inventory to at least 1000 ppm.

## 1.5 QUALITY ASSURANCE

- A. Testing Agency Qualifications: For testing agency providing classification marking for fire-retardant-treated material, an inspection agency acceptable to authorities having jurisdiction that periodically performs inspections to verify that the material bearing the classification marking is representative of the material tested.

## 1.6 DELIVERY, STORAGE, AND HANDLING

- A. Stack lumber flat with spacers beneath and between each bundle to provide air circulation.

- B. Protect lumber from weather by covering with waterproof sheeting, securely anchored. Provide for air circulation around stacks and under coverings.

## **PART 2 - PRODUCTS**

### **2.1 PERFORMANCE REQUIREMENTS**

- A. Fabrication Engineering and Design Data: Engage a qualified professional engineer, as defined in Section 01 33 16, "Fabrication Engineering Design Data," to design rough carpentry complying with requirements.

### **2.2 WOOD PRODUCTS, GENERAL**

- A. Regional Materials: Dimension lumber, except treated materials, shall be manufactured within 100 miles of Project site from materials that have been extracted, harvested, or recovered, as well as manufactured, within 100 miles of Project site.
- B. Certified Wood: Lumber and plywood shall be certified as "FSC Pure" or "FSC Mixed Credit" according to FSC STD-01-00 and FSC STD-40-004.
- C. Lumber: DOC PS 20 and applicable rules of grading agencies indicated. If no grading agency is indicated, provide lumber that complies with the applicable rules of any rules-writing agency certified by the ALSC Board of Review. Provide lumber graded by an agency certified by the ALSC Board of Review to inspect and grade lumber under the rules indicated.
  - 1. Factory mark each piece of lumber with grade stamp of grading agency.
  - 2. For exposed lumber indicated to receive a stained or natural finish, mark grade stamp on end or back of each piece or omit grade stamp and provide certificates of grade compliance issued by grading agency.
  - 3. Dress lumber, S4S, unless otherwise indicated.
- D. Maximum Moisture Content of Lumber: 15 percent for 2-inch nominal (38-mm actual) thickness or less, 19 percent for more than 2-inch nominal (38-mm actual) thickness unless otherwise indicated.

### **2.3 WOOD-PRESERVATIVE-TREATED MATERIALS**

- A. Preservative Treatment by Pressure Process: AWP A U1; Use Category UC2 for interior construction not in contact with ground, Use Category UC3b for exterior construction not in contact with ground, and Use Category UC4a for items in contact with ground.
  - 1. Preservative Chemicals: Acceptable to authorities having jurisdiction and containing no arsenic or chromium.
  - 2. For exposed items indicated to receive a stained or natural finish, chemical formulations shall not require incising, contain colorants, bleed through, or otherwise adversely affect finishes.
- B. Kiln-dry lumber after treatment to a maximum moisture content of 19 percent. Do not use material that is warped or does not comply with requirements for untreated material.

- C. Mark lumber with treatment quality mark of an inspection agency approved by the ALSC Board of Review except as otherwise specified.
- D. Application:
  - 1. Treat items indicated on Drawings, and the following:
    - a. Wood cants, nailers, curbs, equipment support bases, blocking, stripping, and similar members in connection with roofing, flashing, vapor barriers, and waterproofing.
    - b. Wood blocking, furring, and similar concealed members in contact with masonry or concrete.
    - c. Wood framing members that are less than 18 inches (460 mm) above the ground in crawlspaces or unexcavated areas.

## 2.4 FIRE-RETARDANT-TREATED MATERIALS

- A. General: Where fire-retardant-treated materials are indicated, materials shall comply with requirements in this article, that are acceptable to authorities having jurisdiction, and with fire-test-response characteristics specified as determined by testing identical products per test method indicated by a qualified testing agency.
- B. Fire-Retardant-Treated Lumber and Plywood by Pressure Process: Products with a flame-spread index of 25 or less when tested according to ASTM E84, and with no evidence of significant progressive combustion when the test is extended an additional 20 minutes, and with the flame front not extending more than 10.5 feet (3.2 m) beyond the centerline of the burners at any time during the test.
  - 1. Treatment shall not promote corrosion of metal fasteners.
  - 2. Exterior Type: Treated materials shall comply with requirements specified above for fire-retardant-treated lumber and plywood by pressure process after being subjected to accelerated weathering according to ASTM D2898. Use for exterior locations and where indicated. Provide one of the following:
    - a. FRX; Lonza
    - b. Exterior Fire X; Hoover Treated Wood Products
  - 3. Interior Type A: Treated materials shall have a moisture content of 28 percent or less when tested according to ASTM D3201 at 92 percent relative humidity. Use where exterior type is not indicated. Provide one of the following:
    - a. D-Blaze; Viance.
    - b. Dricon; Lonza.
    - c. Pyro-guard; Hoover Treated Wood Products, Inc.
- C. Kiln-dry lumber after treatment to a maximum moisture content of 19 percent. Kiln-dry plywood after treatment to a maximum moisture content of 15 percent.
- D. Identify fire-retardant-treated wood with appropriate classification marking of qualified testing agency unless otherwise specified,
- E. For exposed items indicated to receive a stained or natural finish, chemical formulations shall not bleed through, contain colorants, or otherwise adversely affect finishes.
- F. Application:
  - 1. Treat items indicated on Drawings, and the following:

- a. Concealed blocking.
- b. Plywood backing panels.

## **2.5 MISCELLANEOUS LUMBER**

- A. General: Provide miscellaneous lumber indicated and lumber for support or attachment of other construction, including the following:
  - 1. Blocking, minimum 1-1/2 inches x 5 1/2 inches ( 2 x 6 dimensional lumber) at roof edge conditions.
  - 2. Nailers, minimum 1-1/2 inches x 5 1/2 inches ( 2 x 6 dimensional lumber) at roof edge conditions.
  - 3. Rooftop equipment bases and support curbs.
  - 4. Cants.
  - 5. Furring.
  - 6. Grounds.
  - 7. Utility shelving.
- B. Dimension Lumber Items: Construction or No. 2 grade lumber of any of the following species:
  - 1. Hem-fir (north); NLGA.
  - 2. Mixed southern pine or southern pine; SPIB.
  - 3. Spruce-pine-fir; NLGA.
  - 4. Hem-fir; WCLIB or WWP.
  - 5. Spruce-pine-fir (south); NeLMA, WCLIB, or WWP.
  - 6. Western woods; WCLIB or WWP.
  - 7. Northern species; NLGA.
  - 8. Eastern softwoods; NeLMA.
- C. Concealed Boards: 15 percent maximum moisture content of any of the following species and grades:
  - 1. Mixed southern pine or southern pine, No. 3 grade; SPIB.
  - 2. Eastern softwoods, No. 3 Common grade; NELMA.
  - 3. Northern species, No. 3 Common grade; NLGA.
  - 4. Western woods, Standard or No. 3 Common grade; WCLIB or WWP.
- D. For blocking not used for attachment of other construction, Utility, Stud, or No. 3 grade lumber of any species may be used provided that it is cut and selected to eliminate defects that will interfere with its attachment and purpose.
- E. For blocking and nailers used for attachment of other construction, select and cut lumber to eliminate knots and other defects that will interfere with attachment of other work.
- F. Fasten to meet wind load requirements in structural drawings.
- G. For furring strips for installing plywood or hardboard paneling, select boards with no knots capable of producing bent-over nails and damage to paneling.

## **2.6 PLYWOOD BACKING PANELS**

- A. Communications and Electrical Equipment Backing Panels: Plywood, DOC PS 1, Exposure 1, C-D Plugged, fire-retardant treated, in thickness indicated or, if not indicated, not less than 3/4-inch (19-mm) nominal thickness.

## **2.7 FASTENERS**

- A. General: Provide fasteners of size and type indicated that comply with requirements specified in this article for material and manufacture.
  - 1. Where carpentry is exposed to weather, in ground contact, pressure-preservative treated, or in area of high relative humidity, provide fasteners of Type 304 stainless steel.
- B. Nails, Brads, and Staples: ASTM F1667.
- C. Screws for Fastening to Metal Framing: ASTM C954, length as recommended by screw manufacturer for material being fastened.
- D. Power-Driven Fasteners: Anchor bolt and sleeve assembly of material indicated below with capability to sustain, without failure, a load equal to 6 times the load imposed when installed in unit masonry assemblies and equal to 10 times the load imposed when installed in concrete as determined by testing per ASTM E488 conducted by a qualified independent testing and inspecting agency. Fastener systems with an evaluation report acceptable to authorities having jurisdiction, based on ICC-ES AC70.
- E. Post-Installed Expansion Anchors: Anchor bolt and sleeve assembly of material indicated below with capability to sustain, without failure, a load equal to 6 times the load imposed when installed in unit masonry assemblies and equal to 4 times the load imposed when installed in concrete as determined by testing per ASTM E488 conducted by a qualified independent testing and inspecting agency. Fastener systems with an evaluation report acceptable to authorities having jurisdiction, based on ICC-ES AC58 or ICC-ES AC308 as appropriate for the substrate.
  - 1. Material:
    - a. Interior: Carbon-steel components, zinc plated to comply with ASTM B633, Class Fe/Zn 5.
    - b. Exterior: Stainless steel with bolts and nuts complying with ASTM F593 and ASTM F594, Alloy Group 1 or 2 (ASTM F738M and ASTM F836M, Grade A1 or A4).

## **2.8 MISCELLANEOUS MATERIALS**

- A. Adhesives for Gluing Furring to Concrete or Masonry: Formulation complying with ASTM D3498 that is approved for use indicated by adhesive manufacturer.
  - 1. Adhesives shall have a VOC content of 70g/L or less.
- B. Flexible Flashing: Composite, self-adhesive, flashing product consisting of a pliable, butyl rubber or rubberized-asphalt compound, bonded to a high-density polyethylene film, aluminum foil, or spunbonded polyolefin to produce an overall thickness of not less than 0.025 inch (0.6 mm).

## **2.9 LOW-EMITTING MATERIALS**

- A. Architectural paints and coatings wet-applied inside the weather-proofing system must meet the VOC general emissions testing criteria of CDPH Standard Method v1.2.
- B. All paints and coatings wet-applied inside the weather-proofing system must have VOC content in compliance with the applicable VOC limits (g/L) found in tables in Division 01, Section 01 81 13 "Sustainable Design Requirements - LEED v4 BD+C."

- C. Adhesives and Sealants wet-applied inside the weather-proofing system must meet the VOC general emissions testing criteria of CDPH Standard Method v1.2.
- D. All adhesives and sealants wet-applied inside the weather-proofing system must have VOC content in compliance with the applicable VOC limits (g/L) found in tables in Division 01 Section 01 81 13.14 "Sustainable Design Requirements - LEED v4 BD+C."
- E. Provide non-structural composite wood products that contain either No Added Formaldehyde (NAF) resins or Ultra Low Emitting Formaldehyde (ULEF) resins per CARB ATCM criteria noted in Division 01, Section 01 81 13.14 "Sustainable Design Requirements - LEED v4 BD+C."
- F. Provide structural composite wood products tested per EN 717-1:2014 as compliant with emissions class E1. Structural composite wood, with no added urea-formaldehyde resins or surface treatments, and certified per the following: PS 1-09 or PS 2-10 for plywood, PS 2-10 for OSB, ASTM D 5446-13 for structural composite lumber.

### **PART 3 - EXECUTION**

#### **3.1 INSTALLATION, GENERAL**

- A. Framing Standard: Comply with AF&PA's WCD 1, "Details for Conventional Wood Frame Construction," unless otherwise indicated.
- B. Set carpentry to required levels and lines, with members plumb, true to line, cut, and fitted. Fit carpentry accurately to other construction. Locate furring, nailers, blocking, grounds, and similar supports to comply with requirements for attaching other construction.
- C. Install plywood backing panels by fastening to studs; coordinate locations with utilities requiring backing panels. Install fire-retardant-treated plywood backing panels with classification marking of testing agency exposed to view.
- D. Install metal framing anchors to comply with manufacturer's written instructions. Install fasteners through each fastener hole.
- E. Do not splice structural members between supports unless otherwise indicated.
- F. Provide blocking and framing as indicated and as required to support facing materials, fixtures, specialty items, and trim.
  - 1. Provide metal clips for fastening gypsum board at corners and intersections where framing or blocking does not provide a surface for fastening edges of panels. Space clips not more than 16 inches (406 mm) on center.
- G. Provide fire blocking in furred spaces, stud spaces, and other concealed cavities as indicated and as follows:
  - 1. Fire block furred spaces of walls, at each floor level, at ceiling, and at not more than 96 inches (2438 mm) on center with solid wood blocking or noncombustible materials accurately fitted to close furred spaces.
- H. Sort and select lumber so that natural characteristics do not interfere with installation or with fastening other materials to lumber. Do not use materials with defects that interfere with function



of member or pieces that are too small to use with minimum number of joints or optimum joint arrangement.

- I. Comply with AWPAC M4 for applying field treatment to cut surfaces of preservative-treated lumber.
  - 1. Use inorganic boron for items that are continuously protected from liquid water.
  - 2. Use copper naphthenate for items not continuously protected from liquid water.
- J. Where wood-preservative-treated lumber is installed adjacent to metal decking, install continuous flexible flashing separator between wood and metal decking.
- K. Securely attach rough carpentry work to substrate by anchoring and fastening as indicated, complying with the following:
  - 1. Table 2304.10.1, "Fastening Schedule," in ICC's International Building Code.
  - 2. ICC-ES evaluation report for fastener.
  - 3. Engineered roof edge nailer fastening patterns to accommodate project design wind loads.
  - 4. Structural calculations and details of anchoring systems including type, size, and spacing of fasteners to cold formed metal framing and other scenarios not covered by FM 1-49.
- L. Use steel common nails unless otherwise indicated. Select fasteners of size that will not fully penetrate members where opposite side will be exposed to view or will receive finish materials. Make tight connections between members. Install fasteners without splitting wood. Drive nails snug but do not countersink nail heads unless otherwise indicated.

### **3.2 WOOD BLOCKING AND NAILER INSTALLATION**

- A. Install where indicated and where required for attaching other work. Form to shapes indicated and cut as required for true line and level of attached work. Coordinate locations with other work involved.
- B. Attach items to substrates to support applied loading. Fasten blocking and nailers at exterior to the building to meet wind loading in accordance with structural drawings.
- C. Recess bolts and nuts flush with surfaces unless otherwise indicated.

### **3.3 WOOD FURRING INSTALLATION**

- A. Install level and plumb with closure strips at edges and openings. Shim with wood as required for tolerance of finish work.

### **3.4 PROTECTION**

- A. Protect wood that has been treated with inorganic boron (SBX) from weather. If, despite protection, inorganic boron-treated wood becomes wet, apply EPA-registered borate treatment. Apply borate solution by spraying to comply with EPA-registered label.
- B. Protect miscellaneous rough carpentry from weather. If, despite protection, miscellaneous rough carpentry becomes wet, apply EPA-registered borate treatment. Apply borate solution by spraying to comply with EPA-registered label.

**END OF SECTION**