

Radiosensitization using gold nanoparticles


Lies Deceuninck en Hannelore Verhoeven

Bachelor Thesis 2016

As. Bert De Roo, Mattias

Vervaele, Stephanie Seré


Introduction
Synthesis GNP
Chemical protocol
Size GNP
Stabilization
Characterization



Cancer treatment


- Chemotherapy
- Surgery
- **Radiation therapy**

Energy $\sim MeV$




Radiosensitization with $\text{GNP}_{\text{E}} \sim \text{keV}$

Photoelectric absorption



Compton effect




Why gold?


- High atomic number (79)
- Low toxicity

Targeting

Passive targeting
PEG coating




Active targeting
Antibodies



Goal

1. Synthesis
2. Characterization
3. Radiosensitization





TEM image analysis to determine core diameter




Gold ions: HAuCl_4 solution

Reducing agent: $\text{Na}_3\text{C}_6\text{H}_5\text{O}_7$

Chemical protocol




Size GNP




Citrate 1%

100ml HAuCl₄ 0.01%

Zeta Potential




Laser Doppler Gel electrophoresis






$$\zeta = \frac{2\eta v}{3E\epsilon} \quad |\zeta| \geq 30\text{mV}$$


Zeta Potential: Results



Functionalization PEG




20k, 10k, 5k, 1k



UV-Vis spectroscopy


1. Add PEG
2. Size GNP
3. Add NaCl
4. Size GNP



bigger size \rightarrow too little PEG
same size \rightarrow enough PEG


Results

GNP no PEG




Results

15nm GNP 20k PEG for different PEG/GNP




Results

15nm GNP 20k PEG for different PEG/GNP



Results

15nm GNP 20k PEG for different PEG/GNP



Overview

Introduction

Synthesis GNP

Chemical Protocol

Size GNP

Stabilization

Characterization

Size GNP


Chemical Protocol

UV-VIS


TEM

Hydrodynamic Radius



DLS



Dynamic light scattering (DLS)




Hydrodynamic radius (R_h)
 \rightarrow Rayleigh scattering




Results

Functionalisation no PEG



Results

Functionalisation 20k PEG




Results

Functionalization 15nm 20k PEG

Proportion (PEG/GNP)	Average
5/10	51.93 ± 2.76
6/10	80.89 ± 14.64
7/10	65.24 ± 14.32
8/10	83.91 ± 18.42
9/10	

Original functionalization 20k (8/10)




Results

Functionalization 15nm 20k PEG

Proportion (PEG/GNP)	Average	Average (centrifuge)
5/10	51.93 ± 2.76	68.70 ± 7.99
6/10	80.89 ± 14.64	65.16 ± 11.61
7/10	65.24 ± 14.32	57.73 ± 7.72
8/10	83.91 ± 18.42	72.36 ± 10.44
9/10		56.54 ± 3.91

Original functionalization 20k (8/10)



Conclusion

- Synthesis of GNP
- Characterization
- Stabilization with neutral PEG
- Stabilization with positively charged PEG
- X-Rays
- Analyze effect on DNA
- Solve problem with DLS

