

All Aluminium Alloy Conductors (AAAC) as per IS 398 (Part IV)

Actual Area	Stranding		Diameter of Complete Conductor	Weight	Rated Strength	DC Resistance at 20°C	Current Capacity	
	No. of Aluminium Wires	Individual Wire Diameter					at 75°C	at 80°C
(sq.mm.)	(No.)	(mm)	(mm)	(kg/km)	kn	(Ω /km)	(ampere)	(ampere)
22	7	2.00	6.00	60.16	6.45	1.5410	91	108
34	7	2.50	7.50	94.00	10.11	0.9900	118	141
55	7	3.15	9.45	149.20	16.03	0.6210	156	188
80	7	3.81	11.43	218.26	23.41	0.4250	195	237
100	7	4.26	12.78	272.86	29.26	0.3390	223	271
125	19	2.89	14.45	342.51	36.64	0.2735	254	310
148	19	3.15	15.75	406.91	43.50	0.2290	281	345
173	19	3.40	17.00	474.02	50.54	0.1969	307	378
200	19	3.66	18.30	549.40	58.66	0.1710	334	412
232	19	3.94	19.70	636.67	68.05	0.1471	364	451
288	37	3.15	22.05	794.05	84.71	0.1182	412	515
346	37	3.45	24.15	952.56	101.58	0.0984	457	575
400	37	3.71	25.97	1101.63	117.40	0.0829	503	635
465	37	4.00	28.00	1280.50	136.38	0.0734	539	684
525	61	3.31	29.79	1448.39	146.03	0.0651	576	734
570	61	3.45	31.05	1573.71	158.66	0.0598	603	772
604	61	3.55	31.95	1666.00	167.99	0.0568	620	796
642	61	3.66	32.94	1771.36	178.43	0.0534	641	825
695	61	3.81	34.29	1919.13	193.25	0.0492	670	864
767	61	4.00	36.00	2115.54	213.05	0.0446	705	914