

All Aluminium Conductors (AAC) as per IS 398 (Part I)

Nominal Aluminium Area	Sectional Area	Stranding		Diameter of Complete Conductor	Weight	Rated Strength at 20°C	DC Resistance at 20°C	Current Capacity	
		No. of Aluminium Wires	Individual Wire Diameter					at 75°C	at 80°C
(sq.mm.)	(sq.mm.)	(No.)	(mm)	(mm)	(kg/km)	kN	(Ω /km)	(ampere)	(ampere)
25	26.85	7	2.21	6.63	74	4.52	1.0960	109	129
50	52.83	7	3.10	9.30	145	8.25	0.5525	163	196
100	106.00	7	4.39	13.17	290	15.96	0.2752	247	300
150	150.90	19	3.18	15.90	415	23.28	0.1942	303	372
240	237.60	19	3.99	19.95	654	35.74	0.1235	394	488
300	322.70	19	4.65	23.25	888	48.74	0.0911	468	586