

Aluminium Conductor Steel Reinforced (ACSR) as per IS 398 (Part II)

Nominal Aluminium Area	Sectional Area	Stranding				Diameter of Complete Conductor	Weight	Rated Strength	DC Resistance at 20°C	Current Capacity	
		No. of Wires		Wire Diameter						at 75°C	at 80°C
		Aluminium	Steel	Aluminium	Steel						
(sq.mm.)	(sq.mm.)	(No.)	(No.)	(mm)	(mm)	(mm)	(kg/km)	(kn)	(Ω/km)	(ampere)	(ampere)
10	12.37	6	1	1.50	1.50	4.50	43	3.97	2.7800	59	69
18	21.12	6	1	1.96	1.96	5.88	73	6.74	1.6180	81	97
20	24.48	6	1	2.11	2.11	6.33	85	7.61	1.3940	89	106
30	36.88	6	1	2.59	2.59	7.77	128	11.12	0.9289	114	136
50	61.70	6	1	3.35	3.35	10.05	214	18.25	0.5524	155	186
80	91.97	6	1	4.09	4.09	12.27	319	26.91	0.3712	196	237
100	118.50	6	7	4.72	1.57	14.15	394	32.41	0.2792	231	282
150	194.90	30	7	2.59	2.59	18.13	726	67.34	0.1871	315	389
200	261.50	30	7	3.00	3.00	21.00	974	89.67	0.1390	374	465
400	425.20	42	7	3.50	1.96	26.88	1281	88.79	0.0731	525	664
420	484.50	54	7	3.18	3.18	28.62	1621	130.32	0.0687	546	693
520	597.00	54	7	3.53	3.53	31.77	1998	159.60	0.0560	612	783
560	591.70	42	7	4.13	2.30	31.68	1781	120.16	0.0523	631	808