

Technical Data Sheet (TDS)

High-Performance Regenerated Cellulose Casing

1. Product Overview

Product Name: HAITU High-Performance Regenerated Cellulose Casing
Application: Designed for high-speed automated peeling lines (e.g., Frankfurters, Hot Dogs, Sausages).
Key Characteristics: * Optimized for high-speed automated machinery (Handtmann, Vemag, etc.)

- Excellent smoke permeability & deep color transfer
- Superior dimensional stability for precise weight control
- Clean, effortless peeling performance

2. Physical & Technical Specifications

Property	Value / Range	Test Method
Caliber (Diameter)	13mm – 40mm	Standard Gauge
Wall Thickness	0.035mm – 0.055mm	Micrometer
Tensile Strength (MD)	> 45 N/15mm	ISO 527
Tensile Strength (CD)	> 20 N/15mm	ISO 527
Elongation at Break (MD)	< 20%	ISO 527
Elongation at Break (CD)	< 30%	ISO 527
Water Vapor Permeability	High (Optimized)	ASTM E96
Smoke Permeability	Excellent	Internal Standard
Shrinkage (at 80°C)	3% – 5%	Internal Standard

3. Processing Recommendations

- **Preparation:** * *Pre-moistened grade:* Ready to use, no soaking required.
 - *Dry grade:* Soak in water at 20-30°C for 20-30 minutes before filling.
- **Filling Pressure:** Ensure filling pressure does not exceed the mechanical limit of the casing (typically < 0.2 MPa, varies by caliber).
- **Peeling:** Recommended for steam or dry peeling lines. Maintain peeling temperature between 10°C – 15°C for maximum efficiency.

4. Storage & Shelf Life

- **Storage Environment:** Store in a cool, dry, well-ventilated area. Protect from direct sunlight and extreme humidity.
- **Recommended Temp:** 5°C – 25°C.
- **Shelf Life:** 24 months from the date of manufacture when kept in original sealed packaging.

5. Regulatory Compliance

- ☐ Food Grade Certified
- ☐ BRC / IFS / FDA Compliant
- *Note: Please contact our technical support team for specific batch certificates.*

HAITU CASING SOLUTIONS *Your partner in high-efficiency food processing.* [Website URL] | [Contact Email] | [Phone Number]

- 官方网站: www.haitucasing.com
- 技术支持: sales@haitucasing.com
- 联系手机: +86 15092056506

title: 纤维素肠衣 - 技术参数表 (TDS) date: 2026-06-09

技术参数表 (TDS)

高性能再生纤维素肠衣

1. 产品概述

产品名称: HAITU 高性能再生纤维素肠衣
应用范围: 专为高速自动化剥离生产线设计 (如: 法兰克福香肠、热狗、小香肠)。
核心特性: * 适配高速自动化生产设备 (如 Handtmann, Vemag 等)

- 优异的烟熏渗透性, 确保色泽深邃均匀
- 卓越的尺寸稳定性, 保障精确的定量灌装
- 特殊表面处理, 剥离顺滑、快速

2. 物理与技术规格

项目 (Property)	数值范围 (Value / Range)	检测标准 (Test Method)
口径 (Caliber)	13mm – 40mm	标准量规
壁厚 (Wall Thickness)	0.035mm – 0.055mm	测微计
纵向抗张强度 (Tensile Strength MD)	> 45 N/15mm	ISO 527
横向抗张强度 (Tensile Strength CD)	> 20 N/15mm	ISO 527

项目 (Property)	数值范围 (Value / Range)	检测标准 (Test Method)
纵向断裂伸长率 (Elongation MD)	< 20%	ISO 527
横向断裂伸长率 (Elongation CD)	< 30%	ISO 527
水汽渗透率 (WVTR)	高 (优化水分控制)	ASTM E96
烟熏渗透性 (Smoke Permeability)	极佳 (均匀上色)	企业标准
收缩率 (Shrinkage at 80°C)	3% – 5%	企业标准

3. 工艺建议

- **准备工作：** * *预润湿型*：开袋即用，无需浸泡。
 - *干型*：灌装前需在 20-30°C 的水中浸泡 20-30 分钟。
- **灌装压力：** 请确保灌装压力不超过肠衣的机械极限（通常 < 0.2 MPa，具体视口径而定）。
- **剥离工艺：** 适用于蒸汽剥离或干式剥离生产线。建议剥离温度保持在 10°C – 15°C，以获得最佳生产效率。

4. 储存与保质期

- **储存环境：** 储存于阴凉、干燥、通风良好处。避免阳光直射和极端潮湿。
- **推荐温度：** 5°C – 25°C。
- **保质期：** 在原密封包装条件下，自生产日期起 24 个月。

5. 合规性声明

- ☐ 符合食品接触安全标准
- ☐ BRC / IFS / FDA 合规
- *注：如需特定批次的质检证明，请联系我们的技术支持团队。*

HAITU CASING SOLUTIONS 高效率食品加工合作伙伴

- 官方网站: www.haitucasing.com
- 技术支持: sales@haitucasing.com
- 联系手机: +86 15092056506