A Mechanistic Model for Radiation-Induced Segregation Controlled Grain-Boundary Oxidation in Austenitic Stainless Steels

Zhuo Wang Md Shahrier Hasan Jaime Marian

October 12, 2026

1 Introduction

2 Model Formulation and Calibration

The model consists of two components: a radiation-induced segregation (RIS) model for the evolving GB chemistry and a reduced-dimensional oxidation model for oxygen transport, consumption, and oxide growth. The RIS-predicted Cr, Ni, Si, and Fe concentrations provide the local alloy composition for the oxidation model. Oxygen transport along the boundary is solved for the cross-section-averaged concentration of the oxidized zone, and the delivery of oxygen to the oxide/metal interface is closed by the fundamental mode of the steady diffusion equation in the cross-section. The oxide composition determines the effective oxygen diffusivity through an effective-medium treatment, which controls the local oxygen consumption and oxide growth rate. The formulations of the two components are described below.

Figure 2 summarises the model. The computational domain, Fig. 2a, is a grain boundary that opens onto the surface exposed to the primary water. Oxygen enters at the mouth through the surface film and migrates along the boundary within the oxidized zone, whose half-width grows as the oxide thickens. Only the half-domain on one side of the boundary is simulated, the other half following by symmetry.

The boundary acts as a sink of finite efficiency for the vacancies and self-interstitials produced by irradiation, Fig. 2b. The resulting redistribution




Figure 1: Physical picture of intergranular oxidation in primary water without (a–c) and with (d–f) prior irradiation. (a) Solution-annealed boundary with uniform chemistry. (b) Oxygen entering at the boundary mouth oxidizes Cr selectively and forms a Cr-rich intergranular oxide. (c) The Cr-rich oxide limits oxygen transport along the boundary and the penetration stays shallow. (d) Irradiation drives point defects to the boundary and the resulting radiation-induced segregation depletes Cr and enriches Ni and Si. (e) On exposure the Cr-depleted boundary forms a Cr-poor, Fe-rich oxide, and the segregated Si oxidizes and dissolves, leaving pores. (f) The degraded oxide transports oxygen faster along the boundary and the oxide penetrates deeper.




Figure 2: Overview of the model: (a) physical picture and computational domain, (b) radiation-induced segregation, (c) oxygen transport across the oxide and the interfacial reactions, and (d) coupling between the two components.

depletes Cr and enriches Ni and Si at the boundary, and the imbalance between the two defect fluxes gives the segregation contribution $\mathbf{v}_{\mathrm{lat}}^{\mathrm{RIS}} = \mathbf{J}_{\mathrm{V}} - \mathbf{J}_{\mathrm{I}}$ to the lattice velocity; the profiles shown are calculated, mirrored about the boundary and convolved with a 1 nm FWHM Gaussian. At a given depth, Fig. 2c, the oxygen delivered along the boundary reaches the advancing oxide/metal interface through the oxide cross-section and is partitioned there among the four oxide phases; the metal swept by the front is either oxidized, rejected into the metal, or carried away through the oxide, and the net removal sets the oxidation contribution v_{ox}. The two components are coupled as shown in Fig. 2d: irradiation fixes the boundary chemistry and part of the lattice velocity, the boundary chemistry controls the interfacial reaction rates, and the oxide that forms feeds back on the oxygen supply through its thickness and its effective diffusivity.

Notation. Alloying-element indices are $i, j \in \{\mathrm{Cr}, \mathrm{Ni}, \mathrm{Si}, \mathrm{Fe}\}$; oxide-phase indices are $k \in \{\mathrm{Cr_2O_3}, \mathrm{Fe_3O_4}, \mathrm{FeCr_2O_4}, \mathrm{SiO_2}\}$. Superscripts V and I denote quantities associated with vacancies and self-interstitials; the superscript GB denotes a value taken on the grain boundary. C is a site fraction, $\mathbf{J}$ a flux in the two-dimensional metal domain, and J a flux on the one-dimensional grain-boundary line. The coordinate x is normal to the boundary and y runs along it.

2.1 Radiation-Induced Segregation Model

The RIS model is based on solving a set of coupled mass-conservation equations for the alloying elements (Cr, Ni, Si, and Fe) and point defects (vacancies and self-interstitials). For each alloying element i, the concentration evolves according to

$$\frac{\partial C_i}{\partial t} = -\nabla \cdot \mathbf{J}_i. \tag{1}$$

The site fractions of vacancies and self-interstitials are governed separately by

$$\frac{\partial C_{\mathrm{V}}}{\partial t} = -\nabla \cdot \mathbf{J}_{\mathrm{V}} + \epsilon K_0 - R\, C_{\mathrm{I}} C_{\mathrm{V}}, \tag{2}$$

$$\frac{\partial C_{\mathrm{I}}}{\partial t} = -\nabla \cdot \mathbf{J}_{\mathrm{I}} + \epsilon K_0 - R\, C_{\mathrm{I}} C_{\mathrm{V}}, \tag{3}$$

where C_{V} and C_{I} are the vacancy and self-interstitial site fractions, ϵ is the damage efficiency, K_0 is the radiation dose rate, and R is the vacancy–interstitial recombination rate coefficient. The flux of each alloying element carried by each defect mechanism is

$$\mathbf{J}_i^{\mathrm{V}} = -\sum_j L_{ij}^{\mathrm{V}} \nabla(\mu_j - \mu_{\mathrm{V}}) \,, \tag{4}$$

$$\mathbf{J}_i^{\mathrm{I}} = -\sum_j L_{ij}^{\mathrm{I}} \nabla(\mu_j + \mu_{\mathrm{I}}) \,, \tag{5}$$

with the Onsager coefficients

$$L_{ii}^{\mathrm{V}} = \frac{C_i D_i^{\mathrm{V}} C_{\mathrm{V}}}{k_B T} \left(1 + \frac{1 - f_0^{\mathrm{V}}}{f_0^{\mathrm{V}}} \frac{C_i D_i^{\mathrm{V}}}{\sum_m C_m D_m^{\mathrm{V}}}\right), \tag{6}$$

$$L_{ij}^{\mathrm{V}} = L_{ji}^{\mathrm{V}} = \frac{1 - f_0^{\mathrm{V}}}{f_0^{\mathrm{V}}} \frac{C_i D_i^{\mathrm{V}} \, C_j D_j^{\mathrm{V}} \, C_{\mathrm{V}}}{k_B T \sum_m C_m D_m^{\mathrm{V}}}, \qquad i \neq j, \tag{7}$$

$$L_{ii}^{\mathrm{I}} = \frac{C_i D_i^{\mathrm{I}} C_{\mathrm{I}}}{k_B T} \left(1 + \frac{1 - f_0^{\mathrm{I}}}{f_0^{\mathrm{I}}} \frac{C_i D_i^{\mathrm{I}}}{\sum_m C_m D_m^{\mathrm{I}}}\right), \tag{8}$$

$$L_{ij}^{\mathrm{I}} = L_{ji}^{\mathrm{I}} = \frac{1 - f_0^{\mathrm{I}}}{f_0^{\mathrm{I}}} \frac{C_i D_i^{\mathrm{I}} \, C_j D_j^{\mathrm{I}} \, C_{\mathrm{I}}}{k_B T \sum_m C_m D_m^{\mathrm{I}}}, \qquad i \neq j, \tag{9}$$

where D_i^{V} and D_i^{I} are the mechanism-specific diffusion coefficients of element i, and f_0^{V} and f_0^{I} are the corresponding correlation factors. The net defect fluxes follow from conservation of lattice sites,

$$\mathbf{J}_{\mathrm{V}} = -\sum_i \mathbf{J}_i^{\mathrm{V}}, \tag{10}$$

$$\mathbf{J}_{\mathrm{I}} = \sum_i \mathbf{J}_i^{\mathrm{I}}, \tag{11}$$

and give rise to a lattice velocity

$$\mathbf{v}_{\mathrm{lat}}^{\mathrm{RIS}} = \mathbf{J}_{\mathrm{V}} - \mathbf{J}_{\mathrm{I}}. \tag{12}$$

Grain-boundary sink condition. The boundary is treated as a sink of finite efficiency for both point defects. At the boundary plane the defect fluxes obey the Robin conditions

$$\mathbf{J}_{\mathrm{V}} \cdot \hat{\mathbf{e}}_x \big|_{x=0} = k_{\mathrm{V}}^{\mathrm{GB}} \left(C_{\mathrm{V}}\big|_{x=0} - C_{\mathrm{V}}^{\mathrm{eq}}\right), \tag{13}$$

$$\mathbf{J}_{\mathrm{I}} \cdot \hat{\mathbf{e}}_x \big|_{x=0} = k_{\mathrm{I}}^{\mathrm{GB}} \left(C_{\mathrm{I}}\big|_{x=0} - C_{\mathrm{I}}^{\mathrm{eq}}\right), \tag{14}$$

where $C_{\mathrm{V}}^{\mathrm{eq}}$ and $C_{\mathrm{I}}^{\mathrm{eq}}$ are the thermal-equilibrium site fractions and $k_{\mathrm{V}}^{\mathrm{GB}}$, $k_{\mathrm{I}}^{\mathrm{GB}}$ are the boundary transfer coefficients of the two defects. The perfect-sink (Dirichlet) condition $C_{\mathrm{V}} = C_{\mathrm{V}}^{\mathrm{eq}}$, $C_{\mathrm{I}} = C_{\mathrm{I}}^{\mathrm{eq}}$ is recovered for $k^{\mathrm{GB}} \to \infty$. With the Dirichlet condition the defect gradients at the boundary, and with them both the magnitude and the width of the segregation profiles, do not converge under mesh refinement, a behaviour also reported for other Onsager-type RIS models (Oplinger et al. 2026); the finite-efficiency condition removes this dependence (Supplementary Information, Sec. S1). The transfer coefficients are calibrated together with the defect-mediated transport coefficients, Sec. 2.4.1.

2.2 Grain-Boundary Oxidation Model

The oxidized zone is treated as a channel of half-width $L(y,t)$, the distance from the boundary mid-plane to the oxide/metal interface, which the oxide phases of thickness L_k fill, $L = \sum_k L_k$. The oxide is mixed locally rather than layered, so a single effective diffusivity applies across and along the boundary,

$$D_{\mathrm{O}}^{\mathrm{eff}} = \sum_k f_k \, D_{\mathrm{O}}^{k}, \tag{15}$$

with f_k the volume fraction and D_{O}^{k} the oxygen diffusivity of phase k. Integrating the two-dimensional oxygen balance over the cross-section gives, for the section-averaged concentration $\bar{C}_{\mathrm{O}}(y,t)$,

$$\frac{\partial}{\partial t}\big(L\,\bar{C}_{\mathrm{O}}\big) = -\frac{\partial}{\partial y}\big(L\,J_{\mathrm{O}}\big) - J_{\mathrm{r}}, \tag{16}$$

$$J_{\mathrm{O}} = -D_{\mathrm{O}}^{\mathrm{eff}}\,\frac{\partial \bar{C}_{\mathrm{O}}}{\partial y}, \tag{17}$$

where J_{r} is the oxygen flux reaching the interface. Equation (16) is exact up to terms of order $\partial L/\partial y$ and makes no assumption on the lateral concentration profile; L inside the time derivative accounts for the dilution of dissolved oxygen as the section widens (Supplementary Information, Sec. S3).

The relation between J_{r} and $\bar{C}_{\mathrm{O}}$ is obtained from the fundamental separable mode of the steady diffusion equation in the cross-section, $C_{\mathrm{O}} \propto \cos(\mu x/L)$, which satisfies the symmetry condition at the mid-plane and the reaction condition at the interface. It gives

$$J_{\mathrm{r}} = \frac{D_{\mathrm{O}}^{\mathrm{eff}}\,\mu^2\,\bar{C}_{\mathrm{O}}}{L}, \qquad C_{\mathrm{O}}^{\mathrm{int}} = \bar{C}_{\mathrm{O}}\,\mu\cot\mu, \tag{18}$$

where $C_{\mathrm{O}}^{\mathrm{int}}$ is the oxygen concentration at the interface and the dimensionless eigenvalue $\mu \in (0, \pi/2)$ is fixed at every position by the interfacial balance between oxygen supply and consumption,

$$\frac{D_{\mathrm{O}}^{\mathrm{eff}}\,\mu^2\,\bar{C}_{\mathrm{O}}}{L} = \sum_k J_{\mathrm{r}}^k\left(\bar{C}_{\mathrm{O}}\,\mu\cot\mu\right). \tag{19}$$

The interfacial reaction rates of the four oxide phases are

$$J_{\mathrm{r}}^{\mathrm{Cr_2O_3}} = k_{\mathrm{r}}^{\mathrm{Cr_2O_3}}\,C_{\mathrm{O}}^{\mathrm{int}}\,C_{\mathrm{Cr}}^{\mathrm{GB}}, \tag{20}$$

$$J_{\mathrm{r}}^{\mathrm{Fe_3O_4}} = k_{\mathrm{r}}^{\mathrm{Fe_3O_4}}\left(C_{\mathrm{O}}^{\mathrm{int}} - C_{\mathrm{O}}^{\mathrm{th}}\right)C_{\mathrm{Fe}}^{\mathrm{GB}}, \tag{21}$$

$$J_{\mathrm{r}}^{\mathrm{FeCr_2O_4}} = k_{\mathrm{r}}^{\mathrm{FeCr_2O_4}}\,C_{\mathrm{O}}^{\mathrm{int}}\left(\frac{1}{C_{\mathrm{Fe}}^{\mathrm{GB}}} + \frac{2}{C_{\mathrm{Cr}}^{\mathrm{GB}}}\right)^{-1}, \tag{22}$$

$$J_{\mathrm{r}}^{\mathrm{SiO_2}} = k_{\mathrm{r}}^{\mathrm{SiO_2}}\,C_{\mathrm{O}}^{\mathrm{int}}\,C_{\mathrm{Si}}^{\mathrm{GB}}, \tag{23}$$

where k_{r}^k is the interfacial rate constant of phase k and $C_{\mathrm{O}}^{\mathrm{th}}$ is the threshold oxygen concentration for magnetite formation; their sum is the total interfacial consumption,

$$J_{\mathrm{r}} = J_{\mathrm{r}}^{\mathrm{Cr_2O_3}} + J_{\mathrm{r}}^{\mathrm{Fe_3O_4}} + J_{\mathrm{r}}^{\mathrm{FeCr_2O_4}} + J_{\mathrm{r}}^{\mathrm{SiO_2}}. \tag{24}$$

The left-hand side of Eq. (19) increases and the right-hand side decreases monotonically with μ, so the root is unique; it is found by Newton's method. In the reaction-limited limit, $\mu^2 \simeq kL/D_{\mathrm{O}}^{\mathrm{eff}}$ with $k = \mathrm{d}J_{\mathrm{r}}/\mathrm{d}C_{\mathrm{O}}^{\mathrm{int}}$, the interface sees the average concentration, $C_{\mathrm{O}}^{\mathrm{int}} \simeq \bar{C}_{\mathrm{O}}$; in the diffusion-limited limit $\mu \to \pi/2$, $C_{\mathrm{O}}^{\mathrm{int}} \to 0$ and $J_{\mathrm{r}} \to \pi^2 D_{\mathrm{O}}^{\mathrm{eff}}\bar{C}_{\mathrm{O}}/4L$. The closure thus spans both regimes without a prescribed transport resistance; its derivation, the neglected higher modes and its range of validity are given in the Supplementary Information, Sec. S3. The corresponding rates of metal removal follow from the stoichiometry of each phase,

$$J_{\mathrm{r}}^{\mathrm{Cr}} = \tfrac{2}{3}J_{\mathrm{r}}^{\mathrm{Cr_2O_3}} + \tfrac{2}{4}J_{\mathrm{r}}^{\mathrm{FeCr_2O_4}}, \tag{25}$$

$$J_{\mathrm{r}}^{\mathrm{Fe}} = \tfrac{3}{4}J_{\mathrm{r}}^{\mathrm{Fe_3O_4}} + \tfrac{1}{4}J_{\mathrm{r}}^{\mathrm{FeCr_2O_4}}, \tag{26}$$

$$J_{\mathrm{r}}^{\mathrm{Si}} = \tfrac{1}{2}J_{\mathrm{r}}^{\mathrm{SiO_2}}. \tag{27}$$

Interfacial mass redistribution. The element with the largest ratio of consumption to availability sets the rate at which the oxidation front advances into the metal,

$$v_{\mathrm{lat}}^{\mathrm{ox,max}} = \max_i \frac{J_{\mathrm{r}}^i}{C_i^{\mathrm{GB}}}, \tag{28}$$

with $J_{\mathrm{r}}^{\mathrm{Ni}} = 0$ since Ni is not oxidized. The front sweeps element i at the rate $v_{\mathrm{lat}}^{\mathrm{ox,max}} C_i^{\mathrm{GB}}$, of which only J_{r}^i is oxidized; the excess

$$E_i = \max\bigl(v_{\mathrm{lat}}^{\mathrm{ox,max}} C_i^{\mathrm{GB}} - J_{\mathrm{r}}^i,\, 0\bigr) \tag{29}$$

is either rejected into the metal ahead of the front or removed through the oxide, where it is retained as unoxidized solute or transported along the oxide grain boundaries to the surface (Deng et al. 2020). The fraction removed through the oxide is

$$\lambda_i = \frac{v_{\mathrm{lat}}^{\mathrm{ox,max}}}{v_{\mathrm{lat}}^{\mathrm{ox,max}} + v_i^{\mathrm{r}}}, \tag{30}$$

where v_i^{r} is the redistribution velocity of element i, the characteristic velocity at which it can be rejected into the metal. Complete rejection ($\lambda_i = 0$) is recovered for $v_i^{\mathrm{r}} \to \infty$; for $v_i^{\mathrm{r}} \ll v_{\mathrm{lat}}^{\mathrm{ox,max}}$ the front outruns the rejection and the excess is carried into the oxide ($\lambda_i \to 1$). The net removal of element i from the metal is then

$$\tilde{J}_{\mathrm{r}}^i = J_{\mathrm{r}}^i + \lambda_i E_i, \tag{31}$$

which replaces J_{r}^i in the interfacial conditions of Sec. 2.3.1. The motivation for this treatment and its limiting behaviour are given in the Supplementary Information, Sec. S2.

2.3 Coupling Strategy and Simulation Protocol

2.3.1 Lattice Velocity and Metal Consumption

Metal atoms leave the metal domain only at the grain-boundary plane, either by oxidation or by removal through the oxide, Eq. (31). Because the metal lattice is incompressible, this removal creates no source in the interior: the entire lattice translates towards the interface at the velocity set by the net interfacial removal. Denoting by

$$v_{\mathrm{ox}}(y,t) = \sum_i \tilde{J}_{\mathrm{r}}^i = \sum_i \bigl(J_{\mathrm{r}}^i + \lambda_i E_i\bigr) \tag{32}$$

the recession rate of the metal/oxide interface, which lies between the oxidation rate $\sum_i J_{\mathrm{r}}^i$ (complete rejection) and the sweep velocity $v_{\mathrm{lat}}^{\mathrm{ox,max}}$ (complete removal), the total lattice velocity in the metal domain is

$$\mathbf{v}_{\mathrm{lat}}(x,y,t) = \mathbf{v}_{\mathrm{lat}}^{\mathrm{RIS}}(x,y,t) + v_{\mathrm{ox}}(y,t)\,\hat{\mathbf{e}}_x. \tag{33}$$

The two contributions differ in character. The segregation term is local: it is determined pointwise by the defect fluxes at (x, y). The oxidation term is not; it is evaluated at the boundary and is independent of x, so a single value applies across the whole domain at a given y. Segregation therefore redistributes the lattice internally, whereas oxidation translates it rigidly, so that the total flux of alloying element i entering Eq. (1) is

$$\mathbf{J}_i = \mathbf{J}_i^{\mathrm{V}} + \mathbf{J}_i^{\mathrm{I}} + C_i \mathbf{v}_{\mathrm{lat}}, \tag{34}$$

subject to the interfacial condition

$$\mathbf{J}_i \cdot \hat{\mathbf{e}}_x \big|_{x=0} = \tilde{J}_{\mathrm{r}}^{i}, \tag{35}$$

which removes from the boundary plane the atoms incorporated into the growing oxide or carried away through it.

Equations (34) and (35) collect the three ways in which an alloying element can move. The first two terms are the diffusive fluxes carried by the two defect mechanisms, Eqs. (4) and (5); the third is the drift of the entire lattice relative to the laboratory frame; the interfacial consumption enters not as a bulk term but as an outgoing flux on the boundary plane.

The two contributions to $\mathbf{v}_{\mathrm{lat}}$ have different origins but act identically on every species. $\mathbf{v}_{\mathrm{lat}}^{\mathrm{RIS}}$ arises because the vacancy and interstitial fluxes are unequal, so lattice sites are created and destroyed at different rates; v_{ox} arises because oxidation consumes metal atoms from the interfacial layer, so the lattice is displaced towards the advancing front. Because the drift term $C_i \mathbf{v}_{\mathrm{lat}}$ is proportional to the local concentration and carries no species selectivity, it does not by itself alter the relative composition; selectivity enters only through the mechanism-specific diffusivities in Eqs. (6)–(9), through the stoichiometric sinks in Eqs. (25)–(27), and through the element-specific redistribution fractions λ_i of Eq. (30).

2.3.2 Sequential Irradiation–Oxidation Protocol

The reference experiments irradiate the specimen first and expose it to the primary water environment afterwards. The model reproduces this protocol as two consecutive stages that share the same governing equations and differ only in two switches: the dose rate K_0 and the oxygen boundary condition at the grain-boundary mouth.

In the irradiation stage the specimen is irradiated to the target dose with no oxygen present, $K_0 > 0$ and $C_{\mathrm{O}} \equiv 0$, so that Eqs. (1)–(12) govern the

evolution alone and all interfacial reaction rates vanish identically. The stage is integrated to $t_{\mathrm{irr}} = \Phi/K_0$, where Φ is the nominal dose in dpa, and yields the segregated composition profiles $C_i(x, y, t_{\mathrm{irr}})$.

The oxidation stage continues from the final state of the irradiation stage: all concentration fields, including the point-defect populations, are inherited unchanged,

$$(C_i,\, C_{\mathrm{V}},\, C_{\mathrm{I}})\big|_{t=0^+} = (C_i,\, C_{\mathrm{V}},\, C_{\mathrm{I}})\big|_{t=t_{\mathrm{irr}}}\,, \qquad L_k\big|_{t=0^+} = 0, \tag{36}$$

and the exposure clock is restarted from zero. The dose rate is then set to zero, $K_0 = 0$, so that the inherited defect supersaturation decays by recombination according to Eqs. (2) and (3) without further production.

Simultaneously, the oxygen boundary condition at the mouth of the boundary is switched on. Oxygen ingress is limited by the surface film that grows on the free surface, whose resistance increases as the film thickens; this is imposed as a Robin condition with a time-decaying transfer coefficient,

$$J_{\mathrm{O}}\big|_{y=0} = h(t)\left(C_{\mathrm{O}}^{\mathrm{w}} - \bar{C}_{\mathrm{O}}\big|_{y=0}\right), \qquad h(t) = \frac{k_{\mathrm{s}}}{\sqrt{t} + \sqrt{t_0}}, \tag{37}$$

where $C_{\mathrm{O}}^{\mathrm{w}}$ is the oxygen concentration of the bulk water, k_{s} is the surface transfer coefficient, and t_0 regularizes the initial instant. The $t^{-1/2}$ decay reproduces the parabolic thickening of the surface film, so that the cumulative oxygen admitted through the mouth grows as $t^{1/2}$. The deep end of the boundary is closed, $J_{\mathrm{O}}\big|_{y=L_{\mathrm{GB}}} = 0$.

Because no point defects are produced once $K_0 = 0$, the inherited supersaturation decays on the recombination timescale, which is short compared with the exposure time; segregation therefore effectively ceases early in the exposure stage, and the composition field that the oxidation model sees is the one established during irradiation. The sequential protocol thus isolates the compositional pathway: any dose dependence of the predicted oxidation depth must be carried by the radiation-induced segregation profile inherited through Eq. (36), since neither radiolysis nor sustained irradiation-assisted transport is present.

2.3.3 Fully Coupled Irradiation–Oxidation Framework

The sequential protocol of Sec. 2.3.2 is a special case of the governing equations rather than a separate model: it is obtained by switching K_0 and the

mouth boundary condition on and off in turn. Leaving both switches on throughout, $K_0 > 0$ together with the Robin condition Eq. (37), gives the fully coupled problem in which segregation and oxidation proceed simultaneously, as they do in reactor service. No additional equations or parameters are required; Eqs. (1)–(12) are integrated as a single stage.

In this mode the two processes feed back on each other. Segregation continues to modify the boundary composition while the oxidation front advances, so the composition that the interfacial reactions see evolves in time rather than being fixed at its end-of-irradiation value; conversely, the metal consumed at the front and the associated lattice drift, Eq. (32), alter the concentration field on which the segregation fluxes act. Predictions obtained in this mode are reported in Sec. 3.5; because no experiment in the present dataset imposes concurrent irradiation and exposure, this mode is used only for prediction and takes no part in the calibration of Sec. 2.4.

2.4 Model Parameterization and Calibration

The two components are parameterized and calibrated separately and against separate data. The RIS model is calibrated first; the oxidation model is then calibrated with the RIS model related parameters fixed.

2.4.1 RIS Parameterization

The RIS model requires the mechanism-specific diffusion coefficients D_i^{V} and D_i^{I} of the four alloying elements, the correlation factors f_0^{V} and f_0^{I}, the recombination coefficient R, the damage efficiency ϵ, the dose rate K_0, and the grain-boundary transfer coefficients $k_{\mathrm{V}}^{\mathrm{GB}}$ and $k_{\mathrm{I}}^{\mathrm{GB}}$ of Eqs. (13) and (14). The dose rate and irradiation temperature are those of the reference experiment. The correlation factors are taken from their crystallographic values for the fcc lattice. The damage efficiency accounts for the fraction of displacements that survive in-cascade recombination and escape as freely migrating defects; its value is that reported for proton irradiation. The vacancy and interstitial migration energies and pre-exponential factors are taken from the literature and adjusted within their reported ranges, jointly with the transfer coefficients, to reproduce both the magnitude and the width of the measured grain-boundary composition profiles across the dose series. Because these profiles are measured before exposure, the RIS calibration is independent of the oxidation model. The resulting values are given in Table 1.

2.4.2 Oxidation Kinetics Parameterization

The oxidation model requires the interfacial rate constants k_{r}^{k} of the four oxide phases, their oxygen diffusivities D_{O}^{k}, the surface transfer coefficient k_{s} of the Robin condition Eq. (37), the magnetite threshold $C_{\mathrm{O}}^{\mathrm{th}}$, and the redistribution velocities v_i^{r} of Eq. (30). The oxide molar volumes and densities used in the thickness update are taken from crystallographic data and held fixed.

The model is calibrated against the dose-dependent grain-boundary oxidation depths of Deng et al. (2017), measured after exposure in simulated PWR primary water at 0, 0.5, and 3 dpa. The predicted oxidation depth is defined as the distance from the boundary mouth to the deepest position at which the total oxide thickness $\sum_k L_k$ exceeds a fixed threshold L_{th}, applied identically at every dose. The free parameters are adjusted to reproduce the measured depths at all three doses simultaneously, using a single parameter set; no parameter is allowed to take different values at different doses. The resulting values are given in Table 2.

Table 1: Parameters of the radiation-induced segregation model.

Symbol	Description	Value	Source


Table 2: Parameters of the grain-boundary oxidation model.

Symbol	Description	Value	Source

3 Results

3.1 Radiation-Induced Segregation Profiles

Figure 3 compares the calculated and measured grain-boundary composition profiles after irradiation to 0.5 and 3.0 dpa. The calculated profiles are convolved with a 1 nm Gaussian to account for the finite spatial resolution of the measurements. These profiles are the target of the RIS calibration of Sec. 2.4.1.



(a) (b) (c)

Figure 3: Calculated and measured grain-boundary composition profiles after irradiation to 0.5 and 3.0 dpa: (a) Cr, (b) Ni, (c) Si. Solid lines are calculated profiles obtained with the finite-efficiency sink condition, Eqs. (13) and (14), and convolved with a 1 nm FWHM Gaussian; symbols are the measurements of Deng et al. (2021) at 0.5 and 3.0 dpa.

Cr is depleted at the boundary and Ni and Si are enriched, at both doses. The calculated boundary Cr concentration falls from the matrix value of about 20 at.% to about 14 at.% at 0.5 dpa and about 11 at.% at 3.0 dpa, against measured minima of about 16.5 and 11.5 at.% (Fig. 3a). Ni rises from about 9 at.% to about 12 and 14.5 at.%, against measured maxima of about 12.5 and 14.5 at.% (Fig. 3b). Si rises from about 0.3 at.% to about 1.4 and 2.8 at.%, against measured maxima of about 2.0 and 2.8 at.% (Fig. 3c). The boundary values at 3.0 dpa are reproduced for all three elements; at 0.5 dpa the model underestimates the Cr depletion and the Si enrichment.

The widths of the profiles differ between the two doses. The measured profiles return to their matrix values within roughly 5 nm of the boundary at 0.5 dpa and within roughly 8 nm at 3.0 dpa. The calculated 0.5 dpa profiles reproduce this width, whereas the calculated 3.0 dpa profiles are broader than measured: 15 nm from the boundary the calculated Cr and Ni have not yet returned to their matrix values. The dose dependence of the segregation magnitude is therefore captured, while the width of the segregated zone at the higher dose is overestimated.

3.2 Oxide Composition and Interfacial Chemistry

Figure 4 compares the calculated composition across the intergranular oxide with the EDX line scans of Deng et al. (2017). The measurements show the signature of selective oxidation: Cr is enriched and Fe depleted in the




Figure 4: Calculated and measured composition profiles across the intergranular oxide after the 500 h exposure: (a–c) solution-annealed, (d–f) 0.5 dpa, (g–i) 3.0 dpa; Cr, Ni and Fe from left to right. Calculated profiles are convolved with a Gaussian of 1 nm FWHM to match the EDX probe; measurements are the line scans of Deng et al. (2017).

oxide relative to the matrix. On the metal side of the interface, however, the scans show no significant Cr depletion or Fe enrichment, and only a slight Ni enrichment. In the irradiated specimens the Cr profile exhibits a minimum at the centre of the oxide that deepens with increasing dose. This indicates that the Cr concentration at the advancing interface is set by the radiation-induced segregation profile and is not modulated by the selective oxidation:

the shape of the segregation profile is retained as the front moves into the metal.

A model in which all unoxidized metal is rejected to the metal side cannot reproduce this behaviour. Because Cr reacts much faster than Fe, such a model depletes Cr and enriches Fe strongly at the interface, in conflict with the scans. With the interfacial mass redistribution of Eqs. (28)–(31), the excess Fe and Ni swept by the front are carried away through the oxide instead, as proposed by Deng et al. (2020), and the calculated profiles reproduce both the retained segregation shape and the central Cr minimum, whose depth increases with dose in the measurements and in the model. The calculated Cr and Fe contents of the oxide follow the measured dose dependence: less Cr is available at the front after irradiation, so the oxide that forms there is poorer in Cr and richer in Fe. No Ni oxide is observed experimentally (Deng et al. 2021); the small amount of Ni detected in the oxide is treated as unoxidized solute retained in the oxide, which the model represents through the Ni fraction λ_{Ni}. The calculated profiles are plotted with the oxide formed first located at the centre of the intergranular oxide, consistent with symmetric growth into both grains.

Silica formed at the boundary is not retained: the segregated Si is oxidized preferentially and the resulting SiO_2 dissolves into the water, leaving porosity in the intergranular oxide (Du et al. 2026). The model adopts this behaviour explicitly. All SiO_2 produced is treated as dissolved and the volume it occupied is retained as free volume available for oxygen transport, so the calculated SiO_2 volume fraction is a measure of the porosity generated within the intergranular oxide rather than of a phase present in it.

3.3 Dose-Dependent Grain-Boundary Oxidation Kinetics

The oxidation parameters are calibrated against the dose dependence of the intergranular oxide penetration depth after 500 h of exposure measured by Deng et al. (2017) at 0, 0.5 and 3.0 dpa, Fig. 5. With a single parameter set the calculated depths are 38, 71 and 97 nm against measured values of 40, 62 and 105 nm: the unirradiated depth is matched, the 0.5 dpa depth is overestimated by 9 nm and the 3.0 dpa depth underestimated by 8 nm. The increase of penetration depth with dose is carried entirely by the segregation profiles inherited from the irradiation stage, Eq. (36).





Figure 5: Calculated and measured oxidation front depth after the 500 h exposure as a function of dose, taken at a total oxide thickness of 1 nm. These measurements, from Deng et al. (2017), are the ones used to calibrate the oxidation parameters.

3.4 Predictions against Independent Experiments

With the parameters fixed by the calibration of Fig. 5, the model is used to predict the time dependence of the penetration depth, which is compared in Fig. 6 with the measurements of Deng et al. (2020) at 0.5 and 1.5 dpa after 100 and 1500 h. At 100 h the calculated and measured depths are of the same order, 20–40 nm. At 1500 h the model gives about 95 and 110 nm against measured values of about 194 and 231 nm, roughly half (Fig. 6a). The two experimental series are, however, not mutually consistent: although the authors report the same material, irradiation and exposure conditions, the apparent effective diffusivity of the oxidation front, $\bar{D}_{\mathrm{eff}} = L^2/2t$, is larger for the 0.5 dpa specimen of Deng et al. (2020) than for the 3.0 dpa specimen of Deng et al. (2017) (Supplementary Information, Table S1). A model calibrated on the 2017 series is therefore expected to underestimate the depths of the 2020 series. When the depths are normalized by the maximum over both doses, Fig. 6b, the calculated 0.5 dpa value at 1500 h, 0.85, matches the measured 0.84, so the ratio between the two doses at long times is reproduced; at 100 h the calculated normalized depths, about 0.20 and 0.25, exceed the measured 0.12 and 0.18, i.e. the calculated kinetics are relatively



(a) (b)

Figure 6: Predicted and measured time dependence of the intergranular oxide penetration depth at 0.5 and 1.5 dpa, obtained with the calibrated parameters held fixed; neither the 1.5 dpa dose nor the exposure times shown enter the calibration. (a) Penetration depth versus exposure time. (b) Penetration depth normalized by the maximum depth over both doses, $L/L_{\max}$, taken separately for the calculations ($L_{\max} = 110$ nm) and the measurements ($L_{\max} = 231$ nm). Measurements from Deng et al. (2020).

faster at short times. The model thus predicts the relative effect of dose at long exposure, while the absolute rate is tied to the series used for calibration.

3.5 Fully Coupled Predictions under Concurrent Irradiation and Oxidation

4 Discussion

4.1 Effect of Radiation-Induced Segregation on Grain-Boundary Oxidation

4.2 Rate-Controlling Transport and Oxide Chemistry

4.3 Implications of Concurrent Irradiation and Oxidation

4.4 Predictive Capability and Model Limitations

5 Conclusions

References

Deng, P., Q. Peng, and E. H. Han (Jan. 14, 2021). "Grain Boundary Oxidation of Proton-Irradiated Nuclear Grade Stainless Steel in Simulated Primary Water of Pressurized Water Reactor". In: *Sci Rep* 11.1, p. 1371. ISSN: 2045-2322 (Electronic) 2045-2322 (Linking). DOI: 10.1038/s41598-020-80600-x.

Deng, Ping et al. (2017). "Effect of Irradiation on Corrosion of 304 Nuclear Grade Stainless Steel in Simulated PWR Primary Water". In: *Corrosion Science* 127, pp. 91–100. ISSN: 0010938X. DOI: 10.1016/j.corsci.2017.08.010.

Deng, Ping et al. (2020). "Corrosion Behavior and Mechanism of Irradiated 304 Nuclear Grade Stainless Steel in High-Temperature Water". In: *Acta Metallurgica Sinica (English Letters)* 34.2, pp. 174–186. ISSN: 1006-7191 2194-1289. DOI: 10.1007/s40195-020-01123-y.

Du, Donghai et al. (2026). "Silicon Segregation Enhances IASCC of Austenitic Stainless Steels via Oxide Degradation: Decoupling from Chromium Depletion Effects". In: *Corrosion Science* 258. ISSN: 0010938X. DOI: 10.1016/j.corsci.2025.113424.

Oplinger, Russell et al. (2026). "Radiation-Induced Segregation in Dilute Fe–Cr: A Rate-Theory Framework for the Cr Enrichment–Depletion Transition at the Grain Boundary". In: *Journal of Applied Physics* 139.15. ISSN: 0021-8979 1089-7550. DOI: 10.1063/5.0323296.