

Li₃PS₄ glass — sulfide transferability test

Moving beyond oxychlorides tests whether structural and transport agreement persist

1 Literature

Mirmira et al. (2021)
Experimental glass
Chen et al. (2025): DeePMD

2 Structure

Author-data precursor
Li₁₉₂P₆₄S₂₅₆; 512 atoms
Melt-quench with NEP89

3 MD protocol

300 / 500 / 700 / 900 K
50 ps NPT equilibration
200 ps NVT production

4 Analysis

Li MSD and D(T)
Li-S / P-S RDF and CN
Framework motion

5 Conclusion

Local motifs partly retained
Transport magnitude differs
Dedicated work remains