Instituto Federal de São Paulo

Campus Birigui

Relatório de Ensaio


Máquina: **Emic DL30000N** Célula: **Trd 24** Extensômetro: **-** Data: **21/06/2024** Hora: **10:59:03** Trabalho n° **0056**

Programa: **Tesc versão 3.04** Método de Ensaio: **Davi IC PLA**

Ident. Amostra: >>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>> Identificação: **Amostras A10** Material: **PLA Maker** Operador: **Vicente**

Corpo de Prova	Compr. Base (mm)	Força @Força Max. (N)	Força @Ruptura (N)	Tensão @Ruptura (MPa)	Tensão @Escoam. ES1 (MPa)	Mod.Elástic. (MPa)
CP 1	**50.00**	**1918.37**	**1903.41**	**39.42**	**22.99**	**578.95**
CP 2	**50.00**	**2080.14**	**2064.15**	**42.84**	**22.97**	**558.94**
CP 3	**50.00**	**1880.78**	**1866.49**	**38.62**	**22.49**	**562.64**
CP 4	**50.00**	**2196.32**	**2186.96**	**45.42**	**24.69**	**561.35**
CP 5	**50.00**	**1976.21**	**1976.21**	**41.07**	**25.34**	**586.99**
Número CPs	**5**	**5**	**5**	**5**	**5**	**5**
Média	**50.00**	**2010**	**1999**	**41.47**	**23.69**	**569.8**
Desv.Padrão	**0.0000**	**128.3**	**129.2**	**2.736**	**1.241**	**12.45**
Coef.Var.(%)	**0.0000**	**6.383**	**6.463**	**6.598**	**5.238**	**2.185**
Mínimo	**50.00**	**1881**	**1866**	**38.62**	**22.49**	**558.9**
Máximo	**50.00**	**2196**	**2187**	**45.42**	**25.34**	**587.0**

Tensão (MPa)



Observação: Ensaios realizados em 21/06/2024 período da manhã - CPs 1 e 2, velocidade 5 mm/min, CP 3 velocidade 2 mm/min



This document was created with the Win2PDF “Print to PDF” printer available at

https://www.win2pdf.com

This version of Win2PDF 10 is for evaluation and non-commercial use only.
Visit https://www.win2pdf.com/trial/ for a 30 day trial license.

This page will not be added after purchasing Win2PDF.

https://www.win2pdf.com/purchase/