Instituto Federal de São Paulo

Campus Birigui

Relatório de Ensaio


Máquina: **Emic DL30000N** Célula: **Trd 24** Extensômetro: **-** Data: **10/06/2013** Hora: **15:48:56** Trabalho n° **0060**

Programa: **Tesc versão 3.04** Método de Ensaio: **Davi IC PLA**

Ident. Amostra: >>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>>> Identificação: **Amostras A12** Material: **PLA Maker** Operador: **Vicente**

Corpo de Prova	Compr. Base (mm)	Força @Força Max. (N)	Força @Ruptura (N)	Tensão @Ruptura (MPa)	Tensão @Escoam. ES1 (MPa)	Mod.Elástic. (MPa)
CP 1	**50.00**	**1866.83**	**1852.21**	**43.71**	**25.13**	**623.26**
CP 2	**50.00**	**1991.86**	**1976.55**	**45.97**	**24.42**	**605.49**
CP 3	**50.00**	**1905.62**	**1890.82**	**44.69**	**25.68**	**633.30**
CP 4	**50.00**	**1992.03**	**1977.57**	**47.32**	**28.87**	**629.32**
CP 5	**50.00**	**1979.95**	**1968.72**	**47.07**	**25.22**	**625.79**
Número CPs	**5**	**5**	**5**	**5**	**5**	**5**
Média	**50.00**	**1947**	**1933**	**45.75**	**25.86**	**623.4**
Desv.Padrão	**0.0000**	**57.58**	**58.02**	**1.542**	**1.740**	**10.72**
Coef.Var.(%)	**0.0000**	**2.957**	**3.001**	**3.370**	**6.726**	**1.720**
Mínimo	**50.00**	**1867**	**1852**	**43.71**	**24.42**	**605.5**
Máximo	**50.00**	**1992**	**1978**	**47.32**	**28.87**	**633.3**

Tensão (MPa)



Observação: Ensaios realizados em 05/08/2024 período da TARDE



This document was created with the Win2PDF “Print to PDF” printer available at

https://www.win2pdf.com

This version of Win2PDF 10 is for evaluation and non-commercial use only.
Visit https://www.win2pdf.com/trial/ for a 30 day trial license.

This page will not be added after purchasing Win2PDF.

https://www.win2pdf.com/purchase/