程中的质量把关失控,导致局部缺陷,耐蚀性降低,环境变化时得以暴露,造成腐蚀。

(3)催化烟气脱硫吸收塔的腐蚀是工艺变化和材料缺陷共同作用的结果。

(4)基于目前的工艺条件,对催化烟气脱硫吸收塔重新堆焊部位进行修补,并严格选用合格的焊条材料,且严格按照防腐蚀施工工艺标准,以确保防腐蚀施工质量;同时,运行中严格控制引起腐蚀的因素,以降低设备腐蚀速率,来减轻脱硫吸收塔腐蚀、延长该装置的安全运行周期,催化脱硫装置脱硫吸收塔已连续运行24个月。

参考文献

[1]魏宝．金属腐蚀理论及应用[M]．北京:化工工业出版社,2004.

[2]中华人民共和国国家质量监督检验检疫总局．金属显微组织检验方法:GB/T 13298[S],北京:国家标准出版社,2015.

[3]美国材料及试验协会．压力容器和一般用途用铬及铬-镍不锈钢钢板、薄板和钢带标准技术条件:ASTM A240/A240M[S],2016.

[4]中华人民共和国国家质量监督检验检疫总局．不锈钢焊条:GB/T983—2012[S],北京:国家标准出版社,2019.

[5]王博,李德超,李庆华,等．硝酸重沸器的腐蚀失效分析和防护对策[J]．表面技术,2011,40(1):63-67.

[6]熊金平,左禹,郭超,等．苯酚生产装置的316L不锈钢塔开裂失效分析[J]．腐蚀科学与防护技术,2005,17(5):363-365.

CORROSION ANALYSIS OF CATALYTIC DESULFURIZATION UNIT ABSORPTION TOWER

TIAN Zhaohai

(*Shengli Refinery of Qilu Branch Co.*, *SINOPEC*, *Zibo Shandong* 255400)

Abstract: Catalytic cracking flue gas desulfurization technology can fully realize the discharge of flue gas purification and achieve emission standards. However, due to existence of the corrosive medium, corrosion problem happens in the desulfurization absorber tower of many catalytic desulfurization devices. This article analyzes the corrosion of a desulfurization absorber tower in a compang and identifies the causes of corrosion. The combined action of changes in the operating mode after reconstruction of the desulfurization absorber tower and local defects of the materials causes the corrosion. By strictly controlling the manufacturing process of composite plate, improving the nozzle structure of outlet distributor of circulating pump and moving up the ammonia water distributor, the desulphurization tower has not been corroded again.

Key words: catalytic cracking; flue gas desulfurization; corrosion

一种己内酰胺加氢精制催化剂及其制备方法和应用

本公开涉及一种己内酰胺加氢精制催化剂及其制备方法和应用,所述催化剂为多孔晶态合金颗粒;所述催化剂含有镍、硅和可选的改性金属元素;所述改性金属元素选自元素周期表第IB族、第IIB族、第IIIB族、第IVB族、第VIB族、第VIIB族和第VIII族中的一种或几种;以所述催化剂的总重量为基准,所述镍元素的质量分数为10%~70%,所述硅元素的质量分数为10%~80%,所述改性金属元素的质量分数为0%~30%。本公开的催化剂能够用于己内酰胺加氢精制反应,具有较高的加氢活性,制备得到的己内酰胺纯度高。(中国石油化工股份有限公司;中国石油化工股份有限公司石油化工科学研究院)/CN202010898515.3,2024-03-15

一种重质油加氢处理催化剂及其制备方法

本发明公开了一种重质油加氢处理催化剂及其制备方法。所述催化剂包括载体及活性金属组分;催化剂在密相装填时的空隙率大于43.5%,优选空隙率为45%~50%,更优选空隙率为46%~48%。本发明催化剂具有较大孔容和孔径,并具有较大的床层空隙率,能够有效降低沥青质和胶质大分子在催化剂孔道内部扩散阻力,提高加氢转化效率。特别适用于重质油加氢处理过程中的对原料中沥青质和胶质大分子的加氢转化过程。(中国石油化工股份有限公司;中石化(大连)石油化工研究院有限公司)/CN202011182283.8,2024-03-08

(C)1994-2024 China Academic Journal Electronic Publishing House. All rights reserved.　http://www.cnki.net