

ML Line A/B Blockage (HD1/2): Prevention and extend service time

26 June, 2015

Participants:

Suriya T.

Nirutti N.

Chuchat M.

Somchai Sa.

Thakul W.


Saowani L.

Objective

- To extend service time of ML line A/B from 3 months to 6 months
- To decrease production loss 3,040 Ton/year
- To decrease manufacturing cost from margin loss and cleaning cost of 9,520,000 THB*

*see calculation in slide no. 10

Drawing of ML line





















Line B

Line A

ML Line Cleaning history

Inspection date	30 Sep 14	7 Jan 15	4 Mar 15	20 May 15
Service date	30 Jun – 28 Sep, 14	30 Sep, 14 – 7 Jan, 15	7 Jan – 2 Mar, 15	4 Mar – 20 May, 15
Service (days)	92	100	54	77
Product sequence	1100J -> 1600J -> 5S -> 5200B -> 6200B -> 3502C -> 6600B -> 7F	6F -> 7F	6F -> 7F	7F-> 1600J-> 2308J-> 2200JP -> 5S -> 5200B -> 6200B -> 3502C -> 6600B -> 6F -> 7F
Product (T)	79,800	86,400	41,600	52,200
Flexible M-0301A	~ 50% Plugged	Plugged ~ 90%	Almost cleaned	Almost cleaned
Flexible M-0301B	> 50% Plugged (More than M-0301A)	Plugged ~ 20%	Plugged 10%	No data
ML line A	Plugged 3 - 7 cm. thickness (~ 20% Plugged)	Plug at near flexible only, but in the line almost cleaned	Slightly accumulate	Almost cleaned, accumulate only at flange
ML line B	~ 30% Plugged higher than M-0301A	Plug at near flexible only, but in the line almost cleaned	Almost cleaned	Almost cleaned, accumulate only at flange
%Load M-0301A/B	50/50	46 - 48/52-54	50/50	48/52
Remark	30-Jun-14: M-0301A L/O leak at gear side	17-Dec-15: M-0301A Motor abnormal sound, vibration > 9 mm/s		






ML Line Cleaning history

Inspection date	30 Sep 14	7 Jan 15	4 Mar 15	20 May 15
Service date	30 Jun – 28 Sep, 14	30 Sep, 14 – 7 Jan, 15	7 Jan – 2 Mar, 15	4 Mar – 20 May, 15
Service (days)	92	100	54	77
Product sequence	1100J -> 1600J -> 5S -> 5200B -> 6200B -> 3502C -> 6600B -> 7F	6F -> 7F	6F -> 7F	7F-> 1600J-> 2308J-> 2200JP -> 5S -> 5200B -> 6200B -> 3502C -> 6600B -> 6F -> 7F
Product (T)	79,800	86,400	41,600	52,200
Flexible M-0301A	 50%	 80%	 <5%	 <5%
Flexible M-0301B	 >50%	 20%	 10%	No Data
ML line A	 20%	 10%	 <5%	 <5%
ML line B	 30%	 10%	 <5%	 <5%
Steam tracing Line A / B	No data			

Summary

1. Production sequence should not be the cause of ML line blockage
2. Service period of ML line A/B is around 3 months (max. 100 days)
From 2 latest - service periods, ML line is almost cleaned (ML line blockage is only 5-10%), this might be from insulation in Jan 2015

This is the sign that ML line service can be extended.

ML Line	Line A	Line B	
Flexible			
Flange to ML line	 <p data-bbox="378 1096 821 1139">3 rounds of steam tracing</p>	 <p data-bbox="1058 1096 1632 1139">No steam tracing (only insulation)</p>	

Action

Activity	RP	Status
1. ปรับปรุงการพัน steam tracing ที่ flexible ทั้ง line A/B	Chuchat M.	Done 17 Jun 15
2. เก็บข้อมูล temp. ที่ flange ของ Line A/B เปรียบเทียบก่อน, หลังปรับปรุงการพัน steam tracing	Suriya T.	Done 22 Jun 15
3. ติดตามผลภายหลังการปรับปรุง steam tracing และนัดประชุมอีกครั้งในเดือนกันยายน 2558	Saowani L.	

Before improvement

Flexible M-0301A



- It has steam tracing more than M-0301B (16 round)
- Temperature at flex ~68 °C

Bottom flange of flexible M-0301A



- It has steam tracing but no has inside insulation cover
- Temperature at bottom flange ~68 °C

Flexible M-0301B




- It has steam tracing 7 round
- Temperature at flex ~57 °C

Bottom flange of flexible M-0301B



- No has steam tracing but it has inside insulation cover
- Temperature at bottom flange ~55 °C

Line A



Line B



Calculation

Basis:

1. To decrease ML line cleaning 4 to 2 times/year (included Annual SD)
2. ML line cleaning cost 200,000 THB/time
3. Downtime to clean ML line 40 hr/time
4. Margin ref. grade (HD7000F) 100 USD/Ton-PE (1USD = 30 THB)
5. Production rate = 38 T/hr

Calculation:

- 1). Product loss = $38 \text{ T/hr} \times 40 \text{ hr} = 1,520 \text{ T/time} \times 2 \text{ times SD} = \mathbf{3,040 \text{ T/year}}$
- 2). Margin loss = $38 \text{ T/hr} \times 40 \text{ hr} \times 2 \text{ times SD} \times 100 \text{ USD/T} \times 30 \text{ THB/USD} = 9,120,000 \text{ THB/year}$
- 3). ML cleaning 2 times/year = $2 \times 200,000 = 400,000 \text{ THB/year}$

Cost saving from decreasing 2 time/year of ML Line SD = Margin loss + Cleaning cost
= 9,120,000 + 400,000 = 9,520,000 THB/year

Project Team



THANK YOU FOR YOUR ATTENTION