Monocrystalline

Polycrystalline

LP182*182-M-60-MH

Rated Power 440-460W





MBB Cell

New circuit design, lower internal current, lower internal resistance loss.



Higher Output Power

Module adopts 120 pcs of 182*182mm half cells, the maximum power can reach 460W.



Harsh Environmental Adaptability

Strict salt spray and ammonia corrosion test by TUV Nord.





Low Light Features

Higher performance under low light environment.



PID Protection

Ensure the attenuation probability caused by PID phenomenon is minimized.



Load Capacity

Mechanical load tests including wind load 2400 Pa and snow load 5400 Pa done by TUV Nord.







J-PEC Product








IEC 61215-2: 2016 IEC 61730-2: 2016

Headquarter : Leapton Energy Co., Ltd.

♥ Tosei Bldg. 6F, 1-2-1 Aioi-cho, Chuo-ku Kobe-shi, Hyogo, 650-0025, Japan Manufacturer: Leapton Solar (Changshu) Co., Ltd.

\(+81-78-382-3182


www.leaptonenergy.jp



\$\ +86-512-88800068



■ MECHANICAL DIAGRAMS



SPECIFICATIONS

Weight	23.5kg
Dimensions	1909mm*1134mm*30mm
Cell Dimensions	182*182mm
Cell Amount	60*2 pcs
Maximum System Volta	ige 1500V
Junction Box	IP68
Frame	Aluminum Alloy
Cable	4mm2, Landscape: N 1200mm/P 1200mm Portrait: N 200mm/P 300mm
Connector	MC4 compatible
Application Level	Class A

■ ELECTRICAL PARAMETERS AT STC

Power	440W	445W	450W	455W	460W
Open Circuit Voltage	41.00V	41.20V	41.40V	41.60V	41.80V
Short Circuit Current	13.58A	13.63A	13.68A	13.73A	13.78A
Maximun Power Voltage	34.20V	34.50V	34.70V	34.90V	35.20V
Maximum Power Current	12.84A	12.90A	12.96A	13.02A	13.08A
Module Efficiency	20.33%	20.56%	20.79%	21.02%	21.25%

^{*} Under Standard Test Conditions (STC) of irradiance of 1000 W/m2, spectrum AM 1.5 and cell temperature of 25°C.

ELECTRICAL PARAMETERS AT NMOT

Power	324W	328W	331W	335W	339W
Open Circuit Voltage	38.28V	38.48V	36.68V	38.88V	39.08V
Short Circuit Current	10.68A	10.73A	10.78A	10.83A	10.88A
Maximun Power Voltage	31.94V	32.14V	32.34V	32.54V	32.74V
Maximum Power Current	10.14A	10.21A	10.24A	10.30A	10.35A
Module Efficiency	14.97%	15.15%	15.29%	15.47%	15.66%

^{*} Under Nominal Module Operating Temperature (NMOT), irradiance of 800 W/m2, spectrum AM 1.5, ambient temperature 20°C, wind speed 1 m/s.

TEMPERATURE CHARACTERISTICS

NMOT	41±3°C	Temp Coefficient of ISC	+0.05%/°C
Temp Coefficient of VOC	-0.28%/°C	Temp Coefficient of Pmax	-0.36%/°C


PACKING CONFIGURATION

Modules/Pallet 36 Pieces Modules/40'Container 864 Pieces 24 Pallets, Total=(36+36)x12=864 Pieces

Packing Description


CHARACTERISTICS

LP182*182-M-60-MH-440W



Leapton Energy Co., Ltd.

LP182*182-M-60-MH-440W



MAXIMUM RATING

Output Tolerance 0~+5W -40°C~+85°C **Operating Temperature** Wind Load/Snow Load 2400pa/5400pa **Fuse Current** 25A



\(+81-78-382-3182



www.leaptonenergy.jp

Warranty

- Tosei Bldg. 6F, 1-2-1 Aioi-cho, Chuo-ku Kobe-shi, Hyogo, 650-0025, Japan Manufacturer : Leapton Solar (Changshu) Co., Ltd.
- No.9, Sunshine Avenue, Changshu City, Jiangsu, China

\(+86-512-88800068

www.leaptonpv.com