

Tabelle 1: NIXSW results for QA on Ag(100) - α -phase: coherent positions p_c , coherent fractions f_c , and distances z_{200} .

Component	f_c	p_c	z_{200} (Å)
C _{arom}	0.369 ± 0.015	0.459 ± 0.007	2.981 ± 0.014
C _{NH}	0.811 ± 0.031	0.438 ± 0.006	2.938 ± 0.012
C _{CO}	0.615 ± 0.020	0.469 ± 0.007	3.001 ± 0.014
C _O	0.436 ± 0.029	0.458 ± 0.011	2.979 ± 0.022
C _{total}	0.523 ± 0.012	0.455 ± 0.004	2.973 ± 0.008
N1	0.288 ± 0.013	0.499 ± 0.009	3.062 ± 0.018
O1	0.546 ± 0.016	0.332 ± 0.004	2.721 ± 0.008

Tabelle 2: NIXSW results for QA on Ag(100) - β -phase: coherent positions p_c , coherent fractions f_c , and distances z_{200} .

Component	f_c	p_c	z_{200} (Å)
C _{arom} + C _{NH}	0.758 ± 0.017	0.387 ± 0.003	2.834 ± 0.006
C _{CO}	0.660 ± 0.025	0.350 ± 0.002	2.758 ± 0.004
C _O	0.564 ± 0.026	0.387 ± 0.007	2.834 ± 0.014
C _{total}	0.712 ± 0.012	0.378 ± 0.002	2.815 ± 0.004
N1	0.374 ± 0.021	0.486 ± 0.008	3.036 ± 0.016
N2	0.645 ± 0.034	0.184 ± 0.004	2.419 ± 0.008
N _{total}	0.645 ± 0.034	0.289 ± 0.005	2.633 ± 0.010
O1	0.658 ± 0.056	0.272 ± 0.007	2.599 ± 0.014
O2	0.559 ± 0.072	0.291 ± 0.011	2.638 ± 0.022
O _{total}	0.598 ± 0.042	0.282 ± 0.006	2.619 ± 0.012