

PRODUCT DESCRIPTION

Marine Guard is a two-component, high-performance polymer protective coating originally engineered for marine service — hulls, jetties and steel structures under continuous salt-water attack. The cured film is hard and glossy, markedly increasing surface strength and abrasion resistance. It coats concrete, steel and timber; restores dusting or weathered concrete to a hard, dust-free condition; protects steel against corrosion even in permanent salt-water immersion; and extends the service life of exterior timber. The system is based on a polyaminoamide curing technology powered by Huntsman Advanced Materials, with a 100% solids formulation — no solvent is added at the factory. Adhesion to dry and damp concrete is excellent, and the coating may be applied to new concrete from approximately one week of cure. The continuous 100% solids film also allows the product to serve as a moisture barrier beneath floor coatings and floor coverings. A topcoat is recommended for this product in service.

KEY DATA

Chemistry	Two-component polymer coating / polyaminoamide curing system
Solids content	100% solids — no solvent added at the factory. If the mixed material is too viscous, up to 10% thinner may be added on site.
Substrates	Concrete (including damp substrates and new concrete from approx. 1 week of cure), steel and timber. Also used as an adhesion primer on glazed floor tile and beneath PU floor-coating systems, and as a moisture barrier on concrete floors.
Mix ratio (A : B)	2 : 1 by weight — always weigh with a scale (e.g. A 100 g : B 50 g, A 200 g : B 100 g). Mix only the quantity that can be applied in time.
Mixing	Stir for at least 1 full minute until completely uniform, including the base and sides of the container — inadequately mixed material will not cure.
Working time	Approx. 15 minutes per mixed batch. Never mix the full kit at once; material that cannot be applied in time is lost.
Application	Brush or roller. A 4-inch foam or short-nap roller is recommended for the smoothest finish. Apply a minimum of 1–2 coats; additional coats for porous or heavy-duty surfaces.
Recoat interval	Approx. 6 hours between coats. Durability scales with film thickness — for exterior timber and heavy-duty service, apply additional coats to build a thick film (accepting the amber yellowing).
Ready for use	Minimum 6 hours after the final coat; allow longer before immersion or heavy-load service
Coverage	Approx. 5 m ² per kg of mixed material at 2 coats, applied by roller (1 kg ≈ 5 m ² · 2.5 kg ≈ 12.5 m ² · 5 kg ≈ 25 m ²). Brush application increases consumption. On absorbent substrates (raw concrete, bare timber) apply a thin first coat to seal the surface — otherwise coverage is significantly reduced.
Appearance	High-gloss amber film. The film yellows significantly under sustained UV exposure. A topcoat (e.g. a PU floor finish) is recommended for this product in service. For a non-yellowing clear finish on timber, use LucernaPro CrystalSeal instead.
Packaging	1 kg, 2.5 kg and 5 kg kits (Part A + Part B pre-measured)
Tool cleaning	Clean tools with thinner immediately after use; cured material cannot be removed.
Shelf life	Opened material: reseal tightly and avoid air contact — approx. 3 months

APPLICATION

1. Surface preparation: the substrate must be clean and dry with minimal dust; remove oil, grease and any loose or flaking material. Fill all cracks and holes flush before coating — the coating cannot compensate for unrepaired defects. 2. Weigh Part A and Part B at 2 : 1 and mix for at least 1 minute until fully uniform. 3. Apply by brush or roller within 15 minutes of mixing, maintaining a continuous film; a 4-inch foam or short-nap roller gives the smoothest result. 4. Recoat after approx. 6 hours; apply at least 1–2 coats. 5. Allow a minimum of 6 hours after the final coat before returning the surface to service. 6. Clean all tools with thinner immediately.

USE AS AN ADHESION PRIMER

Marine Guard may be used as an adhesion primer on glazed floor tile and on concrete prior to PU floor-coating systems. Apply one thin, continuous coat of mixed material, allow approx. 6 hours, then apply the finish system. The primer coat seals the substrate and improves the adhesion of the subsequent coating, reducing the risk of delamination.

USE AS A MOISTURE BARRIER

Rising moisture from the substrate is a leading cause of blistering, cracking and delamination of floor coatings and floor coverings. Applied as a continuous, pinhole-free film in a minimum of 2 coats, Marine Guard acts as a moisture barrier on concrete floors prior to the application of finish coatings or coverings. Film continuity and thickness are critical to barrier performance — thin or discontinuous films will not perform this function. The product has not been tested to a specific vapor-permeance standard; for critical applications, carry out a site trial first.

HEALTH & SAFETY

Before cure, the components may cause skin and eye irritation. Wear protective gloves and eye protection during mixing and application, and ensure adequate ventilation. Keep out of reach of children. Refer to the GHS pictograms on the product label and the Safety Data Sheet. For professional and DIY use.