

PRODUCT DESCRIPTION

BoundGravel is a two-component, high-performance polymer binder engineered for resin-bound gravel surfacing ("European-style" stone floors) without any cement. The mixed binder is blended with washed, fully dry decorative aggregate and trowelled directly onto the substrate in a single operation. The system is based on a polyaminoamide curing technology powered by Huntsman Advanced Materials, with a 100% solids formulation — no solvent is added. The cured matrix is tough yet flexible, bonding every stone into a seamless, water-permeable surface with high resistance to cracking at a layer thickness of approximately 10 mm.

KEY DATA

Chemistry	Two-component polymer binder / polyaminoamide curing system
Solids content	100% solids — no added solvent
Mix ratio (A : B)	2 : 1 — e.g. 1 kg mixed binder = Part A 666 ml : Part B 333 ml. Mix Part A and Part B thoroughly before adding aggregate.
Binder : aggregate	1 kg mixed binder per 20 kg aggregate (e.g. 500 ml binder per 10 kg aggregate for smaller batches). Binder content may be increased for higher durability; avoid excess causing pooling.
Working time	Approx. 15 minutes per mixed batch — mix only the quantity that can be placed in time. Never mix the full kit at once.
Layer thickness	Approx. 10 mm with No. 5 washed-gravel aggregate (approx. 2–3 mm grain)
Coverage	2.5 kg kit + 50 kg aggregate ≈ 3–4 m² · 5 kg kit + 100 kg aggregate ≈ 8–10 m² (at approx. 10 mm)
Initial set	Approx. 4 hours
Ready for use	After 24 hours minimum
Orientation	Horizontal surfaces only — the system cannot be applied vertically
Packaging	2.5 kg and 5 kg kits (Part A + Part B pre-measured)
Tool cleaning	Clean tools immediately after use with a lubricant spray (e.g. Sonax); do not allow the binder to cure on tools
Shelf life	Opened material: reseal tightly, avoid air contact — approx. 3 months

AGGREGATE SELECTION & PREPARATION

Use washed decorative gravel, standard No. 5 grade (approx. 2–3 mm). Any aggregate size may be used, but larger stones increase the required layer thickness and reduce coverage. Do not use white aggregate — it will yellow under sunlight; golden-yellow and black tones are recommended. Aggregate preparation is the single most important factor in system performance: wash the aggregate thoroughly to remove dust, then allow it to dry completely. Wet or damp aggregate must never be used.

APPLICATION

1. Mix Part A and Part B at 2 : 1 until fully uniform, in batch sizes matched to your working speed. 2. Gradually add the aggregate and blend until every stone is evenly coated. 3. Lubricate the trowel with a spray such as Sonax and trowel the mix to approx. 10 mm, levelling to an even finish. Place each batch within 15 minutes of mixing and do not leave mixed material standing in the sun. 4. For maximum durability, brush an additional coat of mixed binder over the finished surface. 5. Clean all tools immediately.

HEALTH & SAFETY

Before cure, the components may cause skin and eye irritation. Wear protective gloves and eye protection during mixing and application, and ensure adequate ventilation. Keep out of reach of children. Refer to the GHS pictograms on the product label and the Safety Data Sheet. For professional and DIY exterior use.