

PRODUCT DESCRIPTION

IronLock is a single-component, ready-to-use water-based anti-corrosive coating for steel and coated-steel substrates. It is built around an active anti-corrosive pigment sourced from a United States specialty-chemicals producer — chosen in place of the zinc-based inhibitive pigments in common use because it is not classified as toxic and not classified as hazardous to the aquatic environment — dispersed in a waterborne binder system. It is formulated to bond directly to substrates that conventional anti-corrosive paints handle poorly, including hot-dip galvanised steel, zinc sheet and metal roofing sheet, and needs no separate primer. The dried film is low in odour, tolerates standing water, and acts both as a corrosion barrier and as a renewable wear layer on surfaces under continuous water flow such as gutters. It is not intended for use over active rust.

KEY DATA

Chemistry	Single-component waterborne coating with an active anti-corrosive pigment (US-sourced)
Supplied form	Ready to use — stir thoroughly before use; do not thin with water
Colours	White · Grey · Black
Substrates	Steel, sheet steel, structural sections, galvanised steel, zinc sheet, roofing sheet
Primer	None required — direct-to-metal
Application	Brush, roller or spray — thin, even coats
Coats	2 coats standard; apply the second coat cross-wise to the first
Overcoating interval	30–60 minutes, ambient-dependent — overcoat once dry to the touch
Coverage	1 kg » approx. 5 m ² over 2 coats on smooth substrates (4.5 kg » approx. 22 m ²). Open sections — railings, fences, gratings, lattice — consume substantially more
Service exposure	Interior and exterior; tolerates standing water once fully dry
Tool cleaning	Water, immediately while the coating is still wet
Packaging	1 kg · 4.5 kg
Storage	Sealed original container, dry, 10–30 °C — protect from frost, do not allow to freeze
Shelf life	12 months unopened

NOTE ON VALUES

Coverage assumes smooth, non-absorbent substrates at normal film build. Profiled roofing sheet, previously corroded steel and open sections such as fences and gratings consume significantly more, because the true surface area is several times the area the eye estimates. Figures here are typical guidance only, not a specification.

APPLICATION NOTES

- Assess the substrate first. IronLock is a protective coating, not a rust treatment — it is not designed to be applied over active rust.
- Rust must be removed or converted first. Loose scale must always come off mechanically; where full mechanical cleaning is impractical — structural steel, large frameworks — convert the remaining rust with a rust converter and let it dry before coating.
- Degrease new material. New steel, galvanised steel and roofing sheet normally carry an invisible mill oil or anti-corrosion film from the factory — the most common single cause of coating failure. Clean with a degreaser or soapy water, rinse and dry fully.
- Stir thoroughly from the bottom of the pack until colour and consistency are uniform — inadequate stirring leaves the anti-corrosive pigment sitting in the bottom.
- Apply thin, even coats rather than one heavy coat, especially on round sections, corners, welds and fastener heads — the points where film thins and where corrosion starts first.
- Do not apply if rain is expected within a few hours, onto wet or dew-covered surfaces, or onto roofing sheet hot in direct sun — the film dries too fast to flow out evenly.
- On rainwater gutters, coat the full run inside and out — the inner face is where water, silt and leaf litter attack the substrate first. Avoid water, abrasion and heavy loads for the first 24 hours.

HEALTH & SAFETY

Water-based and low in odour, but this is an industrial coating. Wear gloves and eye protection, avoid prolonged skin contact, and ventilate when spraying. Keep out of reach of children. Do not empty into drains or waterways. Refer to the Safety Data Sheet for full information.

Lucerna Co., Ltd. · 23 Suriyat Rd. Soi 4, Nai Mueang, Mueang, Ubon Ratchathani 34000, Thailand
Tel 062-005-7933 · Lucernapro@yahoo.com · www.lucernapro.com

The information herein is given in good faith based on our current knowledge and practical experience. Coverage and drying behaviour depend on substrate and site conditions; values are typical guidance only and do not constitute a specification. Users must verify suitability for their intended application. Made in Thailand.