

PRODUCT DESCRIPTION

SchutzFirearm is a one-component polysilazane ceramic coating for the exterior protection of firearms, applied by the wipe-on, wipe-off method. On curing, the liquid converts to a dense ceramic network of Si–N–Si and Si–O–Si bonds anchored to the metal — a permanent micron-thin barrier, not an oil film that evaporates or wipes away. The cured surface is dry to the touch and matte: it sheds water, resists cleaning chemicals and heat, reduces glare, and gives a firmer grip than an oiled surface — the exterior no longer needs rust-preventive oil at all. Consumption is remarkably low: 2–3 drops coat an entire handgun. The chemistry comes from industrial thin-film ceramic coating work; protecting a firearm is a small task for it.

KEY DATA

Type	One-component polysilazane ceramic coating — wipe on, wipe off
Substrates	Steel, plastic and polymer frames — exterior surfaces
Finish	Matte, glare-reducing, dry to the touch; micron-thin — does not alter part dimensions when applied thin and wiped off
Consumption	2–3 small drops per handgun, applied from a coating foam — never dropped onto the firearm directly
Flash time	Wipe off excess after at least 2 minutes and no later than 5 — time it, do not guess. Past 5 minutes the film hardens and is very difficult to remove.
Cure	Initial 24 hours dry, no water contact · full cure 7 days — full hardness, chemical and heat resistance develop only after this
Pack size	10 ml bottle
Bottle care	Reseal immediately after use — the coating cures with moisture in the air, and a bottle left open hardens in the bottle
Storage	Tightly closed, cool, dry and shaded, away from heat and ignition sources. Keep out of reach of children.

MEASURED PROPERTIES — AFTER 7-DAY FULL CURE

Pencil hardness	4H
Water contact angle	> 100° — hydrophobic; water beads and rolls off
Heat resistance	Up to 400 °C after full cure
Chemical resistance	Acids, alkalis, solvents and common cleaning agents; UV-stable outdoors
Abrasion	Withstands normal handling and holster wear

APPLICATION

Degrease completely first — the ceramic film cannot bond over oil; wash off all rust-preventive oil and leave the surface clean and dry. Place 2–3 drops on the coating foam and spread thinly; coverage is all that is needed — a thicker film protects no better, it only streaks and hardens into residue. Work one section at a time (slide, frame, small parts) to keep the wipe timing easy. After 2–5 minutes, buff the excess off with a microfiber cloth in circular strokes until uniform, leaving no residue. Cure 24 hours dry; full protection arrives at 7 days.

LIMITATIONS

The coating prevents — it does not reverse. Existing rust is not removed and existing wear marks are not filled; the worn front slide edges of any well-used firearm are only partially masked, though protected well against further wear. Do not coat the bore or internal slide parts unless certain — toleranced components are not worth the risk; when in doubt, skip them. The internal mechanism still requires its normal lubrication; only the exterior is freed from oil.

HEALTH & SAFETY

Solvent-borne and flammable. Use only with good ventilation, away from flames, sparks and smoking; the coating releases vapour while drying and curing. Wear gloves and avoid contact with skin and eyes; wash skin with soap and water. Do not ingest. Keep away from moisture until applied. Keep out of reach of children. Dispose of residues in accordance with local regulations.